



PVC U 65x2000 mm rörd

Artikelnr P2202199

Beständig

Delvis beständig

Ej beständig

Kemikalie	Koncentration	Temp.	Beständighet
1,4-Dioxane	100%	20 Å°C	
2-Hydroxypropionic acid (lactic acid)	90%	20 Å°C	
Acetic acid	100%	20 Å°C	
Acetone	100%	20 Å°C	
Ammonia	conc.	20 Å°C	
Ammonium chloride	â€”	20 Å°C	
Amyl alcohol	â€”	20 Å°C	
Apple juice	â€”	20 Å°C	
Benzene	â€”	20 Å°C	
Bleaching solution	12.5 cl	20 Å°C	
Boric acid	100%	20 Å°C	
Brake fluid	â€”	20 Å°C	
Butyl acetate	â€”	20 Å°C	
Calcium chloride	â€”	20 Å°C	
Carbon disulphide	100%	20 Å°C	
Carbon tetrachloride	â€”	20 Å°C	
Chlorine (gas)	100%	20 Å°C	
Chlorobenzene	100%	20 Å°C	
Chloroform	â€”	20 Å°C	
Citric acid	10%	20 Å°C	
Cresol	â€”	20 Å°C	
Cyclohexanone	100%	20 Å°C	
Cyclohexene	100%	20 Å°C	
Diesel	â€”	20 Å°C	
Diethylene oxide	â€”	20 Å°C	
Ethyl acetate	100%	20 Å°C	
Ethyl alcohol (ethanol)	96%	20 Å°C	

Kemikalie	Koncentration	Temp.	Best�ndighet
Ethylene chloride	100%	20 ��C	�
Food oil	��	20 ��C	�
Formaldehyde (aqueous)	40%	20 ��C	�
Formic acid	10%	20 ��C	�
Frost protection agent	��	20 ��C	�
Fuel (aromatic free)	��	20 ��C	�
Fuel oil	��	20 ��C	�
Glycerine	100%	20 ��C	�
Glycol	100%	20 ��C	�
Heptane	100%	20 ��C	�
Hydrochloric acid	10%	20 ��C	�
Hydrochloric acid (concentrated)	conc.	20 ��C	�
Hydrofluoric acid	40%	20 ��C	�
Hydrogen peroxide	10%	20 ��C	�
Hydrogen sulfide (aqueous)	��	20 ��C	�
Isopropyl alcohol	100%	20 ��C	�
Linseed oil	��	20 ��C	�
Mercurochrome	��	20 ��C	�
Methyl alcohol (methanol)	100%	20 ��C	�
Methyl ethyl ketone (MEK)	100%	20 ��C	�
Methylene chloride	100%	20 ��C	�
Milk	��	20 ��C	�
Mineral oils (aromatic free)	��	20 ��C	�
Nitric acid	50%	20 ��C	�
Nitric acid	10%	20 ��C	�
Nitrobenzene	��	20 ��C	�
Oxalic acid	��	20 ��C	�
Ozone (gas)	��� 0.5 ppm	20 ��C	�
Paraffin oil	100%	20 ��C	�
Perchloroethylene	��	20 ��C	�
Petroleum	100%	20 ��C	�
Petroleum ether	100%	20 ��C	�
Phenol (aqueous)	ca. 9%	20 ��C	�
Phosphoric acid	50%	20 ��C	�
Potassium hydroxide solution	50%	20 ��C	�

