

PC 3000x500x12 mm transparente

Artikelnr P1002727

Beständig

Delvis beständig

Ej beständig

Kemikalie	Concentration	Temp.	Beständighet
1,4-Dioxane	100%	20 Å°C	
2-Hydroxypropionic acid (lactic acid)	90%	20 Å°C	
Acetic acid	100%	20 Å°C	
Acetone	100%	20 Å°C	
Ammonia	conc.	20 Å°C	
Ammonium chloride	â€”	20 Å°C	
Apple juice	â€”	20 Å°C	
Benzene	â€”	20 Å°C	
Bleaching solution	12.5 cl	20 Å°C	
Boric acid	100%	20 Å°C	
Butyl acetate	â€”	20 Å°C	
Calcium chloride	â€”	20 Å°C	
Carbon disulphide	100%	20 Å°C	
Carbon tetrachloride	â€”	20 Å°C	
Chlorine (gas)	100%	20 Å°C	
Chlorobenzene	100%	20 Å°C	
Chloroform	â€”	20 Å°C	
Citric acid	10%	20 Å°C	
Cresol	â€”	20 Å°C	
Cyclohexanone	100%	20 Å°C	
Cyclohexene	100%	20 Å°C	
Diesel	â€”	20 Å°C	
Diethylene oxide	â€”	20 Å°C	
Ethyl acetate	100%	20 Å°C	
Ethyl alcohol (ethanol)	96%	20 Å°C	
Ethylene chloride	100%	20 Å°C	
Food oil	â€”	20 Å°C	

Kemikalie	Concentraci3n	Temp.	Best3ndighet
Formaldehyde, aqueous	40%	20 3C	
Formic acid	10%	20 3C	
Frost protection agent	3C	20 3C	
Fuel oil	3C	20 3C	
Fuel, aromatic free	3C	20 3C	
Glycerine	100%	20 3C	
Glycol	100%	20 3C	
Heptane	100%	20 3C	
Hydrochloric acid	10%	20 3C	
Hydrochloric acid (concentrated)	conc.	20 3C	
Hydrofluoric acid	40%	20 3C	
Hydrogen peroxide	10%	20 3C	
Hydrogen sulfide, aqueous	3C	20 3C	
Isopropyl alcohol	100%	20 3C	
Linseed oil	3C	20 3C	
Mercurochrome	3C	20 3C	
Methyl alcohol (methanol)	100%	20 3C	
Methyl ethyl ketone (MEK)	100%	20 3C	
Methylene chloride	100%	20 3C	
Milk	3C	20 3C	
Nitric acid (10%)	10%	20 3C	
Nitric acid (50%)	50%	20 3C	
Nitrobenzene	3C	20 3C	
Oxalic acid	3C	20 3C	
Ozone (gas)	3C 0.5 ppm	20 3C	
Paraffin oil	100%	20 3C	
Perchloroethylene	3C	20 3C	
Petroleum	100%	20 3C	
Petroleum ether	100%	20 3C	
Phenol, aqueous	ca. 9%	20 3C	
Phosphoric acid	50%	20 3C	
Potassium hydroxide solution	50%	20 3C	
Premium fuel	3C	20 3C	
Propyl alcohol	3C	20 3C	
Pyridine	3C	20 3C	

Kemikalie	Concentration	Temp.	Beständighet
Silicone oil	â€”	20 Å°C	●
Sodium carbonate, aqueous	â€”	20 Å°C	●
Sodium chloride, aqueous	â€”	20 Å°C	●
Sodium hydrogen sulfite	â€”	20 Å°C	●
Sodium hydroxide solution (15%)	15%	20 Å°C	●
Sodium hydroxide solution (60%)	60%	20 Å°C	●
Sodium nitrate, aqueous	â€”	20 Å°C	●
Sulphuric acid	96%	20 Å°C	●
Tetrahydrofuran (THF)	100%	20 Å°C	●
Toluene	100%	20 Å°C	●
Trichloroethylene	100%	20 Å°C	●
Vinegar, standard	5-10%	20 Å°C	●
Water	â€”	20 Å°C	●
Xylene	â€”	20 Å°C	●