

PC 3000x610x70 mm transparente

Artikelnr P1002748

1. Tekniskt datablad

Egenskap	Värde	Enhet	Standard
Densidad	1.2	g/cm ³	ISO 1183
Lımite de resistencia a la tracci3n	75	MPa	ISO 527
M3dulo de elasticidad (tracci3n)	2400	MPa	ISO 527-2
Resistencia a la tensi3n	60	MPa	
Deformaci3n a la rotura	50	%	ISO 527-2
Punto de fusi3n	160	C	ISO 3146
Temperatura de servicio m3xima (corto plazo)	119	C	UL746B
Temperatura de funcionamiento m3xima	113.75	C	
Temperatura m3nima	-54	C	UL746B
Deformaci3n t3rmica (HDT/A)	130	C	ISO 75-2
Deformaci3n t3rmica (HDT/B)	140	C	ISO 75
Temperatura de ablandamiento Vicat (VST/B/50)	150	C	ISO 306
Fuerza diel3ctrica	29	kV/mm	IEC 60243-1
Resistividad volum3trica	10AA ³	Ccm	IEC 60093
Constante diel3ctrica (1 MHz)	2.98	-	IEC 60250
Constante diel3ctrica (100 Hz)	3	-	IEC 60250
Factor de p3rdida diel3ctrica (1 MHz)	0.0	-	IEC 60250
Factor de p3rdida diel3ctrica (100 Hz)	0.0	-	IEC 60250
Clasificaci3n de resistencia al fuego (UL 94)	0		UL 94
Resistencia a la flexi3n	2400	MPa	ISO 178
Conductividad t3rmica	0.21	W/(mK)	DIN 52612
Resistencia superficial	10A	C	IEC 60093
ndice de seguimiento comparativo (CTI)	279.2	V	IEC 60112
Absorci3n de agua hasta la saturaci3n	0.15	%	ISO 62
Absorci3n de agua hasta la saturaci3n	0.35	%	ISO 62
Resistencia al impacto con entalla (Charpy)	9	kJ/m ²	ISO 179/1eA

Egenskap	V�rde	Enhet	Standard
Coeficiente de expansi�n t�rmica	0.65	10��/K	DIN 11359
Dureza Shore D	85	� Shore D	ISO 868
Dureza a la presi�n de bala	120	MPa	ISO 2039-1

2. Kemisk best ndighet

● Best ndig
 ● Delvis best ndig
 ● Ej best ndig

Kemikalie	Konc.	Resultat
1,4-Dioxane	100%	●
2-Hydroxypropionic acid (lactic acid)	90%	●
Acetic acid	100%	●
Acetone	100%	●
Ammonia	conc.	●
Ammonium chloride	��	●
Apple juice	��	●
Benzene	��	●
Bleaching solution	12.5 cl	●
Boric acid	100%	●
Butyl acetate	��	●
Calcium chloride	��	●
Carbon disulphide	100%	●
Carbon tetrachloride	��	●
Chlorine (gas)	100%	●
Chlorobenzene	100%	●
Chloroform	��	●
Citric acid	10%	●
Cresol	��	●
Cyclohexanone	100%	●
Cyclohexene	100%	●
Diesel	��	●
Diethylene oxide	��	●
Ethyl acetate	100%	●
Ethyl alcohol (ethanol)	96%	●
Ethylene chloride	100%	●
Food oil	��	●
Formaldehyde, aqueous	40%	●

Kemikalie	Konc.	Resultat
Formic acid	10%	●
Frost protection agent	â€”	●
Fuel oil	â€”	●
Fuel, aromatic free	â€”	●
Glycerine	100%	●
Glycol	100%	●
Heptane	100%	●
Hydrochloric acid	10%	●
Hydrochloric acid (concentrated)	conc.	●
Hydrofluoric acid	40%	●
Hydrogen peroxide	10%	●
Hydrogen sulfide, aqueous	â€”	●
Isopropyl alcohol	100%	●
Linseed oil	â€”	●
Mercurochrome	â€”	●
Methyl alcohol (methanol)	100%	●
Methyl ethyl ketone (MEK)	100%	●
Methylene chloride	100%	●
Milk	â€”	●
Nitric acid (10%)	10%	●
Nitric acid (50%)	50%	●
Nitrobenzene	â€”	●
Oxalic acid	â€”	●
Ozone (gas)	â‰ƒ 0.5 ppm	●
Paraffin oil	100%	●
Perchloroethylene	â€”	●
Petroleum	100%	●
Petroleum ether	100%	●
Phenol, aqueous	ca. 9%	●
Phosphoric acid	50%	●
Potassium hydroxide solution	50%	●
Premium fuel	â€”	●
Propyl alcohol	â€”	●
Pyridine	â€”	●

Kemikalie	Konc.	Resultat
Silicone oil	â€”	●
Sodium carbonate, aqueous	â€”	●
Sodium chloride, aqueous	â€”	●
Sodium hydrogen sulfite	â€”	●
Sodium hydroxide solution (15%)	15%	●
Sodium hydroxide solution (60%)	60%	●
Sodium nitrate, aqueous	â€”	●
Sulphuric acid	96%	●
Tetrahydrofuran (THF)	100%	●
Toluene	100%	●
Trichloroethylene	100%	●
Vinegar, standard	5-10%	●
Water	â€”	●
Xylene	â€”	●