



PE-500 2000x1000x60 mm gris

Artikelnr P1400408

Beständig

Delvis beständig

Ej beständig

Kemikalie	Concentration	Temp.	Beständighet
1,4-Dioxane	100%	20 °C	
2-Hydroxypropionic Acid	90%	20 °C	
Acetaldehyde	â€”	20 °C	
Acetic Acid	100%	20 °C	
Acetic acid	100%	20 °C	
Acetic acid	3%	100 °C	
Acetic acid	3% w/w	20 °C	
Acetic acid	3%	100 °C	
Acetic acid	3%	100 °C	
Acetic acid, aqueous	70%	20 °C	
Acetic anhydride	â€”	20 °C	
Acetone	â€”	20 °C	
Acetone	100%	20 °C	
Acronal dispersions	â€”	20 °C	
Acrylonitrile	â€”	20 °C	
Allyl acetate	â€”	20 °C	
Allyl alcohol	96%	20 °C	
Allyl chloride	â€”	20 °C	
Aluminium chloride, aqueous	any	20 °C	
Aluminium chloride, solid	â€”	20 °C	
Aluminium fluoride	Conc.	20 °C	
Aluminium hydroxide	â€”	20 °C	
Aluminium metaphosphate	â€”	20 °C	
Aluminium sulphate, aqueous saturated	â€”	20 °C	
Aluminium sulphate, solid	â€”	20 °C	
Ammonia	concentrated	20 °C	
Ammonia, gaseous	â€”	20 °C	

Kemikalie	Concentration	Temp.	Beständighet
Ammonia, liquid	â€”	20 Å°C	●
Ammonium Chloride	â€”	20 Å°C	●
Amyl Alcohol	â€”	20 Å°C	●
Aniline	any	20 Å°C	●
Anisole	â€”	20 Å°C	●
Apple Juice	â€”	20 Å°C	●
Aqua regia	â€”	20 Å°C	●
Beer	â€”	20 Å°C	●
Benzaldehyde, aqueous	any	20 Å°C	●
Benzene	technically grade	20 Å°C	●
Benzene	â€”	20 Å°C	●
Benzoic acid, aqueous	any	20 Å°C	●
Benzyl alcohol	â€”	20 Å°C	●
Bitumen	â€”	20 Å°C	●
Bleaching Solution	12.5 cl	20 Å°C	●
Boric Acid	100%	20 Å°C	●
Brake Fluid	â€”	20 Å°C	●
Bromine, liquid	100%	20 Å°C	●
Butanol, aqueous	any	20 Å°C	●
Butter	â€”	20 Å°C	●
Butyl Acetate	â€”	20 Å°C	●
Calcium Chloride	â€”	20 Å°C	●
Calcium carbonate	â€”	20 Å°C	●
Calcium carbonate	â€”	20 Å°C	●
Calcium hypochlorite, aqueous suspension	any	20 Å°C	●
Camphor	â€”	20 Å°C	●
Carbon Disulfide	100%	20 Å°C	●
Carbon Tetrachloride	â€”	20 Å°C	●
Carbon disulphide	â€”	20 Å°C	●
Caustic soda	any	20 Å°C	●
Chlorine (gas)	100%	20 Å°C	●
Chlorine, liquid	â€”	20 Å°C	●
Chloroacetic acid, aqueous	â‰¥85%	20 Å°C	●
Chlorobenzene	100%	20 Å°C	●

Kemikalie	Concentration	Temp.	Beständighet
Chlorobenzene	â€”	20 Å°C	●
Chloroform	technically grade	20 Å°C	●
Chloroform	â€”	20 Å°C	●
Chromosulphuric acid	â€”	20 Å°C	●
Cider	â€”	20 Å°C	●
Citric Acid	10%	20 Å°C	●
Citrus fruit juices	â€”	20 Å°C	●
Coconut oil	â€”	20 Å°C	●
Cod liver oil	â€”	20 Å°C	●
Cresol	â€”	20 Å°C	●
Cresol	100%	20 Å°C	●
Cyclohexane	â€”	20 Å°C	●
Cyclohexanol	â€”	20 Å°C	●
Cyclohexanone	100%	20 Å°C	●
Cyclohexanone	â€”	20 Å°C	●
Cyclohexene	100%	20 Å°C	●
Detergents	â€”	20 Å°C	●
Dibutyl ether	â€”	20 Å°C	●
Dibutyl phthalate	â€”	20 Å°C	●
Dichloroacetic acid	â€”	20 Å°C	●
Dichloroethane	â€”	20 Å°C	●
Diesel Fuel	â€”	20 Å°C	●
Diesel fuel	â€”	20 Å°C	●
Diethylene Oxide	â€”	20 Å°C	●
Diglycolic acid, aqueous	30%	20 Å°C	●
Dimethyl formamide	â€”	20 Å°C	●
Dimethylamine	â€”	20 Å°C	●
Dioxane	â€”	20 Å°C	●
Ethanol	10%	100 Å°C	●
Ethanol	10%	100 Å°C	●
Ethanol	10% v/v	20 Å°C	●
Ethanol	10%	100 Å°C	●
Ethyl Acetate	100%	20 Å°C	●
Ethyl Alcohol	96%	20 Å°C	●
Ethyl acetate	â€”	20 Å°C	●

Kemikalie	Concentration	Temp.	Beständighet
Ethylene Chloride	100%	20 Å°C	●
Ethylene alcohol	96%	20 Å°C	●
Ethylene chloride	â€”	20 Å°C	●
Ethylene diamine	â€”	20 Å°C	●
Ethylene glycol	â€”	20 Å°C	●
Ferric chloride, aqueous	any	20 Å°C	●
Ferric nitrate, aqueous saturated	â€”	20 Å°C	●
Ferric sulphate, aqueous saturated	â€”	20 Å°C	●
Ferrous (II) chloride, aqueous saturated	â€”	20 Å°C	●
Ferrous (II) sulfate, aqueous saturated	â€”	20 Å°C	●
Ferrous (III) chloride, aqueous saturated	â€”	20 Å°C	●
Ferrous (III) nitrate, aqueous saturated	â€”	20 Å°C	●
Ferrous (III) sulfate, aqueous saturated	â€”	20 Å°C	●
Food Oil	â€”	20 Å°C	●
Formaldehyde (aqueous)	40%	20 Å°C	●
Formaldehyde, aqueous	â‰ƒ40%	20 Å°C	●
Formic Acid	10%	20 Å°C	●
Formic acid, aqueous	85%	20 Å°C	●
Frigen 12 (Freon 12)	100%	20 Å°C	●
Frost Protection Agent	â€”	20 Å°C	●
Fruit juices	any	20 Å°C	●
Fuel (aromatic free)	â€”	20 Å°C	●
Fuel oil	â€”	20 Å°C	●
Furfural	â€”	20 Å°C	●
Glycerin, aqueous	any	20 Å°C	●
Glycerine	100%	20 Å°C	●
Glycol	100%	20 Å°C	●
Glykol, aqueous	as supplied	20 Å°C	●
Glysantin	â€”	20 Å°C	●
Heating Oil	â€”	20 Å°C	●
Heptane	100%	20 Å°C	●
Heptane	â€”	20 Å°C	●
Hexane	â€”	20 Å°C	●
Honey	â€”	20 Å°C	●
Hydrobromic acid, aqueous	50%	20 Å°C	●

Kemikalie	Concentration	Temp.	Beständighet
Hydrochloric Acid	10%	20 Å°C	●
Hydrochloric Acid (concentrated)	concentrated	20 Å°C	●
Hydrochloric acid, aqueous	any	20 Å°C	●
Hydrofluoric Acid	40%	20 Å°C	●
Hydrogen Peroxide	10%	20 Å°C	●
Hydrogen Sulfide (aqueous solution)	â€”	20 Å°C	●
Ink	â€”	20 Å°C	●
Iodine in potassium iodide solution	3% iodine	20 Å°C	●
Isooctane	â€”	20 Å°C	●
Isopropanol	â€”	20 Å°C	●
Isopropyl Alcohol	100%	20 Å°C	●
Isopropyl ether	â€”	20 Å°C	●
Jam	â€”	20 Å°C	●
Kerosene	â€”	20 Å°C	●
Linseed Oil	â€”	20 Å°C	●
Linseed oil	technically grade	20 Å°C	●
Lithium bromide	â€”	20 Å°C	●
Magnesium stearate	â€”	20 Å°C	●
Magnesium stearate	â€”	20 Å°C	●
Maleic acid, aqueous	any	20 Å°C	●
Menthol	â€”	20 Å°C	●
Mercurochrome	â€”	20 Å°C	●
Mercury	â€”	20 Å°C	●
Methanol	technically grade	20 Å°C	●
Methyl Alcohol	100%	20 Å°C	●
Methyl Ethyl Ketone (MEK)	100%	20 Å°C	●
Methyl chloride	gaseous, technically grade	20 Å°C	●
Methyl ethyl ketone	technically grade	20 Å°C	●
Methylene Chloride	100%	20 Å°C	●
Milk	â€”	20 Å°C	●
Milk	â€”	20 Å°C	●
Mineral Oil (aromatic free)	â€”	20 Å°C	●
Molasses	â€”	20 Å°C	●
Motor oil (heavy duty oil) without additives	â€”	20 Å°C	●

Kemikalie	Concentraci3n	Temp.	Best4ndigheit
Naphtha	â€”	20 4C	●
Naphthalene	â€”	20 4C	●
Nitric Acid	10%	20 4C	●
Nitric Acid (50%)	50%	20 4C	●
Nitric acid, aqueous	50%	20 4C	●
Nitric acid, aqueous	25%	20 4C	●
Nitrobenzene	â€”	20 4C	●
Nitrobenzene	â€”	20 4C	●
Oils, ethereal	â€”	20 4C	●
Oils, vegetable and animal	â€”	20 4C	●
Oleic acid	â€”	20 4C	●
Oleum	any	20 4C	●
Olive oil	â€”	100 4C	●
Olive oil	â€”	100 4C	●
Olive oil	â€”	20 4C	●
Olive oil	â€”	100 4C	●
Oxalic Acid	â€”	20 4C	●
Oxalic acid, aqueous	any	20 4C	●
Oxygen	â€”	20 4C	●
Ozone	50 ppm	20 4C	●
Ozone Gas	â‰‰0.5 ppm	20 4C	●
Paraffine Oil	100%	20 4C	●
Perchloric acid, aqueous	70%	20 4C	●
Perchloric acid, aqueous	20%	20 4C	●
Perchloric acid, aqueous	50%	20 4C	●
Perchloroethylene	â€”	20 4C	●
Petroleum	100%	20 4C	●
Petroleum	â€”	20 4C	●
Petroleum Ether	100%	20 4C	●
Petroleum ether	â€”	20 4C	●
Phenol	â€”	20 4C	●
Phenol (aqueous)	â‰‰9%	20 4C	●
Phosphoric Acid	50%	20 4C	●
Phosphoric acid, aqueous	80% L 95%	20 4C	●

Kemikalie	Concentraci3n	Temp.	Best4ndighet
Phosphoric acid, aqueous	50%	20 4C	●
Phosphorus trichloride	4C	20 4C	●
Photographic developers	4C	20 4C	●
Photographic emulsions	as supplied	20 4C	●
Photographic fixing baths	as supplied	20 4C	●
Phthalic acid, aqueous	50%	20 4C	●
Polyester resins	4C	20 4C	●
Potassium Hydroxide liquor	50%	20 4C	●
Premium Fuel	4C	20 4C	●
Propionic acid, aqueous	any	20 4C	●
Propyl Alcohol	4C	20 4C	●
Pyridine	4C	20 4C	●
Pyridine	4C	20 4C	●
Sea water	4C	20 4C	●
Silicon dioxide	4C	20 4C	●
Silicon dioxide	4C	20 4C	●
Silicone Oil	4C	20 4C	●
Silicone oil	technically grade	20 4C	●
Sodium Carbonate (aqueous)	4C	20 4C	●
Sodium Chloride (aqueous)	4C	20 4C	●
Sodium Hydrogen Sulfite	4C	20 4C	●
Sodium Hydroxide liquor	15%	20 4C	●
Sodium Hydroxide liquor (60%)	60%	20 4C	●
Sodium Nitrate (aqueous)	4C	20 4C	●
Sodium Thiosulfate	4C	20 4C	●
Sodium borate	4C	20 4C	●
Sodium bromide	4C	20 4C	●
Sodium hydroxide, aqueous	any	20 4C	●
Sodium hydroxide, solid	4C	20 4C	●
Stearic acid	4C	20 4C	●
Sugar syrup	4C	20 4C	●
Sulfuric Acid	96%	20 4C	●
Sulphuric acid, aqueous	70%	20 4C	●
Sulphuric acid, aqueous	80%	20 4C	●
Sulphuric acid, aqueous	98%	20 4C	●

Kemikalie	Concentration	Temp.	Beständighet
Sulphuric acid, aqueous	~50%	20 °C	●
Tallow	technically grade	20 °C	●
Tannic acid (tannin), aqueous	10%	20 °C	●
Tetrahydrofuran	technically grade	20 °C	●
Tetrahydrofuran (THF)	100%	20 °C	●
Thionyl chloride	~	20 °C	●
Thiophene	~	20 °C	●
Tin (II) chloride, aqueous	any	20 °C	●
Tin (IV) chloride, aqueous	saturated	20 °C	●
Titanium dioxide	~	20 °C	●
Titanium dioxide	~	20 °C	●
Toluene	technically grade	20 °C	●
Toluene	100%	20 °C	●
Transformer Oil	~	20 °C	●
Transformer oil (insulating oil)	technically grade	20 °C	●
Trichloroacetic acid	technically grade	20 °C	●
Trichloroethylene	technically grade	20 °C	●
Trichloroethylene	100%	20 °C	●
Triethanolamine	~	20 °C	●
Triethanolamine	~	20 °C	●
Turpentine oil	technically grade	20 °C	●
Urea, aqueous	~33%	20 °C	●
Vaseline	technically grade	20 °C	●
Vinegar (standard)	5-10%	20 °C	●
Washing up liquids	usual	20 °C	●
Water	~	20 °C	●
Water, distilled	~	20 °C	●
Wine	~	20 °C	●
Xylene	~	20 °C	●
Xylene	~	20 °C	●
Zinc sludge	~	20 °C	●