



PEEK Mod 190/110x3000 mm negro

Artikelnr P1501272

Beständig Delvis beständig Ej beständig

Kemikalie	Concentraci3n	Temp.	Beständighet
1,4-Dioxane	100	20 Å°C	
2-Hydroxypropionic acid (lactic acid)	90	20 Å°C	
Acetic acid	100	20 Å°C	
Acetone	100	20 Å°C	
Ammonia	â€	20 Å°C	
Ammonium chloride	â€	20 Å°C	
Amyl alcohol	â€	20 Å°C	
Apple juice	â€	20 Å°C	
Benzene	â€	20 Å°C	
Boric acid	100	20 Å°C	
Brake fluid	â€	20 Å°C	
Butyl acetate	â€	20 Å°C	
Calcium chloride	â€	20 Å°C	
Carbon tetrachloride	â€	20 Å°C	
Chlorine (gas)	100	20 Å°C	
Chlorobenzene	100	20 Å°C	
Chloroform	â€	20 Å°C	
Citric acid	10	20 Å°C	
Cyclohexanone	100	20 Å°C	
Cyclohexene	100	20 Å°C	
Diesel	â€	20 Å°C	
Diethylene oxide	â€	20 Å°C	
Ethyl acetate	100	20 Å°C	
Ethyl alcohol (ethanol)	96	20 Å°C	
Ethylene chloride	100	20 Å°C	
Food oil	â€	20 Å°C	
Formaldehyde (aqueous)	40	20 Å°C	

Kemikalie				
Concentraci3n		Temp.		Best3ndighet
Formic acid	10	20 3C		●
Frost protection agent	3C	20 3C		●
Fuel oil	3C	20 3C		●
Fuel, aromatic free	3C	20 3C		●
Glycerine	100	20 3C		●
Glycol	100	20 3C		●
Heptane	100	20 3C		●
Hydrochloric acid	10	20 3C		●
Hydrochloric acid (concentrated)	3C	20 3C		●
Hydrofluoric acid	40	20 3C		●
Hydrogen peroxide	10	20 3C		●
Hydrogen sulfide (aqueous)	3C	20 3C		●
Isopropyl alcohol	100	20 3C		●
Linseed oil	3C	20 3C		●
Mercurochrome	3C	20 3C		●
Methyl alcohol (methanol)	100	20 3C		●
Methyl ethyl ketone (MEK)	100	20 3C		●
Methylene chloride	100	20 3C		●
Milk	3C	20 3C		●
Mineral oils (aromatic free)	3C	20 3C		●
Nitric acid	50	20 3C		●
Nitric acid	10	20 3C		●
Nitrobenzene	3C	20 3C		●
Oxalic acid	3C	20 3C		●
Ozone (gas)	3C	20 3C		●
Paraffin oil	100	20 3C		●
Perchloroethylene	3C	20 3C		●
Petroleum	100	20 3C		●
Petroleum ether	100	20 3C		●
Phenol (aqueous)	9	20 3C		●
Phosphoric acid	50	20 3C		●
Potassium hydroxide solution	50	20 3C		●
Premium fuel	3C	20 3C		●
Propyl alcohol	3C	20 3C		●
Pyridine	3C	20 3C		●

Kemikalie	Concentration	Temp.	Beständighet
Silicone oil	â€”	20 Å°C	●
Sodium carbonate (aqueous)	â€”	20 Å°C	●
Sodium chloride (aqueous)	â€”	20 Å°C	●
Sodium hydrogen sulfite	â€”	20 Å°C	●
Sodium hydroxide solution (caustic soda)	60	20 Å°C	●
Sodium hydroxide solution (caustic soda)	15	20 Å°C	●
Sodium nitrate (aqueous)	â€”	20 Å°C	●
Sodium thiosulfate	â€”	20 Å°C	●
Sulphuric acid	96	20 Å°C	●
Tetrahydrofuran (THF)	100	20 Å°C	●
Toluene	100	20 Å°C	●
Transformer oil	â€”	20 Å°C	●
Trichloroethylene	100	20 Å°C	●
Vinegar (standard)	5-10	20 Å°C	●
Water	â€”	20 Å°C	●
Xylene	â€”	20 Å°C	●