



PEEK Mod 200/140x3000 mm negro

Artikelnr P1501281

Beständig

Delvis beständig

Ej beständig

Kemikalie	Concentration	Temp.	Beständighet
1,4-Dioxane	100	20 Å°C	
2-Hydroxypropionic acid (lactic acid)	90	20 Å°C	
Acetic acid	100	20 Å°C	
Acetone	100	20 Å°C	
Ammonia	â€”	20 Å°C	
Ammonium chloride	â€”	20 Å°C	
Amyl alcohol	â€”	20 Å°C	
Apple juice	â€”	20 Å°C	
Benzene	â€”	20 Å°C	
Boric acid	100	20 Å°C	
Brake fluid	â€”	20 Å°C	
Butyl acetate	â€”	20 Å°C	
Calcium chloride	â€”	20 Å°C	
Carbon tetrachloride	â€”	20 Å°C	
Chlorine (gas)	100	20 Å°C	
Chlorobenzene	100	20 Å°C	
Chloroform	â€”	20 Å°C	
Citric acid	10	20 Å°C	
Cyclohexanone	100	20 Å°C	
Cyclohexene	100	20 Å°C	
Diesel	â€”	20 Å°C	
Diethylene oxide	â€”	20 Å°C	
Ethyl acetate	100	20 Å°C	
Ethyl alcohol (ethanol)	96	20 Å°C	
Ethylene chloride	100	20 Å°C	
Food oil	â€”	20 Å°C	
Formaldehyde (aqueous)	40	20 Å°C	

Kemikalie		Concentraci3n	Temp.	Best3ndighet
Formic acid	10	20 3C		
Frost protection agent	3"	20 3C		
Fuel oil	3"	20 3C		
Fuel, aromatic free	3"	20 3C		
Glycerine	100	20 3C		
Glycol	100	20 3C		
Heptane	100	20 3C		
Hydrochloric acid	10	20 3C		
Hydrochloric acid (concentrated)	3"	20 3C		
Hydrofluoric acid	40	20 3C		
Hydrogen peroxide	10	20 3C		
Hydrogen sulfide (aqueous)	3"	20 3C		
Isopropyl alcohol	100	20 3C		
Linseed oil	3"	20 3C		
Mercurochrome	3"	20 3C		
Methyl alcohol (methanol)	100	20 3C		
Methyl ethyl ketone (MEK)	100	20 3C		
Methylene chloride	100	20 3C		
Milk	3"	20 3C		
Mineral oils (aromatic free)	3"	20 3C		
Nitric acid	50	20 3C		
Nitric acid	10	20 3C		
Nitrobenzene	3"	20 3C		
Oxalic acid	3"	20 3C		
Ozone (gas)	3"	20 3C		
Paraffin oil	100	20 3C		
Perchloroethylene	3"	20 3C		
Petroleum	100	20 3C		
Petroleum ether	100	20 3C		
Phenol (aqueous)	9	20 3C		
Phosphoric acid	50	20 3C		
Potassium hydroxide solution	50	20 3C		
Premium fuel	3"	20 3C		
Propyl alcohol	3"	20 3C		
Pyridine	3"	20 3C		

Kemikalie	Concentration	Temp.	Beständighet
Silicone oil	â€”	20 Å°C	●
Sodium carbonate (aqueous)	â€”	20 Å°C	●
Sodium chloride (aqueous)	â€”	20 Å°C	●
Sodium hydrogen sulfite	â€”	20 Å°C	●
Sodium hydroxide solution (caustic soda)	60	20 Å°C	●
Sodium hydroxide solution (caustic soda)	15	20 Å°C	●
Sodium nitrate (aqueous)	â€”	20 Å°C	●
Sodium thiosulfate	â€”	20 Å°C	●
Sulphuric acid	96	20 Å°C	●
Tetrahydrofuran (THF)	100	20 Å°C	●
Toluene	100	20 Å°C	●
Transformer oil	â€”	20 Å°C	●
Trichloroethylene	100	20 Å°C	●
Vinegar (standard)	5-10	20 Å°C	●
Water	â€”	20 Å°C	●
Xylene	â€”	20 Å°C	●