



# PEEK Mod 277/195x1000 mm negro

Artikelnr P1501105

Beständig

Delvis beständig

Ej beständig

| Kemikalie                             | Concentración | Temp.  | Beständighet |
|---------------------------------------|---------------|--------|--------------|
| 1,4-Dioxane                           | 100           | 20 Å°C | <div></div>  |
| 2-Hydroxypropionic acid (lactic acid) | 90            | 20 Å°C | <div></div>  |
| Acetic acid                           | 100           | 20 Å°C | <div></div>  |
| Acetone                               | 100           | 20 Å°C | <div></div>  |
| Ammonia                               | â€”           | 20 Å°C | <div></div>  |
| Ammonium chloride                     | â€”           | 20 Å°C | <div></div>  |
| Amyl alcohol                          | â€”           | 20 Å°C | <div></div>  |
| Apple juice                           | â€”           | 20 Å°C | <div></div>  |
| Benzene                               | â€”           | 20 Å°C | <div></div>  |
| Boric acid                            | 100           | 20 Å°C | <div></div>  |
| Brake fluid                           | â€”           | 20 Å°C | <div></div>  |
| Butyl acetate                         | â€”           | 20 Å°C | <div></div>  |
| Calcium chloride                      | â€”           | 20 Å°C | <div></div>  |
| Carbon tetrachloride                  | â€”           | 20 Å°C | <div></div>  |
| Chlorine (gas)                        | 100           | 20 Å°C | <div></div>  |
| Chlorobenzene                         | 100           | 20 Å°C | <div></div>  |
| Chloroform                            | â€”           | 20 Å°C | <div></div>  |
| Citric acid                           | 10            | 20 Å°C | <div></div>  |
| Cyclohexanone                         | 100           | 20 Å°C | <div></div>  |
| Cyclohexene                           | 100           | 20 Å°C | <div></div>  |
| Diesel                                | â€”           | 20 Å°C | <div></div>  |
| Diethylene oxide                      | â€”           | 20 Å°C | <div></div>  |
| Ethyl acetate                         | 100           | 20 Å°C | <div></div>  |
| Ethyl alcohol (ethanol)               | 96            | 20 Å°C | <div></div>  |
| Ethylene chloride                     | 100           | 20 Å°C | <div></div>  |
| Food oil                              | â€”           | 20 Å°C | <div></div>  |
| Formaldehyde (aqueous)                | 40            | 20 Å°C | <div></div>  |

| Kemikalie                        | Concentration | Temp.  | Beständighet |
|----------------------------------|---------------|--------|--------------|
| Formic acid                      | 10            | 20 Å°C | <div></div>  |
| Frost protection agent           | â€”           | 20 Å°C | <div></div>  |
| Fuel oil                         | â€”           | 20 Å°C | <div></div>  |
| Fuel, aromatic free              | â€”           | 20 Å°C | <div></div>  |
| Glycerine                        | 100           | 20 Å°C | <div></div>  |
| Glycol                           | 100           | 20 Å°C | <div></div>  |
| Heptane                          | 100           | 20 Å°C | <div></div>  |
| Hydrochloric acid                | 10            | 20 Å°C | <div></div>  |
| Hydrochloric acid (concentrated) | â€”           | 20 Å°C | <div></div>  |
| Hydrofluoric acid                | 40            | 20 Å°C | <div></div>  |
| Hydrogen peroxide                | 10            | 20 Å°C | <div></div>  |
| Hydrogen sulfide (aqueous)       | â€”           | 20 Å°C | <div></div>  |
| Isopropyl alcohol                | 100           | 20 Å°C | <div></div>  |
| Linseed oil                      | â€”           | 20 Å°C | <div></div>  |
| Mercurochrome                    | â€”           | 20 Å°C | <div></div>  |
| Methyl alcohol (methanol)        | 100           | 20 Å°C | <div></div>  |
| Methyl ethyl ketone (MEK)        | 100           | 20 Å°C | <div></div>  |
| Methylene chloride               | 100           | 20 Å°C | <div></div>  |
| Milk                             | â€”           | 20 Å°C | <div></div>  |
| Mineral oils (aromatic free)     | â€”           | 20 Å°C | <div></div>  |
| Nitric acid                      | 50            | 20 Å°C | <div></div>  |
| Nitric acid                      | 10            | 20 Å°C | <div></div>  |
| Nitrobenzene                     | â€”           | 20 Å°C | <div></div>  |
| Oxalic acid                      | â€”           | 20 Å°C | <div></div>  |
| Ozone (gas)                      | â€”           | 20 Å°C | <div></div>  |
| Paraffin oil                     | 100           | 20 Å°C | <div></div>  |
| Perchloroethylene                | â€”           | 20 Å°C | <div></div>  |
| Petroleum                        | 100           | 20 Å°C | <div></div>  |
| Petroleum ether                  | 100           | 20 Å°C | <div></div>  |
| Phenol (aqueous)                 | 9             | 20 Å°C | <div></div>  |
| Phosphoric acid                  | 50            | 20 Å°C | <div></div>  |
| Potassium hydroxide solution     | 50            | 20 Å°C | <div></div>  |
| Premium fuel                     | â€”           | 20 Å°C | <div></div>  |
| Propyl alcohol                   | â€”           | 20 Å°C | <div></div>  |
| Pyridine                         | â€”           | 20 Å°C | <div></div>  |

| Kemikalie                                | Concentration | Temp.  | Beständighet |
|------------------------------------------|---------------|--------|--------------|
| Silicone oil                             | â€”           | 20 Å°C | ●            |
| Sodium carbonate (aqueous)               | â€”           | 20 Å°C | ●            |
| Sodium chloride (aqueous)                | â€”           | 20 Å°C | ●            |
| Sodium hydrogen sulfite                  | â€”           | 20 Å°C | ●            |
| Sodium hydroxide solution (caustic soda) | 60            | 20 Å°C | ●            |
| Sodium hydroxide solution (caustic soda) | 15            | 20 Å°C | ●            |
| Sodium nitrate (aqueous)                 | â€”           | 20 Å°C | ●            |
| Sodium thiosulfate                       | â€”           | 20 Å°C | ●            |
| Sulphuric acid                           | 96            | 20 Å°C | ●            |
| Tetrahydrofuran (THF)                    | 100           | 20 Å°C | ●            |
| Toluene                                  | 100           | 20 Å°C | ●            |
| Transformer oil                          | â€”           | 20 Å°C | ●            |
| Trichloroethylene                        | 100           | 20 Å°C | ●            |
| Vinegar (standard)                       | 5-10          | 20 Å°C | ●            |
| Water                                    | â€”           | 20 Å°C | ●            |
| Xylene                                   | â€”           | 20 Å°C | ●            |