

# PEEK+PTFE 3000x500x6 mm beige

Artikelnr P1501507

## 1. Tekniskt datablad

Egenskap	VÄrde	Enhet	Standard
Densidad	1.31	g/cm <sup>3</sup>	ISO 1183
MÅdulo de elasticidad (tracci3n)	4400	MPa	ISO 527-2
Deformaci3n a la rotura	20	%	ISO 527-2
Punto de fusi3n	340	Å°C	ISO 3146
Temperatura de servicio m3xima (corto plazo)	310	Å°C	
Temperatura de funcionamiento m3xima	200	Å°C	
Deformaci3n t3rmica (HDT/A)	160	Å°C	ISO 75-2
Fuerza diel3ctrica	24	kV/mm	IEC 60243-1
Resistividad volum3trica	10 <sup>14</sup>	ÎÅ-cm	IEC 60093
Constante diel3ctrica (1 MHz)	3.6	-	IEC 60250
Constante diel3ctrica (100 Hz)	3.2	-	IEC 60250
Factor de p3rdida diel3ctrica (1 MHz)	0.0	-	IEC 60250
Factor de p3rdida diel3ctrica (100 Hz)	0.0	-	IEC 60250
Resistencia a la flexi3n	110	MPa	ISO 527-2
Conductividad t3rmica	0.25	W/(mÅ·K)	DIN 52612
Resistencia superficial	10 <sup>14</sup>	Î©	IEC 60093
Åndice de seguimiento comparativo (CTI)	150	V	IEC 60112
Absorci3n de agua hasta la saturaci3n	0.2	%	ISO 62
Absorci3n de agua hasta la saturaci3n	0.45	%	ISO 62
Resistencia al impacto con entalla (Charpy)	3.5	kJ/mÅ <sup>2</sup>	ISO 179/1eA
Coefficiente de expansi3n t3rmica	0.5	10 <sup>-6</sup> Å/K	ISO 11359
Dureza a la presi3n de bala	230	MPa	ISO 2039-1

## 2. Kemisk best3ndighet

● Best3ndig ● Delvis best3ndig ● Ej best3ndig

Kemikalie

Konc.

Resultat

Kemikalie	Konc.	Resultat
1,4-Dioxane	100	●
2-Hydroxypropionic Acid	90	●
Acetic Acid	100	●
Acetone	100	●
Ammonia	â€”	●
Ammonium Chloride	â€”	●
Amyl Alcohol	â€”	●
Apple Juice	â€”	●
Benzene	â€”	●
Bleaching Solution	â€”	●
Boric Acid	100	●
Brake Fluid	â€”	●
Butyl Acetate	â€”	●
Calcium Chloride	â€”	●
Carbon Disulfide	100	●
Carbon Tetrachloride	â€”	●
Chlorine (gas)	100	●
Chlorobenzene	100	●
Chloroform	â€”	●
Citric Acid	10	●
Cresol	â€”	●
Cyclohexanone	100	●
Cyclohexene	100	●
Diesel Fuel	â€”	●
Diethylene Oxide	â€”	●
Ethyl Acetate	100	●
Ethyl Alcohol	96	●
Ethylene Chloride	100	●
Food Oil	â€”	●
Formaldehyde (aqueous)	40	●
Formic Acid	10	●
Frost Protection Agent	â€”	●
Fuel, aromatic free	â€”	●
Glycerine	100	●

Kemikalie	Konc.	Resultat
Glycol	100	●
Heating Oil	â€”	●
Heptane	100	●
Hydrochloric Acid	10	●
Hydrochloric Acid (concentrated)	â€”	●
Hydrofluoric Acid	40	●
Hydrogen Peroxide	10	●
Hydrogen Sulfide (aqueous)	â€”	●
Isopropyl Alcohol	100	●
Linseed Oil	â€”	●
Mercurochrome	â€”	●
Methyl Alcohol	100	●
Methyl Ethyl Ketone (MEK)	100	●
Methylene Chloride	100	●
Milk	â€”	●
Mineral Oils (aromatic free)	â€”	●
Nitric Acid	10	●
Nitric Acid	50	●
Nitrobenzene	â€”	●
Oxalic Acid	â€”	●
Ozone Gas	â€”	●
Paraffine Oil	100	●
Perchloroethylene	â€”	●
Petroleum	100	●
Petroleum Ether	100	●
Phenol (aqueous)	9	●
Phosphoric Acid	50	●
Potassium Hydroxide liquor	50	●
Premium Fuel	â€”	●
Propyl Alcohol	â€”	●
Pyridine	â€”	●
Silicone Oil	â€”	●
Sodium Carbonate (aqueous)	â€”	●
Sodium Chloride (aqueous)	â€”	●
Sodium Hydrogen Sulfite	â€”	●

Kemikalie	Konc.	Resultat
Sodium Hydroxide liquor	15	●
Sodium Hydroxide liquor	60	●
Sodium Nitrate (aqueous)	â€”	●
Sodium Thiosulfate	â€”	●
Sulfuric Acid	96	●
Tetrahydrofuran (THF)	100	●
Toluene	100	●
Transformer Oil	â€”	●
Trichloroethylene	100	●
Vinegar (standard)	5-10	●
Water	â€”	●
Xylene	â€”	●