



PEEK 150/100x3000 mm beige

Artikelnr P1500380

Best ndig

Delvis best ndig

Ej best ndig

Kemikalie	Concentraci�n	Temp.	Best�ndighet
1,4-Dioxane	100	20 �C	
2-Hydroxypropionic acid (lactic acid)	90	20 �C	
Acetic acid	100	20 �C	
Acetone	100	20 �C	
Ammonia	��	20 �C	
Ammonium chloride	��	20 �C	
Amyl alcohol	��	20 �C	
Apple juice	��	20 �C	
Benzene	��	20 �C	
Boric acid	100	20 �C	
Brake fluid	��	20 �C	
Butyl acetate	��	20 �C	
Calcium chloride	��	20 �C	
Carbon tetrachloride	��	20 �C	
Chlorine (gas)	100	20 �C	
Chlorobenzene	100	20 �C	
Chloroform	��	20 �C	
Citric acid	10	20 �C	
Cyclohexanone	100	20 �C	
Cyclohexene	100	20 �C	
Diesel	��	20 �C	
Diethylene oxide	��	20 �C	
Ethyl acetate	100	20 �C	
Ethyl alcohol (ethanol)	96	20 �C	
Ethylene chloride	100	20 �C	
Food oil	��	20 �C	
Formaldehyde (aqueous)	40	20 �C	

Kemikalie	Concentraci3n	Temp.	Best3ndighet
Formic acid	10	20 Å°C	
Frost protection agent	â€”	20 Å°C	
Fuel oil	â€”	20 Å°C	
Fuel, aromatic free	â€”	20 Å°C	
Glycerine	100	20 Å°C	
Glycol	100	20 Å°C	
Heptane	100	20 Å°C	
Hydrochloric acid	10	20 Å°C	
Hydrochloric acid (concentrated)	â€”	20 Å°C	
Hydrofluoric acid	40	20 Å°C	
Hydrogen peroxide	10	20 Å°C	
Hydrogen sulfide (aqueous)	â€”	20 Å°C	
Isopropyl alcohol	100	20 Å°C	
Linseed oil	â€”	20 Å°C	
Mercurochrome	â€”	20 Å°C	
Methyl alcohol (methanol)	100	20 Å°C	
Methyl ethyl ketone (MEK)	100	20 Å°C	
Methylene chloride	100	20 Å°C	
Milk	â€”	20 Å°C	
Mineral oils (aromatic free)	â€”	20 Å°C	
Nitric acid	50	20 Å°C	
Nitric acid	10	20 Å°C	
Nitrobenzene	â€”	20 Å°C	
Oxalic acid	â€”	20 Å°C	
Ozone (gas)	â€”	20 Å°C	
Paraffin oil	100	20 Å°C	
Perchloroethylene	â€”	20 Å°C	
Petroleum	100	20 Å°C	
Petroleum ether	100	20 Å°C	
Phenol (aqueous)	9	20 Å°C	
Phosphoric acid	50	20 Å°C	
Potassium hydroxide solution	50	20 Å°C	
Premium fuel	â€”	20 Å°C	
Propyl alcohol	â€”	20 Å°C	
Pyridine	â€”	20 Å°C	

Kemikalie	Concentration	Temp.	Beständighet
Silicone oil	â€”	20 Å°C	●
Sodium carbonate (aqueous)	â€”	20 Å°C	●
Sodium chloride (aqueous)	â€”	20 Å°C	●
Sodium hydrogen sulfite	â€”	20 Å°C	●
Sodium hydroxide solution (caustic soda)	60	20 Å°C	●
Sodium hydroxide solution (caustic soda)	15	20 Å°C	●
Sodium nitrate (aqueous)	â€”	20 Å°C	●
Sodium thiosulfate	â€”	20 Å°C	●
Sulphuric acid	96	20 Å°C	●
Tetrahydrofuran (THF)	100	20 Å°C	●
Toluene	100	20 Å°C	●
Transformer oil	â€”	20 Å°C	●
Trichloroethylene	100	20 Å°C	●
Vinegar (standard)	5-10	20 Å°C	●
Water	â€”	20 Å°C	●
Xylene	â€”	20 Å°C	●