



# PEEK 200/160x3000 mm negro

Artikelnr P1500472

Beständig

Delvis beständig

Ej beständig

| Kemikalie                             | Concentration | Temp.  | Beständighet |
|---------------------------------------|---------------|--------|--------------|
| 1,4-Dioxane                           | 100           | 20 Å°C |              |
| 2-Hydroxypropionic acid (lactic acid) | 90            | 20 Å°C |              |
| Acetic acid                           | 100           | 20 Å°C |              |
| Acetone                               | 100           | 20 Å°C |              |
| Ammonia                               | â€            | 20 Å°C |              |
| Ammonium chloride                     | â€            | 20 Å°C |              |
| Amyl alcohol                          | â€            | 20 Å°C |              |
| Apple juice                           | â€            | 20 Å°C |              |
| Benzene                               | â€            | 20 Å°C |              |
| Boric acid                            | 100           | 20 Å°C |              |
| Brake fluid                           | â€            | 20 Å°C |              |
| Butyl acetate                         | â€            | 20 Å°C |              |
| Calcium chloride                      | â€            | 20 Å°C |              |
| Carbon tetrachloride                  | â€            | 20 Å°C |              |
| Chlorine (gas)                        | 100           | 20 Å°C |              |
| Chlorobenzene                         | 100           | 20 Å°C |              |
| Chloroform                            | â€            | 20 Å°C |              |
| Citric acid                           | 10            | 20 Å°C |              |
| Cyclohexanone                         | 100           | 20 Å°C |              |
| Cyclohexene                           | 100           | 20 Å°C |              |
| Diesel                                | â€            | 20 Å°C |              |
| Diethylene oxide                      | â€            | 20 Å°C |              |
| Ethyl acetate                         | 100           | 20 Å°C |              |
| Ethyl alcohol (ethanol)               | 96            | 20 Å°C |              |
| Ethylene chloride                     | 100           | 20 Å°C |              |
| Food oil                              | â€            | 20 Å°C |              |
| Formaldehyde (aqueous)                | 40            | 20 Å°C |              |

| Kemikalie                        |     |       |  |              |
|----------------------------------|-----|-------|--|--------------|
| Concentraci3n                    |     | Temp. |  | Best3ndighet |
| Formic acid                      | 10  | 20 3C |  |              |
| Frost protection agent           | 3C  | 20 3C |  |              |
| Fuel oil                         | 3C  | 20 3C |  |              |
| Fuel, aromatic free              | 3C  | 20 3C |  |              |
| Glycerine                        | 100 | 20 3C |  |              |
| Glycol                           | 100 | 20 3C |  |              |
| Heptane                          | 100 | 20 3C |  |              |
| Hydrochloric acid                | 10  | 20 3C |  |              |
| Hydrochloric acid (concentrated) | 3C  | 20 3C |  |              |
| Hydrofluoric acid                | 40  | 20 3C |  |              |
| Hydrogen peroxide                | 10  | 20 3C |  |              |
| Hydrogen sulfide (aqueous)       | 3C  | 20 3C |  |              |
| Isopropyl alcohol                | 100 | 20 3C |  |              |
| Linseed oil                      | 3C  | 20 3C |  |              |
| Mercurochrome                    | 3C  | 20 3C |  |              |
| Methyl alcohol (methanol)        | 100 | 20 3C |  |              |
| Methyl ethyl ketone (MEK)        | 100 | 20 3C |  |              |
| Methylene chloride               | 100 | 20 3C |  |              |
| Milk                             | 3C  | 20 3C |  |              |
| Mineral oils (aromatic free)     | 3C  | 20 3C |  |              |
| Nitric acid                      | 10  | 20 3C |  |              |
| Nitric acid                      | 50  | 20 3C |  |              |
| Nitrobenzene                     | 3C  | 20 3C |  |              |
| Oxalic acid                      | 3C  | 20 3C |  |              |
| Ozone (gas)                      | 3C  | 20 3C |  |              |
| Paraffin oil                     | 100 | 20 3C |  |              |
| Perchloroethylene                | 3C  | 20 3C |  |              |
| Petroleum                        | 100 | 20 3C |  |              |
| Petroleum ether                  | 100 | 20 3C |  |              |
| Phenol (aqueous)                 | 9   | 20 3C |  |              |
| Phosphoric acid                  | 50  | 20 3C |  |              |
| Potassium hydroxide solution     | 50  | 20 3C |  |              |
| Premium fuel                     | 3C  | 20 3C |  |              |
| Propyl alcohol                   | 3C  | 20 3C |  |              |
| Pyridine                         | 3C  | 20 3C |  |              |

| Kemikalie                                | Concentration | Temp.  | Beständighet |
|------------------------------------------|---------------|--------|--------------|
| Silicone oil                             | â€”           | 20 Å°C | ●            |
| Sodium carbonate (aqueous)               | â€”           | 20 Å°C | ●            |
| Sodium chloride (aqueous)                | â€”           | 20 Å°C | ●            |
| Sodium hydrogen sulfite                  | â€”           | 20 Å°C | ●            |
| Sodium hydroxide solution (caustic soda) | 60            | 20 Å°C | ●            |
| Sodium hydroxide solution (caustic soda) | 15            | 20 Å°C | ●            |
| Sodium nitrate (aqueous)                 | â€”           | 20 Å°C | ●            |
| Sodium thiosulfate                       | â€”           | 20 Å°C | ●            |
| Sulphuric acid                           | 96            | 20 Å°C | ●            |
| Tetrahydrofuran (THF)                    | 100           | 20 Å°C | ●            |
| Toluene                                  | 100           | 20 Å°C | ●            |
| Transformer oil                          | â€”           | 20 Å°C | ●            |
| Trichloroethylene                        | 100           | 20 Å°C | ●            |
| Vinegar (standard)                       | 5-10          | 20 Å°C | ●            |
| Water                                    | â€”           | 20 Å°C | ●            |
| Xylene                                   | â€”           | 20 Å°C | ●            |