



PMMA E 2050x1520x6 mm transparente 92%

Artikelnr P1200667  
Material PMMA

1. Tekniskt datablad

| Egenskap                                      | Värde            | Enhet   | Standard    |
|-----------------------------------------------|------------------|---------|-------------|
| Densidad                                      | 1.19             | g/cm³   | ISO 1183    |
| Límite de resistencia a la tracción           | 72               | MPa     | ISO 527     |
| Módulo de elasticidad (tracción)              | 3300             | MPa     | ISO 527-2   |
| Resistencia a la tensión                      | 70               | MPa     | ISO 527-2   |
| Deformación a la rotura                       | 5                | %       | ISO 527-2   |
| Punto de fusión                               | 160              | °C      | ISO 3146    |
| Temperatura de servicio máxima (corto plazo)  | 107.5            | °C      | UL746B      |
| Temperatura de funcionamiento máxima          | 75               | °C      |             |
| Temperatura mínima                            | -40              | °C      |             |
| Deformación térmica (HDT/A)                   | 95               | °C      | ISO 75      |
| Deformación térmica (HDT/B)                   | 100              | °C      | ISO 75      |
| Temperatura de ablandamiento Vicat (VST/B/50) | 103              | °C      | ISO 306     |
| Fuerza dieléctrica                            | 30               | kV/mm   | IEC 60243-1 |
| Resistividad volumétrica                      | 10 <sup>15</sup> | Ω·cm    | IEC 60093   |
| Constante dieléctrica (1 MHz)                 | 1                | -       | IEC 60250   |
| Constante dieléctrica (100 Hz)                | 2.7              | -       | DIN 53483-2 |
| Factor de pérdida dieléctrica (1 MHz)         | 0.03             | -       | IEC 60250   |
| Factor de pérdida dieléctrica (100 Hz)        | 0.06             | -       | DIN 53483-2 |
| Resistencia a la flexión                      | 75               | MPa     | ISO 527-2   |
| Conductividad térmica                         | 0.19             | W/(m·K) | DIN 52612   |
| Resistencia superficial                       | 10 <sup>13</sup> | Ω       | IEC 60093   |
| Índice de seguimiento comparativo (CTI)       | 600              | V       | IEC 60112   |
| Absorción de agua hasta la saturación         | 2.1              | %       | ISO 62      |
| Absorción de agua hasta la saturación         | 2.1              | %       | ISO 62      |
| Resistencia al impacto con entalla (Charpy)   | 1.6              | kJ/m²   | ISO 179/1eA |

| Egenskap                         | Värde | Enhet               | Standard    |
|----------------------------------|-------|---------------------|-------------|
| Resistencia al impacto (Charpy)  | 15    | kJ/m²               | ISO 179/1eU |
| Coeficiente de expansión térmica | 0.0   | 10 <sup>-4</sup> /K | DIN 11359   |
| Dureza Shore D                   | 15    | ° Shore D           |             |
| Dureza Rockwell                  | 100   | M-scale             | ISO 2039-2  |
| Dureza a la presión de bala      | 175   | MPa                 | ISO 2039-1  |

## 2. Kemisk beständighet

● Beständig
 ● Delvis beständig
 ● Ej beständig

| Kemikalie               | Konc. | Resultat |
|-------------------------|-------|----------|
| Acetic acid             | 100%  | ●        |
| Acetone                 | 100%  | ●        |
| Ammonia                 | conc. | ●        |
| Amyl alcohol            | -     | ●        |
| Apple juice             | -     | ●        |
| Benzene                 | -     | ●        |
| Butyl acetate           | -     | ●        |
| Calcium chloride        | -     | ●        |
| Carbon disulphide       | 100%  | ●        |
| Carbon tetrachloride    | -     | ●        |
| Chlorine gas            | 100%  | ●        |
| Chloroform              | -     | ●        |
| Citric acid             | 10%   | ●        |
| Cresol                  | -     | ●        |
| Cyclohexanone           | 100%  | ●        |
| Cyclohexene             | 100%  | ●        |
| Diesel                  | -     | ●        |
| Diethylene oxide        | -     | ●        |
| Ethyl acetate           | 100%  | ●        |
| Ethyl alcohol (ethanol) | 96%   | ●        |
| Ethylene chloride       | 100%  | ●        |
| Formaldehyde, aqueous   | 40%   | ●        |
| Formic acid             | 10%   | ●        |
| Fuel oil                | -     | ●        |
| Fuel, aromatic free     | -     | ●        |

| Kemikalie                                | Konc.     | Resultat |
|------------------------------------------|-----------|----------|
| Glycerine                                | 100%      | ●        |
| Glycol                                   | 100%      | ●        |
| Heptane                                  | 100%      | ●        |
| Hydrochloric acid                        | 10%       | ●        |
| Hydrochloric acid (concentrated)         | conc.     | ●        |
| Hydrofluoric acid                        | 40%       | ●        |
| Hydrogen peroxide                        | 10%       | ●        |
| Hydrogen sulfide, aqueous                | -         | ●        |
| Isopropyl alcohol                        | 100%      | ●        |
| Linseed oil                              | -         | ●        |
| Mercurochrome                            | -         | ●        |
| Methyl alcohol (methanol)                | 100%      | ●        |
| Methyl ethyl ketone (MEK)                | 100%      | ●        |
| Methylene chloride                       | 100%      | ●        |
| Milk                                     | -         | ●        |
| Mineral oils, aromatic free              | -         | ●        |
| Nitric acid                              | 10%       | ●        |
| Nitric acid (50%)                        | 50%       | ●        |
| Nitrobenzene                             | -         | ●        |
| Oxalic acid                              | -         | ●        |
| Ozone (gas)                              | ≤ 0.5 ppm | ●        |
| Paraffin oil                             | 100%      | ●        |
| Perchloroethylene                        | -         | ●        |
| Petroleum                                | 100%      | ●        |
| Petroleum ether                          | 100%      | ●        |
| Phenol, aqueous                          | ca. 9%    | ●        |
| Phosphoric acid                          | 50%       | ●        |
| Potassium hydroxide solution             | 50%       | ●        |
| Premium fuel                             | -         | ●        |
| Silicone oil                             | -         | ●        |
| Sodium carbonate, aqueous                | -         | ●        |
| Sodium chloride, aqueous                 | -         | ●        |
| Sodium hydrogen sulfite                  | -         | ●        |
| Sodium hydroxide solution (60%)          | 60%       | ●        |
| Sodium hydroxide solution (caustic soda) | 15%       | ●        |

| Kemikalie             | Konc. | Resultat |
|-----------------------|-------|----------|
| Sodium thiosulfate    | -     | ●        |
| Sulphuric acid        | 96%   | ●        |
| Tetrahydrofuran (THF) | 100%  | ●        |
| Toluene               | 100%  | ●        |
| Transformer oil       | -     | ●        |
| Trichloroethylene     | 100%  | ●        |
| Vinegar, standard     | 5-10% | ●        |
| Water                 | -     | ●        |
| Xylene                | -     | ●        |