



POM C 1000x1000x25 mm natural

Artikelnr P1005462  
Material POM

1. Tekniskt datablad

| Egenskap                                      | Värde            | Enhet             | Standard         |
|-----------------------------------------------|------------------|-------------------|------------------|
| Densidad                                      | 1.24             | g/cm <sup>3</sup> | ASTM D792        |
| Límite de resistencia a la tracción           | 51               | MPa               | DIN EN ISO 527-2 |
| Módulo de elasticidad (tracción)              | 1200             | MPa               | ASTM D790        |
| Resistencia a la tensión                      | 76.5             | MPa               | ISO 527          |
| Deformación a la rotura                       | 300              | %                 | ASTM D638        |
| Punto de fusión                               | 222              | °C                | ISO 3146         |
| Temperatura de servicio máxima (corto plazo)  | 129              | °C                | UL746B           |
| Temperatura de funcionamiento máxima          | 90               | °C                |                  |
| Temperatura mínima                            | -46.25           | °C                |                  |
| Deformación térmica (HDT/A)                   | 105              | °C                | ASTM D648        |
| Deformación térmica (HDT/B)                   | 155              | °C                | ISO 75           |
| Temperatura de ablandamiento Vicat (VST/B/50) | 50               | °C                | ISO 306          |
| Fuerza dieléctrica                            | 85               | kV/mm             | IEC 60243-1      |
| Resistividad volumétrica                      | 10 <sup>12</sup> | Ω                 | IEC 60093        |
| Constante dieléctrica (1 MHz)                 | 3.7              | -                 | IEC 60250        |
| Factor de pérdida dieléctrica (1 MHz)         | 0.0              | -                 | IEC 60250        |
| Factor de pérdida dieléctrica (100 Hz)        | 0.0              | -                 | IEC 60250        |
| Clasificación de resistencia al fuego (UL 94) | 60695            |                   | UL 94            |
| Resistencia a la flexión                      | 58               | MPa               | ASTM D638        |
| Conductividad térmica                         | 0.3              | W/(m·K)           | DIN 52612        |
| Resistencia superficial                       | 10 <sup>13</sup> | Ω                 | IEC 60093        |
| Índice de seguimiento comparativo (CTI)       | 600              | V                 | IEC 60112        |
| Absorción de agua hasta la saturación         | 2.2              | %                 | ASTM D955        |
| Absorción de agua hasta la saturación         | 0.5              | %                 | ASTM D570        |

| Egenskap                                    | Värde | Enhet               | Standard         |
|---------------------------------------------|-------|---------------------|------------------|
| Resistencia al impacto con entalla (Charpy) | 6     | kJ/m²               | DIN EN ISO 179-1 |
| Resistencia al impacto (Charpy)             | 19    | kJ/m²               | ISO 179/1eU      |
| Coeficiente de expansión térmica            | 0.4   | 10 <sup>-4</sup> /K | ISO 11359        |
| Dureza Shore D                              | 83    | ° Shore D           | ISO 868          |
| Dureza a la presión de bala                 | 230   | MPa                 | ISO 2039-1       |

2. Kemisk beständighet

● Beständig   ● Delvis beständig   ● Ej beständig

| Kemikalie                             | Konc.   | Resultat       |
|---------------------------------------|---------|----------------|
| 1,4-Dioxane                           | 100%    | <span>●</span> |
| 2-Hydroxypropionic acid (lactic acid) | 90%     | <span>●</span> |
| Acetic acid                           | 100%    | <span>●</span> |
| Acetone                               | 100%    | <span>●</span> |
| Ammonia                               | conc.   | <span>●</span> |
| Ammonium chloride                     | -       | <span>●</span> |
| Amyl alcohol                          | -       | <span>●</span> |
| Apple juice                           | -       | <span>●</span> |
| Benzene                               | -       | <span>●</span> |
| Bleaching solution                    | 12.5 cl | <span>●</span> |
| Boric acid                            | 100%    | <span>●</span> |
| Brake fluid                           | -       | <span>●</span> |
| Butyl acetate                         | -       | <span>●</span> |
| Calcium chloride                      | -       | <span>●</span> |
| Carbon disulphide                     | 100%    | <span>●</span> |
| Carbon tetrachloride                  | -       | <span>●</span> |
| Chlorobenzene                         | 100%    | <span>●</span> |
| Chloroform                            | -       | <span>●</span> |
| Citric acid                           | 10%     | <span>●</span> |
| Cyclohexanone                         | 100%    | <span>●</span> |
| Cyclohexene                           | 100%    | <span>●</span> |
| Diesel                                | -       | <span>●</span> |
| Diethylene oxide                      | -       | <span>●</span> |
| Ethyl acetate                         | 100%    | <span>●</span> |
| Ethyl alcohol (ethanol)               | 96%     | <span>●</span> |

| Kemikalie                        | Konc.    | Resultat |
|----------------------------------|----------|----------|
| Food oil                         | -        | ●        |
| Formaldehyde, aqueous            | 40%      | ●        |
| Formic acid                      | 10%      | ●        |
| Frost protection agent           | -        | ●        |
| Fuel oil                         | -        | ●        |
| Fuel, aromatic free              | -        | ●        |
| Glycerine                        | 100%     | ●        |
| Glycol                           | 100%     | ●        |
| Heptane                          | 100%     | ●        |
| Hydrochloric acid                | 10%      | ●        |
| Hydrochloric acid (concentrated) | conc.    | ●        |
| Hydrofluoric acid                | 40%      | ●        |
| Hydrogen peroxide                | 10%      | ●        |
| Hydrogen sulfide, aqueous        | -        | ●        |
| Isopropyl alcohol                | 100%     | ●        |
| Linseed oil                      | -        | ●        |
| Mercurochrome                    | -        | ●        |
| Methyl alcohol (methanol)        | 100%     | ●        |
| Methyl ethyl ketone (MEK)        | 100%     | ●        |
| Methylene chloride               | 100%     | ●        |
| Milk                             | -        | ●        |
| Mineral oils (aromatic free)     | -        | ●        |
| Nitric acid                      | 10%      | ●        |
| Nitric acid (50%)                | 50%      | ●        |
| Nitrobenzene                     | -        | ●        |
| Oxalic acid                      | -        | ●        |
| Ozone (gas)                      | ≤0.5 ppm | ●        |
| Paraffin oil                     | 100%     | ●        |
| Perchloroethylene                | -        | ●        |
| Petroleum                        | 100%     | ●        |
| Petroleum ether                  | 100%     | ●        |
| Phenol, aqueous                  | ca. 9%   | ●        |
| Phosphoric acid                  | 50%      | ●        |
| Potassium hydroxide solution     | 50%      | ●        |
| Premium fuel                     | -        | ●        |

| Kemikalie                       | Konc. | Resultat |
|---------------------------------|-------|----------|
| Propyl alcohol                  | -     | ●        |
| Silicone oil                    | -     | ●        |
| Sodium carbonate, aqueous       | -     | ●        |
| Sodium chloride, aqueous        | -     | ●        |
| Sodium hydrogen sulfite         | -     | ●        |
| Sodium hydroxide solution (15%) | 15%   | ●        |
| Sodium hydroxide solution (60%) | 60%   | ●        |
| Sodium nitrate, aqueous         | -     | ●        |
| Sulphuric acid                  | 96%   | ●        |
| Tetrahydrofuran (THF)           | 100%  | ●        |
| Toluene                         | 100%  | ●        |
| Transformer oil                 | -     | ●        |
| Trichloroethylene               | 100%  | ●        |
| Vinegar, standard               | 5-10% | ●        |
| Water                           | -     | ●        |
| Xylene                          | -     | ●        |