POM C FG 250/150x1000 mm negro

Artikelnr P1007083

BestÃ□ndig Delvis bestÃ□ndig Ej bestÃ□ndig

Kemikalie	ConcentraciÃ³n	Temp.	BestÃ□ndighet
1,4-Dioxane	100%	20 Â°C	
2-Hydroxypropionic acid (lactic acid)	90%	20 Â°C	
Acetic acid	100%	20 Â°C	
Acetone	100%	20 Â°C	
Ammonia	conc.	20 Â°C	
Ammonium chloride	â€”	20 Â°C	
Amyl alcohol	â€”	20 Â°C	
Apple juice	â€”	20 Â°C	
Benzene	â€”	20 Â°C	
Bleaching solution	12.5 cl	20 Â°C	
Boric acid	100%	20 Â°C	
Brake fluid	â€”	20 Â°C	
Butyl acetate	â€”	20 Â°C	
Calcium chloride	â€”	20 Â°C	
Carbon disulphide	100%	20 Â°C	
Carbon tetrachloride	â€”	20 Â°C	
Chlorobenzene	100%	20 Â°C	
Chloroform	â€”	20 Â°C	
Citric acid	10%	20 Â°C	
Cyclohexanone	100%	20 Â°C	
Cyclohexene	100%	20 Â°C	
Diesel	â€”	20 Â°C	
Diethylene oxide	â€”	20 Â°C	
Ethyl acetate	100%	20 Â°C	
Ethyl alcohol (ethanol)	96%	20 Â°C	
Food oil	â€”	20 Â°C	
Formaldehyde, aqueous	40%	20 Â°C	

Kemikalie	ConcentraciÃ³n	Temp.	BestÃ□ndighet
Formic acid	10%	20 Â°C	🟢
Frost protection agent	â€”	20 Â°C	🟢
Fuel oil	â€”	20 Â°C	🟢
Fuel, aromatic free	â€”	20 Â°C	🟢
Glycerine	100%	20 Â°C	🟢
Glycol	100%	20 Â°C	🟢
Heptane	100%	20 Â°C	🟢
Hydrochloric acid	10%	20 Â°C	🔴
Hydrochloric acid (concentrated)	conc.	20 Â°C	🔴
Hydrofluoric acid	40%	20 Â°C	🔴
Hydrogen peroxide	10%	20 Â°C	🟢
Hydrogen sulfide, aqueous	â€”	20 Â°C	🟢
Isopropyl alcohol	100%	20 Â°C	🟢
Linseed oil	â€”	20 Â°C	🟢
Mercurochrome	â€”	20 Â°C	🔴
Methyl alcohol (methanol)	100%	20 Â°C	🟢
Methyl ethyl ketone (MEK)	100%	20 Â°C	🟡
Methylene chloride	100%	20 Â°C	🔴
Milk	â€”	20 Â°C	🟢
Mineral oils (aromatic free)	â€”	20 Â°C	🟢
Nitric acid	10%	20 Â°C	🔴
Nitric acid (50%)	50%	20 Â°C	🔴
Nitrobenzene	â€”	20 Â°C	🟡
Oxalic acid	â€”	20 Â°C	🔴
Ozone (gas)	â‰¤0.5 ppm	20 Â°C	🔴
Paraffin oil	100%	20 Â°C	🟢
Perchloroethylene	â€”	20 Â°C	🟢
Petroleum	100%	20 Â°C	🟢
Petroleum ether	100%	20 Â°C	🟢
Phenol, aqueous	ca. 9%	20 Â°C	🔴
Phosphoric acid	50%	20 Â°C	🔴
Potassium hydroxide solution	50%	20 Â°C	🟡
Premium fuel	â€”	20 Â°C	🟢
Propyl alcohol	â€”	20 Â°C	🟢
Silicone oil	â€”	20 Â°C	🟢

Kemikalie	ConcentraciÃ³n	Temp.	BestÃ□ndighet
Sodium carbonate, aqueous	â€”	20 Â°C	
Sodium chloride, aqueous	â€”	20 Â°C	
Sodium hydrogen sulfite	â€”	20 Â°C	
Sodium hydroxide solution (15%)	15%	20 Â°C	
Sodium hydroxide solution (60%)	60%	20 Â°C	
Sodium nitrate, aqueous	â€”	20 Â°C	
Sulphuric acid	96%	20 Â°C	
Tetrahydrofuran (THF)	100%	20 Â°C	
Toluene	100%	20 Â°C	
Transformer oil	â€”	20 Â°C	
Trichloroethylene	100%	20 Â°C	
Vinegar, standard	5-10%	20 Â°C	
Water	â€”	20 Â°C	
Xylene	â€”	20 Â°C	

This document is for informational purposes only. Specifications may change without notice. Generated 2026-03-23