



PP-C 2440x1220x6 mm negro (con película protectora)

Artikelnr P2201549

1. Tekniskt datablad

Egenskap	Värde	Enhet	Standard
Densidad	0.9	g/cm³	DIN EN ISO 1183-1
Límite de resistencia a la tracción	24	MPa	DIN EN ISO 527
Módulo de elasticidad (tracción)	1241.2	MPa	DIN EN ISO 527
Deformación a la rotura	50	%	DIN EN ISO 527
Punto de fusión	164	°C	ISO 11357-3
Temperatura de servicio máxima (corto plazo)	116	°C	
Temperatura de funcionamiento máxima	75	°C	
Temperatura mínima	-23	°C	
Temperatura de ablandamiento Vicat (VST/B/50)	87	°C	DIN EN ISO 306
Fuerza dieléctrica	40	kV/mm	IEC 60243
Resistividad volumétrica	10¹⁵	Ω·cm	DIN EN 62631-3-1
Constante dieléctrica (1 MHz)	2.48	-	IEC 60250
Factor de pérdida dieléctrica (1 MHz)	0.0	-	IEC 60250
Factor de pérdida dieléctrica (100 Hz)	0.0	-	IEC 60250
Conductividad térmica	0.2	W/(m·K)	DIN 52612-1
Resistencia superficial	10¹⁵	Ω	DIN EN 62631-3-2
Índice de seguimiento comparativo (CTI)	600	V	IEC 60112
Absorción de agua hasta la saturación	0.1	%	DIN EN ISO 62
Absorción de agua hasta la saturación	0.1	%	DIN EN ISO 62
Resistencia al impacto con entalla (Charpy)	4	kJ/m²	DIN EN ISO 179
Coefficiente de expansión térmica	0.0	10⁻⁵/K	DIN 53752
Dureza Shore D	67.25	° Shore D	DIN EN ISO 868
Dureza a la presión de bala	50	MPa	DIN EN ISO 2039-1

2. Kemisk beständighet

● Beständig ● Delvis beständig ● Ej beständig

Kemikalie	Konc.	Resultat
1,4-Dioxane	100	
2-Hydroxypropionic Acid	90	
Acetic Acid	100	
Acetone	100	
Ammonia	â€”	
Ammonium Chloride	â€”	
Amyl Alcohol	â€”	
Apple Juice	â€”	
Benzene	â€”	
Bleaching Solution	â€”	
Boric Acid	100	
Brake Fluid	â€”	
Butyl Acetate	â€”	
Calcium Chloride	â€”	
Carbon Disulfide	100	
Carbon Tetrachloride	â€”	
Chlorine (gas)	100	
Chlorobenzene	100	
Chloroform	â€”	
Citric Acid	10	
Cresol	â€”	
Cyclohexanone	100	
Cyclohexene	100	
Diesel Fuel	â€”	
Diethylene Oxide	â€”	
Ethyl Acetate	100	
Ethyl Alcohol	96	
Ethylene Chloride	100	
Food Oil	â€”	
Formaldehyde, aqueous	40	
Formic Acid	10	
Frost Protection Agent	â€”	
Fuel, aromatic free	â€”	
Glycerine	100	

Kemikalie	Konc.	Resultat
Glycol	100	
Heating Oil	â€”	
Heptane	100	
Hydrochloric Acid	10	
Hydrochloric Acid (concentrated)	â€”	
Hydrofluoric Acid	40	
Hydrogen Peroxide	10	
Hydrogen Sulfide, aqueous solution	â€”	
Isopropyl Alcohol	100	
Linseed Oil	â€”	
Mercurochrome	â€”	
Methyl Alcohol	100	
Methyl Ethyl Ketone (MEK)	100	
Methylene Chloride	100	
Milk	â€”	
Mineral Oils (aromatic free)	â€”	
Nitric Acid	10	
Nitric Acid	50	
Nitrobenzene	â€”	
Oxalic Acid	â€”	
Ozone Gas	â‰ƒ 0.5 ppm	
Paraffine Oil	100	
Perchloroethylene	â€”	
Petroleum	100	
Petroleum Ether	100	
Phenol, aqueous	ca. 9	
Phosphoric Acid	50	
Potassium Hydroxide liquor	50	
Premium Fuel	â€”	
Propyl Alcohol	â€”	
Pyridine	â€”	
Silicone Oil	â€”	
Sodium Carbonate, aqueous	â€”	
Sodium Chloride, aqueous	â€”	
Sodium Hydrogen Sulfite	â€”	

Kemikalie	Konc.	Resultat
Sodium Hydroxide liquor	15	●
Sodium Hydroxide liquor	60	●
Sodium Nitrate, aqueous	â€”	●
Sodium Thiosulfate	â€”	●
Sulfuric Acid	96	●
Tetrahydrofuran (THF)	100	●
Toluene	100	●
Transformer Oil	â€”	●
Trichloroethylene	100	●
Vinegar, standard	5 - 10	●
Water	â€”	●
Xylene	â€”	●