



PP-H AlphaPlus 4000x2000x3 mm gris (con pel cula de protecci n)

Artikelnr P2201013

1. Tekniskt datablad

Egenskap	V�rde	Enhet	Standard
Densidad	0.91	g/cm��	ISO 1183
L�mite de resistencia a la tracci�n	36	MPa	ISO 527
M�dulo de elasticidad (tracci�n)	1700	MPa	ISO 527-2
Resistencia a la tensi�n	30	MPa	ISO 527
Deformaci�n a la rotura	8	%	ISO 527-2
Punto de fusi�n	161	��C	DIN EN ISO 11357
Temperatura de servicio m�xima (corto plazo)	127	��C	UL746B
Temperatura de funcionamiento m�xima	80	��C	
Temperatura m�nima	-7	��C	
Deformaci�n t�rmica (HDT/A)	54	��C	ISO 75
Deformaci�n t�rmica (HDT/B)	90	��C	ISO 75
Temperatura de ablandamiento Vicat (VST/B/50)	50	��C	ISO 306
Fuerza diel�ctrica	40	kV/mm	IEC 60243-1
Resistividad volum�trica	10���	��	DIN EN 62631-3-1
Constante diel�ctrica (1 MHz)	2.4	-	IEC 60250
Factor de p�rdida diel�ctrica (1 MHz)	13.4	-	IEC 60250
Factor de p�rdida diel�ctrica (100 Hz)	0.0	-	IEC 60250
Clasificaci�n de resistencia al fuego (UL 94)	60695		UL 94
Resistencia a la flexi�n	37	MPa	DIN EN ISO 527-2
Conductividad t�rmica	0.27	W/(m��K)	ISO 22007-4
Resistencia superficial	10���	��	IEC 60093
�ndice de seguimiento comparativo (CTI)	600	V	IEC 60112
Absorci�n de agua hasta la saturaci�n	0.2	%	ISO 62
Absorci�n de agua hasta la saturaci�n	0.2	%	ISO 62
Resistencia al impacto con entalla (Charpy)	9	kJ/m��	ISO 179/1eA
Resistencia al impacto (Charpy)	7.7	kJ/m��	ISO 179
Coefficiente de expansi�n t�rmica	1.6	10���/K	ISO 11359-2

Egenskap	Värde	Enhet	Standard
Dureza Shore D	72	Å° Shore D	ISO 868
Dureza a la presi3n de bala	110	MPa	ISO 2039

2. Kemisk beständighet

● Beständig ● Delvis beständig ● Ej beständig

Kemikalie	Konc.	Resultat
1,4-Dioxane	100	●
2-Hydroxypropionic acid (lactic acid)	90	●
Acetic acid	100	●
Acetone	100	●
Ammonia	â€”	●
Ammonium chloride	â€”	●
Amyl alcohol	â€”	●
Benzene	â€”	●
Bleaching solution	â€”	●
Boric acid	100	●
Brake fluid	â€”	●
Butyl acetate	â€”	●
Calcium chloride	â€”	●
Carbon disulphide	100	●
Carbon tetrachloride	â€”	●
Chlorine (gas)	100	●
Chlorobenzene	100	●
Chloroform	â€”	●
Citric acid	10	●
Cresol	â€”	●
Cyclohexanone	100	●
Cyclohexene	100	●
Diesel	â€”	●
Diethylene oxide	â€”	●
Ethyl acetate	100	●
Ethyl alcohol (ethanol)	96	●
Ethylene chloride	100	●

Kemikalie	Konc.	Resultat
Food oil	â€™	●
Formaldehyde, aqueous	40	●
Formic acid	10	●
Frost protection agent	â€™	●
Fuel oil	â€™	●
Fuel, aromatic free	â€™	●
Glycerine	100	●
Glycol	100	●
Heptane	100	●
Hydrochloric acid	10	●
Hydrochloric acid (concentrated)	â€™	●
Hydrofluoric acid	40	●
Hydrogen peroxide	10	●
Hydrogen sulfide, aqueous	â€™	●
Isopropyl alcohol	100	●
Linseed oil	â€™	●
Mercurochrome	â€™	●
Methyl alcohol (methanol)	100	●
Methyl ethyl ketone (MEK)	100	●
Methylene chloride	100	●
Milk	â€™	●
Mineral oils (aromatic free)	â€™	●
Nitric acid	50	●
Nitric acid	10	●
Nitrobenzene	â€™	●
Oxalic acid	â€™	●
Ozone (gas)	â‰‰ 0.5 ppm	●
Paraffin oil	100	●
Perchloroethylene	â€™	●
Petroleum ether	100	●
Phenol, aqueous	ca. 9	●
Phosphoric acid	50	●
Potassium hydroxide solution	50	●
Premium fuel	â€™	●
Propyl alcohol	â€™	●

Kemikalie	Konc.	Resultat
Pyridine	â€”	●
Silicone oil	â€”	●
Sodium carbonate, aqueous	â€”	●
Sodium chloride, aqueous	â€”	●
Sodium hydrogen sulfite	â€”	●
Sodium hydroxide solution (caustic soda)	60	●
Sodium hydroxide solution (caustic soda)	15	●
Sodium nitrate, aqueous	â€”	●
Sodium thiosulfate	â€”	●
Sulphuric acid	96	●
Tetrahydrofuran (THF)	100	●
Toluene	100	●
Transformer oil	â€”	●
Trichloroethylene	100	●
Vinegar, standard	5 - 10	●
Water	â€”	●
Xylene	â€”	●