PP-H AlphaPlus elemento de esquina 90°, 54 mm web, 1500x58 mm gris

Nº artículo	P2201180

Resistente Parcialmente resistente No resistente

Sustancia química	Concentración	Resist.
1,4-Dioxane	100	
2-Hydroxypropionic acid (lactic acid)	90	
Acetic acid	100	
Acetone	100	
Ammonia	–	
Ammonium chloride	–	
Amyl alcohol	–	
Benzene	–	
Bleaching solution	–	
Boric acid	100	
Brake fluid	–	
Butyl acetate	–	
Calcium chloride	–	
Carbon disulphide	100	
Carbon tetrachloride	–	
Chlorine (gas)	100	
Chlorobenzene	100	
Chloroform	–	
Citric acid	10	
Cresol	–	
Cyclohexanone	100	
Cyclohexene	100	
Diesel	–	
Diethylene oxide	–	
Ethyl acetate	100	

Sustancia química	Concentración	Resist.
Ethyl alcohol (ethanol)	96	🟢
Ethylene chloride	100	🟢
Food oil	–	🟢
Formaldehyde, aqueous	40	🟢
Formic acid	10	🟢
Frost protection agent	–	🟢
Fuel oil	–	🟢
Fuel, aromatic free	–	🟢
Glycerine	100	🟢
Glycol	100	🟢
Heptane	100	🟡
Hydrochloric acid	10	🟢
Hydrochloric acid (concentrated)	–	🟢
Hydrofluoric acid	40	🟢
Hydrogen peroxide	10	🟢
Hydrogen sulfide, aqueous	–	🟢
Isopropyl alcohol	100	🟢
Linseed oil	–	🟢
Mercurochrome	–	🟢
Methyl alcohol (methanol)	100	🟢
Methyl ethyl ketone (MEK)	100	🟢
Methylene chloride	100	🟡
Milk	–	🟢
Mineral oils (aromatic free)	–	🟢
Nitric acid	50	🔴
Nitric acid	10	🟢
Nitrobenzene	–	🟢
Oxalic acid	–	🟢
Ozone (gas)	≤ 0.5 ppm	🔴
Paraffin oil	100	🟢
Perchloroethylene	–	🟡
Petroleum ether	100	🟢

Sustancia química	Concentración	Resist.
Phenol, aqueous	ca. 9	🟢
Phosphoric acid	50	🟢
Potassium hydroxide solution	50	🟢
Premium fuel	–	🟢
Propyl alcohol	–	🟢
Pyridine	–	🟢
Silicone oil	–	🟢
Sodium carbonate, aqueous	–	🟢
Sodium chloride, aqueous	–	🟢
Sodium hydrogen sulfite	–	🟢
Sodium hydroxide solution (caustic soda)	60	🟢
Sodium hydroxide solution (caustic soda)	15	🟢
Sodium nitrate, aqueous	–	🟢
Sodium thiosulfate	–	🟢
Sulphuric acid	96	🟡
Tetrahydrofuran (THF)	100	🟡
Toluene	100	🟢
Transformer oil	–	🟢
Trichloroethylene	100	🟡
Vinegar, standard	5 - 10	🟢
Water	–	🟢
Xylene	–	🔴