

PP-H AlphaPlus perfil en U 5000x69x92 mm gris

Artikelnummer: P2201187

3. Resistencia química

A Utmärkt **B** God **C** Begränsad **D** Ej rekommenderad

SUSTANCIA QUÍMICA	BETYG	CONC.	TEMP.
1,4-Dioxane	partially_resistant	100%	
2-Hydroxypropionic acid (lactic acid)	resistant	90%	
Acetic acid	resistant	100%	
Acetone	resistant	100%	
Ammonia	resistant		
Ammonium chloride	resistant		
Amyl alcohol	resistant		
Benzene	partially_resistant		
Bleaching solution	partially_resistant		
Boric acid	resistant	100%	
Brake fluid	resistant		
Butyl acetate	partially_resistant		
Calcium chloride	resistant		
Carbon disulphide	partially_resistant	100%	
Carbon tetrachloride	not_resistant		
Chlorine (gas)	not_resistant	100%	
Chlorobenzene	resistant	100%	
Chloroform	partially_resistant		
Citric acid	resistant	10%	
Cresol	resistant		
Cyclohexanone	resistant	100%	

SUSTANCIA QUÍMICA	BETYG	CONC.	TEMP.
Cyclohexene	resistant	100%	
Diesel	resistant		
Diethylene oxide	partially_resistant		
Ethyl acetate	resistant	100%	
Ethyl alcohol (ethanol)	resistant	96%	
Ethylene chloride	resistant	100%	
Food oil	resistant		
Formaldehyde, aqueous	resistant	40%	
Formic acid	resistant	10%	
Frost protection agent	resistant		
Fuel oil	resistant		
Fuel, aromatic free	resistant		
Glycerine	resistant	100%	
Glycol	resistant	100%	
Heptane	partially_resistant	100%	
Hydrochloric acid	resistant	10%	
Hydrochloric acid (concentrated)	resistant		
Hydrofluoric acid	resistant	40%	
Hydrogen peroxide	resistant	10%	
Hydrogen sulfide, aqueous	resistant		
Isopropyl alcohol	resistant	100%	
Linseed oil	resistant		
Mercurochrome	resistant		
Methyl alcohol (methanol)	resistant	100%	
Methyl ethyl ketone (MEK)	resistant	100%	
Methylene chloride	partially_resistant	100%	
Milk	resistant		
Mineral oils (aromatic free)	resistant		
Nitric acid	not_resistant	50%	
Nitric acid	resistant	10%	
Nitrobenzene	resistant		

SUSTANCIA QUÍMICA	BETYG	CONC.	TEMP.
Oxalic acid	resistant		
Ozone (gas)	not_resistant	≤ 0.5 ppm%	
Paraffin oil	resistant	100%	
Perchloroethylene	partially_resistant		
Petroleum ether	resistant	100%	
Phenol, aqueous	resistant	ca. 9%	
Phosphoric acid	resistant	50%	
Potassium hydroxide solution	resistant	50%	
Premium fuel	resistant		
Propyl alcohol	resistant		
Pyridine	resistant		
Silicone oil	resistant		
Sodium carbonate, aqueous	resistant		
Sodium chloride, aqueous	resistant		
Sodium hydrogen sulfite	resistant		
Sodium hydroxide solution (caustic soda)	resistant	60%	
Sodium hydroxide solution (caustic soda)	resistant	15%	
Sodium nitrate, aqueous	resistant		
Sodium thiosulfate	resistant		
Sulphuric acid	partially_resistant	96%	
Tetrahydrofuran (THF)	partially_resistant	100%	
Toluene	resistant	100%	
Transformer oil	resistant		
Trichloroethylene	partially_resistant	100%	
Vinegar, standard	resistant	5 - 10%	
Water	resistant		
Xylene	not_resistant		