



# PVC U 2000x1000x3 mm verde

Artikelnr P1201161

## 1. Tekniskt datablad

| Egenskap                                      | Värde  | Enhet     | Standard         |
|-----------------------------------------------|--------|-----------|------------------|
| Densidad                                      | 1.53   | g/cm³     | ASTM D792        |
| Límite de resistencia a la tracción           | 48.8   | MPa       | ASTM D638        |
| Módulo de elasticidad (tracción)              | 2669   | MPa       | ASTM D638        |
| Resistencia a la tensión                      | 40     | MPa       | ISO 527          |
| Deformación a la rotura                       | 14     | %         | ISO 527          |
| Punto de fusión                               | 189.2  | °C        | ASTM D3418       |
| Temperatura de servicio máxima (corto plazo)  | 93.3   | °C        | UL 746B          |
| Temperatura de funcionamiento máxima          | 60     | °C        |                  |
| Temperatura mínima                            | -15    | °C        | UL 746B          |
| Deformación térmica (HDT/A)                   | 106.7  | °C        | ASTM D648        |
| Temperatura de ablandamiento Vicat (VST/B/50) | 75     | °C        | ISO 306          |
| Fuerza dieléctrica                            | 40     | kV/mm     | IEC 60243-1      |
| Resistividad volumétrica                      | 10¹¹ µ | Ω·cm      | DIN EN 62631-3-1 |
| Constante dieléctrica (1 MHz)                 | 3.1    | -         | IEC 60250        |
| Constante dieléctrica (100 Hz)                | 3.2    | -         | IEC 60250        |
| Factor de pérdida dieléctrica (1 MHz)         | 0.0    | -         | IEC 60250        |
| Resistencia a la flexión                      | 73.1   | MPa       | ASTM D790        |
| Conductividad térmica                         | 0.14   | W/(m·K)   | ISO 22007-4      |
| Resistencia superficial                       | 10¹¹ Ω | Ω         | DIN EN 62631-3-2 |
| Índice de seguimiento comparativo (CTI)       | 600    | V         | IEC 60112        |
| Absorción de agua hasta la saturación         | 0.5    | %         | ASTM D570        |
| Absorción de agua hasta la saturación         | 0.5    | %         | ASTM D570        |
| Resistencia al impacto con entalla (Charpy)   | 4      | kJ/m²     | ISO 179          |
| Resistencia al impacto (Charpy)               | 550    | kJ/m²     | DIN EN ISO 8256  |
| Coefficiente de expansión térmica             | 1.03   | 10⁻⁵ /K   | ASTM D696        |
| Dureza Shore D                                | 85     | ° Shore D | ASTM D2240       |
| Dureza a la presión de bala                   | 100    | MPa       | ISO 2039         |

| Egenskap | V rde | Enhet | Standard |
|----------|-------|-------|----------|
|----------|-------|-------|----------|

2. Kemisk best ndighet

● Best ndig ● Delvis best ndig ● Ej best ndig

| Kemikalie                             | Konc.   | Resultat |
|---------------------------------------|---------|----------|
| 1,4-Dioxane                           | 100%    | ●        |
| 2-Hydroxypropionic acid (lactic acid) | 90%     | ●        |
| Acetic acid                           | 100%    | ●        |
| Acetone                               | 100%    | ●        |
| Ammonia                               | conc.   | ●        |
| Ammonium chloride                     |         | ●        |
| Amyl alcohol                          |         | ●        |
| Apple juice                           |         | ●        |
| Benzene                               |         | ●        |
| Bleaching solution                    | 12.5 cl | ●        |
| Boric acid                            | 100%    | ●        |
| Brake fluid                           |         | ●        |
| Butyl acetate                         |         | ●        |
| Calcium chloride                      |         | ●        |
| Carbon disulphide                     | 100%    | ●        |
| Carbon tetrachloride                  |         | ●        |
| Chlorine (gas)                        | 100%    | ●        |
| Chlorobenzene                         | 100%    | ●        |
| Chloroform                            |         | ●        |
| Citric acid                           | 10%     | ●        |
| Cresol                                |         | ●        |
| Cyclohexanone                         | 100%    | ●        |
| Cyclohexene                           | 100%    | ●        |
| Diesel                                |         | ●        |
| Diethylene oxide                      |         | ●        |
| Ethyl acetate                         | 100%    | ●        |
| Ethyl alcohol (ethanol)               | 96%     | ●        |
| Ethylene chloride                     | 100%    | ●        |
| Food oil                              |         | ●        |
| Formaldehyde (aqueous)                | 40%     | ●        |

| Kemikalie                        | Konc.       | Resultat |
|----------------------------------|-------------|----------|
| Formic acid                      | 10%         | ●        |
| Frost protection agent           | â€™         | ●        |
| Fuel (aromatic free)             | â€™         | ●        |
| Fuel oil                         | â€™         | ●        |
| Glycerine                        | 100%        | ●        |
| Glycol                           | 100%        | ●        |
| Heptane                          | 100%        | ●        |
| Hydrochloric acid                | 10%         | ●        |
| Hydrochloric acid (concentrated) | conc.       | ●        |
| Hydrofluoric acid                | 40%         | ●        |
| Hydrogen peroxide                | 10%         | ●        |
| Hydrogen sulfide (aqueous)       | â€™         | ●        |
| Isopropyl alcohol                | 100%        | ●        |
| Linseed oil                      | â€™         | ●        |
| Mercurochrome                    | â€™         | ●        |
| Methyl alcohol (methanol)        | 100%        | ●        |
| Methyl ethyl ketone (MEK)        | 100%        | ●        |
| Methylene chloride               | 100%        | ●        |
| Milk                             | â€™         | ●        |
| Mineral oils (aromatic free)     | â€™         | ●        |
| Nitric acid                      | 50%         | ●        |
| Nitric acid                      | 10%         | ●        |
| Nitrobenzene                     | â€™         | ●        |
| Oxalic acid                      | â€™         | ●        |
| Ozone (gas)                      | â‰¤ 0.5 ppm | ●        |
| Paraffin oil                     | 100%        | ●        |
| Perchloroethylene                | â€™         | ●        |
| Petroleum                        | 100%        | ●        |
| Petroleum ether                  | 100%        | ●        |
| Phenol (aqueous)                 | ca. 9%      | ●        |
| Phosphoric acid                  | 50%         | ●        |
| Potassium hydroxide solution     | 50%         | ●        |
| Premium fuel                     | â€™         | ●        |
| Propyl alcohol                   | â€™         | ●        |

| Kemikalie                                | Konc.   | Resultat |
|------------------------------------------|---------|----------|
| Pyridine                                 | â€”     | ●        |
| Silicone oil                             | â€”     | ●        |
| Sodium carbonate (aqueous)               | â€”     | ●        |
| Sodium chloride (aqueous)                | â€”     | ●        |
| Sodium hydrogen sulfite                  | â€”     | ●        |
| Sodium hydroxide solution (caustic soda) | 15%     | ●        |
| Sodium hydroxide solution (caustic soda) | 60%     | ●        |
| Sodium nitrate (aqueous)                 | â€”     | ●        |
| Sodium thiosulfate                       | â€”     | ●        |
| Sulphuric acid                           | 96%     | ●        |
| Tetrahydrofuran (THF)                    | 100%    | ●        |
| Toluene                                  | 100%    | ●        |
| Transformer oil                          | â€”     | ●        |
| Trichloroethylene                        | 100%    | ●        |
| Vinegar (standard)                       | 5 - 10% | ●        |
| Water                                    | â€”     | ●        |
| Xylene                                   | â€”     | ●        |