



PVC U 2000x1000x8 mm rojo marrón

Artikelnr P2202004

Beständig Delvis beständig Ej beständig

| Kemikalie                             | Concentración | Temp. | Beständighet     |
|---------------------------------------|---------------|-------|------------------|
| 1,4-Dioxane                           | 100%          | 20 °C | Ej beständig     |
| 2-Hydroxypropionic acid (lactic acid) | 90%           | 20 °C | Beständig        |
| Acetic acid                           | 100%          | 20 °C | Beständig        |
| Acetone                               | 100%          | 20 °C | Ej beständig     |
| Ammonia                               | conc.         | 20 °C | Beständig        |
| Ammonium chloride                     | -             | 20 °C | Beständig        |
| Amyl alcohol                          | -             | 20 °C | Beständig        |
| Apple juice                           | -             | 20 °C | Beständig        |
| Benzene                               | -             | 20 °C | Ej beständig     |
| Bleaching solution                    | 12.5 cl       | 20 °C | Beständig        |
| Boric acid                            | 100%          | 20 °C | Beständig        |
| Brake fluid                           | -             | 20 °C | Beständig        |
| Butyl acetate                         | -             | 20 °C | Ej beständig     |
| Calcium chloride                      | -             | 20 °C | Beständig        |
| Carbon disulphide                     | 100%          | 20 °C | Ej beständig     |
| Carbon tetrachloride                  | -             | 20 °C | Ej beständig     |
| Chlorine (gas)                        | 100%          | 20 °C | Delvis beständig |
| Chlorobenzene                         | 100%          | 20 °C | Ej beständig     |
| Chloroform                            | -             | 20 °C | Ej beständig     |
| Citric acid                           | 10%           | 20 °C | Beständig        |
| Cresol                                | -             | 20 °C | Ej beständig     |
| Cyclohexanone                         | 100%          | 20 °C | Ej beständig     |
| Cyclohexene                           | 100%          | 20 °C | Beständig        |
| Diesel                                | -             | 20 °C | Beständig        |
| Diethylene oxide                      | -             | 20 °C | Ej beständig     |
| Ethyl acetate                         | 100%          | 20 °C | Ej beständig     |

| Kemikalie                        | Concentración | Temp. | Beständighet |
|----------------------------------|---------------|-------|--------------|
| Ethyl alcohol (ethanol)          | 96%           | 20 °C | <div></div>  |
| Ethylene chloride                | 100%          | 20 °C | <div></div>  |
| Food oil                         | -             | 20 °C | <div></div>  |
| Formaldehyde (aqueous)           | 40%           | 20 °C | <div></div>  |
| Formic acid                      | 10%           | 20 °C | <div></div>  |
| Frost protection agent           | -             | 20 °C | <div></div>  |
| Fuel (aromatic free)             | -             | 20 °C | <div></div>  |
| Fuel oil                         | -             | 20 °C | <div></div>  |
| Glycerine                        | 100%          | 20 °C | <div></div>  |
| Glycol                           | 100%          | 20 °C | <div></div>  |
| Heptane                          | 100%          | 20 °C | <div></div>  |
| Hydrochloric acid                | 10%           | 20 °C | <div></div>  |
| Hydrochloric acid (concentrated) | conc.         | 20 °C | <div></div>  |
| Hydrofluoric acid                | 40%           | 20 °C | <div></div>  |
| Hydrogen peroxide                | 10%           | 20 °C | <div></div>  |
| Hydrogen sulfide (aqueous)       | -             | 20 °C | <div></div>  |
| Isopropyl alcohol                | 100%          | 20 °C | <div></div>  |
| Linseed oil                      | -             | 20 °C | <div></div>  |
| Mercurochrome                    | -             | 20 °C | <div></div>  |
| Methyl alcohol (methanol)        | 100%          | 20 °C | <div></div>  |
| Methyl ethyl ketone (MEK)        | 100%          | 20 °C | <div></div>  |
| Methylene chloride               | 100%          | 20 °C | <div></div>  |
| Milk                             | -             | 20 °C | <div></div>  |
| Mineral oils (aromatic free)     | -             | 20 °C | <div></div>  |
| Nitric acid                      | 50%           | 20 °C | <div></div>  |
| Nitric acid                      | 10%           | 20 °C | <div></div>  |
| Nitrobenzene                     | -             | 20 °C | <div></div>  |
| Oxalic acid                      | -             | 20 °C | <div></div>  |
| Ozone (gas)                      | ≤ 0.5 ppm     | 20 °C | <div></div>  |
| Paraffin oil                     | 100%          | 20 °C | <div></div>  |
| Perchloroethylene                | -             | 20 °C | <div></div>  |
| Petroleum                        | 100%          | 20 °C | <div></div>  |
| Petroleum ether                  | 100%          | 20 °C | <div></div>  |
| Phenol (aqueous)                 | ca. 9%        | 20 °C | <div></div>  |

| Kemikalie                                | Concentración | Temp. | Beständighet |
|------------------------------------------|---------------|-------|--------------|
| Phosphoric acid                          | 50%           | 20 °C | ●            |
| Potassium hydroxide solution             | 50%           | 20 °C | ●            |
| Premium fuel                             | -             | 20 °C | ●            |
| Propyl alcohol                           | -             | 20 °C | ●            |
| Pyridine                                 | -             | 20 °C | ●            |
| Silicone oil                             | -             | 20 °C | ●            |
| Sodium carbonate (aqueous)               | -             | 20 °C | ●            |
| Sodium chloride (aqueous)                | -             | 20 °C | ●            |
| Sodium hydrogen sulfite                  | -             | 20 °C | ●            |
| Sodium hydroxide solution (caustic soda) | 15%           | 20 °C | ●            |
| Sodium hydroxide solution (caustic soda) | 60%           | 20 °C | ●            |
| Sodium nitrate (aqueous)                 | -             | 20 °C | ●            |
| Sodium thiosulfate                       | -             | 20 °C | ●            |
| Sulphuric acid                           | 96%           | 20 °C | ●            |
| Tetrahydrofuran (THF)                    | 100%          | 20 °C | ●            |
| Toluene                                  | 100%          | 20 °C | ●            |
| Transformer oil                          | -             | 20 °C | ●            |
| Trichloroethylene                        | 100%          | 20 °C | ●            |
| Vinegar (standard)                       | 5 - 10%       | 20 °C | ●            |
| Water                                    | -             | 20 °C | ●            |
| Xylene                                   | -             | 20 °C | ●            |