



PVC U 3000x1500x3 mm blanco

Artikelnr P2201968

1. Tekniskt datablad

Egenskap	V�rde	Enhet	Standard
Densidad	1.53	g/cm����	ASTM D792
L�mite de resistencia a la tracci����	48.8	MPa	ASTM D638
M��dulo de elasticidad (tracci����)	2669	MPa	ASTM D638
Resistencia a la tensi����	40	MPa	ISO 527
Deformaci���� a la rotura	14	%	ISO 527
Punto de fusi����	189.2	����	ASTM D3418
Temperatura de servicio m��xima (corto plazo)	93.3	����	UL 746B
Temperatura de funcionamiento m��xima	60	����	
Temperatura m��nima	-15	����	UL 746B
Deformaci���� t��rmica (HDT/A)	106.7	����	ASTM D648
Temperatura de ablandamiento Vicat (VST/B/50)	75	����	ISO 306
Fuerza diel����rica	40	kV/mm	IEC 60243-1
Resistividad volum����rica	10������	��������	DIN EN 62631-3-1
Constante diel����rica (1 MHz)	3.1	-	IEC 60250
Constante diel����rica (100 Hz)	3.2	-	IEC 60250
Factor de p��rdida diel����rica (1 MHz)	0.0	-	IEC 60250
Resistencia a la flexi����	73.1	MPa	ASTM D790
Conductividad t��rmica	0.14	W/(m����)	ISO 22007-4
Resistencia superficial	10������	����	DIN EN 62631-3-2
��ndice de seguimiento comparativo (CTI)	600	V	IEC 60112
Absorci���� de agua hasta la saturaci����	0.5	%	ASTM D570
Absorci���� de agua hasta la saturaci����	0.5	%	ASTM D570
Resistencia al impacto con entalla (Charpy)	4	kJ/m����	ISO 179
Resistencia al impacto (Charpy)	550	kJ/m����	DIN EN ISO 8256
Coefficiente de expansi���� t��rmica	1.03	10��������/K	ASTM D696
Dureza Shore D	85	���� Shore D	ASTM D2240
Dureza a la presi���� de bala	100	MPa	ISO 2039

Egenskap	V�rde	Enhet	Standard
----------	-------	-------	----------

2. Kemisk best ndighet

● Best ndig ● Delvis best ndig ● Ej best ndig

Kemikalie	Konc.	Resultat
1,4-Dioxane	100%	●
2-Hydroxypropionic acid (lactic acid)	90%	●
Acetic acid	100%	●
Acetone	100%	●
Ammonia	conc.	●
Ammonium chloride	��	●
Amyl alcohol	��	●
Apple juice	��	●
Benzene	��	●
Bleaching solution	12.5 cl	●
Boric acid	100%	●
Brake fluid	��	●
Butyl acetate	��	●
Calcium chloride	��	●
Carbon disulphide	100%	●
Carbon tetrachloride	��	●
Chlorine (gas)	100%	●
Chlorobenzene	100%	●
Chloroform	��	●
Citric acid	10%	●
Cresol	��	●
Cyclohexanone	100%	●
Cyclohexene	100%	�
Diesel	��	�
Diethylene oxide	��	�
Ethyl acetate	100%	�
Ethyl alcohol (ethanol)	96%	�
Ethylene chloride	100%	�
Food oil	��	�
Formaldehyde (aqueous)	40%	�

Kemikalie	Konc.	Resultat
Formic acid	10%	●
Frost protection agent	â€”	●
Fuel (aromatic free)	â€”	●
Fuel oil	â€”	●
Glycerine	100%	●
Glycol	100%	●
Heptane	100%	●
Hydrochloric acid	10%	●
Hydrochloric acid (concentrated)	conc.	●
Hydrofluoric acid	40%	●
Hydrogen peroxide	10%	●
Hydrogen sulfide (aqueous)	â€”	●
Isopropyl alcohol	100%	●
Linseed oil	â€”	●
Mercurochrome	â€”	●
Methyl alcohol (methanol)	100%	●
Methyl ethyl ketone (MEK)	100%	●
Methylene chloride	100%	●
Milk	â€”	●
Mineral oils (aromatic free)	â€”	●
Nitric acid	50%	●
Nitric acid	10%	●
Nitrobenzene	â€”	●
Oxalic acid	â€”	●
Ozone (gas)	â‰¤ 0.5 ppm	●
Paraffin oil	100%	●
Perchloroethylene	â€”	●
Petroleum	100%	●
Petroleum ether	100%	●
Phenol (aqueous)	ca. 9%	●
Phosphoric acid	50%	●
Potassium hydroxide solution	50%	●
Premium fuel	â€”	●
Propyl alcohol	â€”	●

Kemikalie	Konc.	Resultat
Pyridine	â€”	
Silicone oil	â€”	
Sodium carbonate (aqueous)	â€”	
Sodium chloride (aqueous)	â€”	
Sodium hydrogen sulfite	â€”	
Sodium hydroxide solution (caustic soda)	15%	
Sodium hydroxide solution (caustic soda)	60%	
Sodium nitrate (aqueous)	â€”	
Sodium thiosulfate	â€”	
Sulphuric acid	96%	
Tetrahydrofuran (THF)	100%	
Toluene	100%	
Transformer oil	â€”	
Trichloroethylene	100%	
Vinegar (standard)	5 - 10%	
Water	â€”	
Xylene	â€”	