

ABS 80x3000 mm natural

Artikelnr P1000044

1. Tekniskt datablad

| Egenskap | Värde | Enhet | Standard |
|---|----------------------|---------------------|-------------------|
| Densidad | 1.05 | g/cm ³ | ISO 1183 |
| Límite de resistencia a la tracción | 37 | MPa | ISO 527-2 |
| Módulo de elasticidad (tracción) | 2600 | MPa | ISO 527-2 |
| Resistencia a la tensión | 36.5 | MPa | ISO 527-2 |
| Deformación a la rotura | 5 | % | ISO 527-2 |
| Punto de fusión | 235 | °C | ISO 3146 |
| Temperatura de servicio máxima (corto plazo) | 93 | °C | UL746B |
| Temperatura de funcionamiento máxima | 82.5 | °C | |
| Deformación térmica (HDT/A) | 80 | °C | ISO 75-2 |
| Deformación térmica (HDT/B) | 100 | °C | ISO 75-2 |
| Temperatura de ablandamiento Vicat (VST/B/50) | 101 | °C | ISO 306 |
| Fuerza dieléctrica | 18 | kV/mm | IEC 60243-1 |
| Resistividad volumétrica | 10 ¹⁴ Ω·m | Ω·cm | IEC 60093 |
| Constante dieléctrica (1 MHz) | 2.6 | - | IEC 60250 |
| Factor de pérdida dieléctrica (1 MHz) | 0.0 | - | IEC 60250 |
| Resistencia a la flexión | 2500 | MPa | ISO 178 |
| Conductividad térmica | 0.2 | W/(m·K) | DIN 52612 |
| Resistencia superficial | 10 ¹⁴ Ω·m | Ω | IEC 60093 |
| Índice de seguimiento comparativo (CTI) | 600 | V | IEC 60112 |
| Absorción de agua hasta la saturación | 0.2 | % | ISO 62 |
| Absorción de agua hasta la saturación | 1 | % | ISO 62 |
| Resistencia al impacto con entalla (Charpy) | 25 | kJ/m ² | ISO 179/1eA |
| Resistencia al impacto (Charpy) | 170 | kJ/m ² | ISO 179/1eU |
| Coefficiente de expansión térmica | 0.8 | 10 ⁻⁶ /K | DIN 11359 |
| Dureza Shore D | 70 | ° Shore D | ISO 868 |
| Dureza Rockwell | 80 | R-scale | DIN EN ISO 2039-2 |

| Egenskap | V rde | Enhet | Standard |
|-----------------------------|-------|-------|------------|
| Dureza a la presi n de bala | 98 | MPa | ISO 2039-1 |

2. Kemisk best ndighet

● Best ndig
 ● Delvis best ndig
 ● Ej best ndig

| Kemikalie | Konc. | Resultat |
|---------------------------------------|-------|----------|
| 1,4-Dioxane | 100 | ● |
| 2-Hydroxypropionic acid (lactic acid) | 90 | ● |
| Acetic acid | 100 | ● |
| Acetone | 100 | ● |
| Ammonia |    | ● |
| Ammonium chloride |    | ● |
| Amyl alcohol |    | ● |
| Apple juice |    | ● |
| Benzene |    | ● |
| Brake fluid |    | ● |
| Butyl acetate |    | ● |
| Calcium chloride |    | ● |
| Carbon disulphide | 100 | ● |
| Carbon tetrachloride |    | ● |
| Chlorine gas | 100 | ● |
| Chlorobenzene | 100 | ● |
| Chloroform |    | ● |
| Citric acid | 10 | ● |
| Cresol |    | ● |
| Cyclohexanone | 100 | ● |
| Cyclohexene | 100 | ● |
| Diesel |    | ● |
| Ethyl acetate | 100 | ● |
| Ethyl alcohol (ethanol) | 96 | ● |
| Ethylene chloride | 100 | ● |
| Food oil |    | ● |
| Formaldehyde, aqueous | 40 | ● |
| Formic acid | 10 | ● |
| Frost protection agent |    | ● |
| Fuel oil |    | ● |

| Kemikalie | Konc. | Resultat |
|----------------------------------|-------|----------|
| Fuel, aromatic free | â€” | ● |
| Glycerine | 100 | ● |
| Glycol | 100 | ● |
| Heptane | 100 | ● |
| Hydrochloric acid | 10 | ● |
| Hydrochloric acid (concentrated) | â€” | ● |
| Hydrofluoric acid | 40 | ● |
| Hydrogen peroxide | 10 | ● |
| Hydrogen sulfide, aqueous | â€” | ● |
| Isopropyl alcohol | 100 | ● |
| Linseed oil | â€” | ● |
| Mercurochrome | â€” | ● |
| Methyl alcohol (methanol) | 100 | ● |
| Methyl ethyl ketone (MEK) | 100 | ● |
| Methylene chloride | 100 | ● |
| Milk | â€” | ● |
| Nitric acid | 50 | ● |
| Nitric acid | 10 | ● |
| Nitrobenzene | â€” | ● |
| Oxalic acid | â€” | ● |
| Ozone (gas) | â€” | ● |
| Paraffin oil | 100 | ● |
| Perchloroethylene | â€” | ● |
| Petroleum | 100 | ● |
| Petroleum ether | 100 | ● |
| Phenol, aqueous | 9 | ● |
| Phosphoric acid | 50 | ● |
| Potassium hydroxide solution | 50 | ● |
| Premium fuel | â€” | ● |
| Propyl alcohol | â€” | ● |
| Pyridine | â€” | ● |
| Silicone oil | â€” | ● |
| Sodium carbonate, aqueous | â€” | ● |
| Sodium chloride, aqueous | â€” | ● |

| Kemikalie | Konc. | Resultat |
|--|-------|----------|
| Sodium hydrogen sulfite | â€” | ● |
| Sodium hydroxide solution (caustic soda) | 60 | ● |
| Sodium hydroxide solution (caustic soda) | 15 | ● |
| Sodium nitrate, aqueous | â€” | ● |
| Sodium thiosulfate | â€” | ● |
| Sulphuric acid | 96 | ● |
| Tetrahydrofuran (THF) | 100 | ● |
| Toluene | 100 | ● |
| Transformer oil | â€” | ● |
| Trichloroethylene | 100 | ● |
| Vinegar (standard) | 5-10 | ● |
| Water | â€” | ● |
| Xylene | â€” | ● |