

PA12 130x3000 mm natural

Artikelnr P1000356

● Beständig
 ● Delvis beständig
 ● Ej beständig

Kemikalie	Concentration	Temp.	Beständighet
1,4-Dioxane	100	20 Å°C	Delvis beständig
2-Hydroxypropionic acid (lactic acid)	90	20 Å°C	Ej beständig
Acetone	100	20 Å°C	Delvis beständig
Ammonia	conc.	20 Å°C	Beständig
Ammonium chloride	â€”	20 Å°C	Beständig
Amyl alcohol	â€”	20 Å°C	Delvis beständig
Apple juice	â€”	20 Å°C	Beständig
Benzene	â€”	20 Å°C	Beständig
Bleaching solution	12.5 cl	20 Å°C	Ej beständig
Boric acid	100	20 Å°C	Delvis beständig
Brake fluid	â€”	20 Å°C	Beständig
Butyl acetate	â€”	20 Å°C	Beständig
Calcium chloride	â€”	20 Å°C	Beständig
Carbon disulphide	100	20 Å°C	Beständig
Carbon tetrachloride	â€”	20 Å°C	Beständig
Chlorine (gas)	100	20 Å°C	Ej beständig
Chlorobenzene	100	20 Å°C	Delvis beständig
Chloroform	â€”	20 Å°C	Ej beständig
Citric acid	10	20 Å°C	Beständig
Cresol	â€”	20 Å°C	Ej beständig
Cyclohexanone	100	20 Å°C	Beständig
Cyclohexene	100	20 Å°C	Delvis beständig
Diesel	â€”	20 Å°C	Beständig
Diethylene oxide	â€”	20 Å°C	Beständig
Ethyl acetate	100	20 Å°C	Beständig
Ethyl alcohol (ethanol)	96	20 Å°C	Delvis beständig
Ethylene chloride	100	20 Å°C	Ej beständig

Kemikalie	Concentraci3n	Temp.	Best3ndighet
Food oil	â€”	20 3C	●
Formaldehyde (aqueous)	40	20 3C	●
Formic acid	10	20 3C	●
Fuel (aromatic free)	â€”	20 3C	●
Fuel oil	â€”	20 3C	●
Glycerine	100	20 3C	●
Glycol	100	20 3C	●
Heptane	100	20 3C	●
Hydrochloric acid	10	20 3C	●
Hydrochloric acid (concentrated)	conc.	20 3C	●
Hydrofluoric acid	40	20 3C	●
Hydrogen peroxide	10	20 3C	●
Hydrogen sulfide (aqueous)	â€”	20 3C	●
Isopropyl alcohol	100	20 3C	●
Linseed oil	â€”	20 3C	●
Mercurochrome	â€”	20 3C	●
Methyl alcohol (methanol)	100	20 3C	●
Methyl ethyl ketone (MEK)	100	20 3C	●
Methylene chloride	100	20 3C	●
Milk	â€”	20 3C	●
Mineral oils (aromatic free)	â€”	20 3C	●
Nitric acid	50	20 3C	●
Nitric acid	10	20 3C	●
Nitrobenzene	â€”	20 3C	●
Oxalic acid	â€”	20 3C	●
Ozone (gas)	â‰ƒ 0.5 ppm	20 3C	●
Paraffin oil	100	20 3C	●
Perchloroethylene	â€”	20 3C	●
Petroleum	100	20 3C	●
Petroleum ether	100	20 3C	●
Phenol (aqueous)	ca. 9	20 3C	●
Phosphoric acid	50	20 3C	●
Potassium hydroxide solution	50	20 3C	●
Premium fuel	â€”	20 3C	●
Propyl alcohol	â€”	20 3C	●

Kemikalie	Concentration	Temp.	Beständighet
Pyridine	â€”	20 Å°C	●
Silicone oil	â€”	20 Å°C	●
Sodium carbonate (aqueous)	â€”	20 Å°C	●
Sodium chloride (aqueous)	â€”	20 Å°C	●
Sodium hydroxide solution (caustic soda)	15	20 Å°C	●
Sodium nitrate (aqueous)	â€”	20 Å°C	●
Sodium thiosulfate	â€”	20 Å°C	●
Sulphuric acid	96	20 Å°C	●
Tetrahydrofuran (THF)	100	20 Å°C	●
Toluene	100	20 Å°C	●
Transformer oil	â€”	20 Å°C	●
Trichloroethylene	100	20 Å°C	●
Vinegar (standard)	5 - 10	20 Å°C	●
Water	â€”	20 Å°C	●
Xylene	â€”	20 Å°C	●