

# PA6 E 155x1000 mm natural

Artikelnr P1000927

## 1. Tekniskt datablad

Egenskap	Värde	Enhet	Standard
Densidad	1.14	g/cm <sup>3</sup>	ISO 1183
Lımite de resistencia a la tracci3n	70	MPa	DIN EN ISO 527
M3dulo de elasticidad (tracci3n)	3250	MPa	ISO 527-2
Resistencia a la tensi3n	75	MPa	ISO 527-2
Deformaci3n a la rotura	40	%	ISO 527-2
Punto de fusi3n	220	C	ISO 3146
Temperatura de servicio m3xima (corto plazo)	160	C	
Temperatura de funcionamiento m3xima	90.5	C	
Temperatura m3nima	-36	C	
Deformaci3n t3rmica (HDT/A)	70	C	ISO 75-2
Deformaci3n t3rmica (HDT/B)	140	C	ISO 75-2
Temperatura de ablandamiento Vicat (VST/B/50)	190	C	ISO 306
Fuerza diel3ctrica	25	kV/mm	IEC 60243-1
Resistividad volum3trica	10 <sup>11</sup>  <sup>2</sup>	cm	IEC 60093
Constante diel3ctrica (1 MHz)	3.7	-	IEC 60250
Constante diel3ctrica (100 Hz)	3.9	-	IEC 60250
Factor de p3rdida diel3ctrica (1 MHz)	0.0	-	IEC 60250
Factor de p3rdida diel3ctrica (100 Hz)	0.0	-	IEC 60250
Clasificaci3n de resistencia al fuego (UL 94)	3		UL 94
Resistencia a la flexi3n	76	MPa	ISO 527-2
Conductividad t3rmica	0.28	W/(mK)	DIN 52612
Resistencia superficial	10 <sup>11</sup>  <sup>3</sup>		IEC 60093
ndice de seguimiento comparativo (CTI)	600	V	IEC 60112
Absorci3n de agua hasta la saturaci3n	2.5	%	ISO 62
Absorci3n de agua hasta la saturaci3n	9	%	ISO 62
Resistencia al impacto con entalla (Charpy)	5.5	kJ/m <sup>2</sup>	ISO 179/1eA

Egenskap	V�rde	Enhet	Standard
Coeficiente de expansi�n t�rmica	0.9	10��/K	ISO 11359
Dureza Shore D	82	� Shore D	DIN EN ISO 868
Dureza a la presi�n de bala	150	MPa	ISO 2039-1

## 2. Kemisk best ndighet

● Best ndig
 ● Delvis best ndig
 ● Ej best ndig

Kemikalie	Konc.	Resultat
1,4-Dioxane	100	●
2-Hydroxypropionic Acid	90	●
Acetic Acid	100	●
Acetone	100	●
Ammonia	conc.	●
Ammonium Chloride	��	●
Amyl Alcohol	��	●
Apple Juice	��	●
Benzene	��	●
Bleaching Solution	12.5 cl	●
Boric Acid	100	●
Brake Fluid	��	●
Butyl Acetate	��	●
Calcium Chloride	��	●
Carbon Disulfide	100	●
Carbon Tetrachloride	��	●
Chlorine (gas)	100	●
Chlorobenzene	100	●
Chloroform	��	●
Citric Acid	10	●
Cresol	��	●
Cyclohexanone	100	●
Cyclohexene	100	●
Diesel Fuel	��	●
Diethylene Oxide	��	●
Ethyl Acetate	100	●
Ethyl Alcohol	96	●

Kemikalie	Konc.	Resultat
Ethylene Chloride	100	●
Food Oil	â€”	●
Formaldehyde (aqueous)	40	●
Formic Acid	10	●
Frost Protection Agent	â€”	●
Fuel (aromatic free)	â€”	●
Glycerine	100	●
Glycol	100	●
Heating Oil	â€”	●
Heptane	100	●
Hydrochloric Acid	10	●
Hydrochloric Acid (concentrated)	conc.	●
Hydrofluoric Acid	40	●
Hydrogen Peroxide	10	●
Hydrogen Sulfide (aqueous)	â€”	●
Isopropyl Alcohol	100	●
Linseed Oil	â€”	●
Mercurochrome	â€”	●
Methyl Alcohol	100	●
Methyl Ethyl Ketone (MEK)	100	●
Methylene Chloride	100	●
Milk	â€”	●
Mineral Oils (aromatic free)	â€”	●
Nitric Acid	10	●
Nitric Acid	50	●
Nitrobenzene	â€”	●
Oxalic Acid	â€”	●
Ozone Gas	â‰ƒ 0.5 ppm	●
Paraffine Oil	100	●
Perchloroethylene	â€”	●
Petroleum	100	●
Petroleum Ether	100	●
Phenol (aqueous)	ca. 9	●
Phosphoric Acid	50	●
Potassium Hydroxide liquor	50	●

Kemikalie	Konc.	Resultat
Premium Fuel	â€”	●
Propyl Alcohol	â€”	●
Pyridine	â€”	●
Silicone Oil	â€”	●
Sodium Carbonate (aqueous)	â€”	●
Sodium Chloride (aqueous)	â€”	●
Sodium Hydrogen Sulfite	â€”	●
Sodium Hydroxide liquor	60	●
Sodium Hydroxide liquor	15	●
Sodium Nitrate (aqueous)	â€”	●
Sodium Thiosulfate	â€”	●
Sulfuric Acid	96	●
Tetrahydrofuran (THF)	100	●
Toluene	100	●
Transformer Oil	â€”	●
Trichloroethylene	100	●
Vinegar (standard)	5 - 10	●
Water	â€”	●
Xylene	â€”	●