



PA6 GF30 150x1000 mm negro

Artikelnr P1001430
Material PA

1. Tekniskt datablad

Egenskap	Värde	Enhet	Standard
Densidad	1.34	g/cm³	ISO 1183
Módulo de elasticidad (tracción)	8700	MPa	ISO 527-2
Punto de fusión	220	°C	ISO 3146
Temperatura de servicio máxima (corto plazo)	180	°C	
Temperatura de funcionamiento máxima	100	°C	
Temperatura mínima	-20	°C	
Deformación térmica (HDT/A)	210	°C	ISO 75-2
Resistividad volumétrica	10 ¹⁴	Ω·cm	IEC 60093
Resistencia a la flexión	120	MPa	ISO 527-2
Conductividad térmica	0.28	W/(m·K)	DIN 52612
Resistencia superficial	10 ¹³	Ω	IEC 60093
Absorción de agua hasta la saturación	2.1	%	ISO 62
Absorción de agua hasta la saturación	6.6	%	ISO 62
Resistencia al impacto con entalla (Charpy)	5	kJ/m²	ISO 179/1eA
Resistencia al impacto (Charpy)	50	kJ/m²	ISO 179/1eU
Coeficiente de expansión térmica	0.26	10 ⁻⁴ /K	DIN 11359
Dureza a la presión de bala	43	MPa	ISO 2039-1

2. Kemisk beständighet

● Beständig ● Delvis beständig ● Ej beständig

Kemikalie	Konc.	Resultat
1,4-Dioxane	100	●
2-Hydroxypropionic Acid	90	●
Acetic Acid	100	●
Acetone	100	●

Kemikalie	Konc.	Resultat
Ammonia	conc.	
Ammonium Chloride	-	
Amyl Alcohol	-	
Apple Juice	-	
Benzene	-	
Bleaching Solution	12.5 cl	
Boric Acid	100	
Brake Fluid	-	
Butyl Acetate	-	
Calcium Chloride	-	
Carbon Disulfide	100	
Carbon Tetrachloride	-	
Chlorine (gas)	100	
Chlorobenzene	100	
Chloroform	-	
Citric Acid	10	
Cresol	-	
Cyclohexanone	100	
Cyclohexene	100	
Diesel Fuel	-	
Diethylene Oxide	-	
Ethyl Acetate	100	
Ethyl Alcohol	96	
Ethylene Chloride	100	
Food Oil	-	
Formaldehyde (aqueous)	40	
Formic Acid	10	
Frost Protection Agent	-	
Fuel (aromatic free)	-	
Glycerine	100	
Glycol	100	
Heating Oil	-	
Heptane	100	
Hydrochloric Acid	10	

Kemikalie	Konc.	Resultat
Hydrochloric Acid (concentrated)	conc.	
Hydrofluoric Acid	40	
Hydrogen Peroxide	10	
Hydrogen Sulfide (aqueous)	-	
Isopropyl Alcohol	100	
Linseed Oil	-	
Mercurochrome	-	
Methyl Alcohol	100	
Methyl Ethyl Ketone (MEK)	100	
Methylene Chloride	100	
Milk	-	
Mineral Oils (aromatic free)	-	
Nitric Acid	10	
Nitric Acid	50	
Nitrobenzene	-	
Oxalic Acid	-	
Ozone Gas	≤ 0.5 ppm	
Paraffine Oil	100	
Perchloroethylene	-	
Petroleum	100	
Petroleum Ether	100	
Phenol (aqueous)	ca. 9	
Phosphoric Acid	50	
Potassium Hydroxide liquor	50	
Premium Fuel	-	
Propyl Alcohol	-	
Pyridine	-	
Silicone Oil	-	
Sodium Carbonate (aqueous)	-	
Sodium Chloride (aqueous)	-	
Sodium Hydrogen Sulfite	-	
Sodium Hydroxide liquor	60	
Sodium Hydroxide liquor	15	
Sodium Nitrate (aqueous)	-	

Kemikalie	Konc.	Resultat
Sodium Thiosulfate	-	
Sulfuric Acid	96	
Tetrahydrofuran (THF)	100	
Toluene	100	
Transformer Oil	-	
Trichloroethylene	100	
Vinegar (standard)	5 - 10	
Water	-	
Xylene	-	