



## PA6 GL 70x2000 mm verde

Artikelnr P1600310

Material PA

### 1. Tekniskt datablad

Egenskap	Värde	Enhet	Standard
Densidad	<b>1.1</b>	g/cm <sup>3</sup>	DIN EN ISO 1183-1
Límite de resistencia a la tracción	<b>67.5</b>	MPa	DIN EN ISO 527
Módulo de elasticidad (tracción)	<b>3000</b>	MPa	DIN EN ISO 527
Deformación a la rotura	<b>198.5</b>	%	DIN EN ISO 527
Punto de fusión	<b>218</b>	°C	ISO 11357-3
Temperatura de servicio máxima (corto plazo)	<b>162.5</b>	°C	
Temperatura de funcionamiento máxima	<b>109</b>	°C	
Temperatura mínima	<b>-40</b>	°C	
Deformación térmica (HDT/A)	<b>90</b>	°C	ISO 75
Fuerza dieléctrica	<b>20</b>	kV/mm	IEC 60243
Resistividad volumétrica	<b>10<sup>15</sup></b>	Ω·cm	DIN EN 62631-3-1
Constante dieléctrica (1 MHz)	<b>3.7</b>	-	IEC 60250
Factor de pérdida dieléctrica (100 Hz)	<b>0.02</b>	-	IEC 60250
Conductividad térmica	<b>0.3</b>	W/(m·K)	DIN 52612-1
Resistencia superficial	<b>10<sup>13</sup></b>	Ω	DIN EN 62631-3-2
Índice de seguimiento comparativo (CTI)	<b>600</b>	V	IEC 60112
Absorción de agua hasta la saturación	<b>5.65</b>	%	DIN EN ISO 62
Absorción de agua hasta la saturación	<b>5.65</b>	%	DIN EN ISO 62
Resistencia al impacto con entalla (Charpy)	<b>13</b>	kJ/m <sup>2</sup>	DIN EN ISO 179
Coefficiente de expansión térmica	<b>0.7</b>	10 <sup>-4</sup> /K	DIN 53752
Dureza Shore D	<b>81</b>	° Shore D	ISO 868

### 2. Kemisk beständighet

● Beständig ● Delvis beständig ● Ej beständig

Kemikalie

Konc.

Resultat

Kemikalie	Konc.	Resultat
1,4-Dioxane	100	●
2-Hydroxypropionic Acid	90	●
Acetic Acid	100	●
Acetone	100	●
Ammonia	conc.	●
Ammonium Chloride	-	●
Amyl Alcohol	-	●
Apple Juice	-	●
Benzene	-	●
Bleaching Solution	12.5 cl	●
Boric Acid	100	●
Brake Fluid	-	●
Butyl Acetate	-	●
Calcium Chloride	-	●
Carbon Disulfide	100	●
Carbon Tetrachloride	-	●
Chlorine (gas)	100	●
Chlorobenzene	100	●
Chloroform	-	●
Citric Acid	10	●
Cresol	-	●
Cyclohexanone	100	●
Cyclohexene	100	●
Diesel Fuel	-	●
Diethylene Oxide	-	●
Ethyl Acetate	100	●
Ethyl Alcohol	96	●
Ethylene Chloride	100	●
Food Oil	-	●
Formaldehyde (aqueous)	40	●
Formic Acid	10	●
Frost Protection Agent	-	●
Fuel (aromatic free)	-	●
Glycerine	100	●

Kemikalie	Konc.	Resultat
Glycol	100	●
Heating Oil	-	●
Heptane	100	●
Hydrochloric Acid	10	●
Hydrochloric Acid (concentrated)	conc.	●
Hydrofluoric Acid	40	●
Hydrogen Peroxide	10	●
Hydrogen Sulfide (aqueous)	-	●
Isopropyl Alcohol	100	●
Linseed Oil	-	●
Mercurochrome	-	●
Methyl Alcohol	100	●
Methyl Ethyl Ketone (MEK)	100	●
Methylene Chloride	100	●
Milk	-	●
Mineral Oils (aromatic free)	-	●
Nitric Acid	10	●
Nitric Acid	50	●
Nitrobenzene	-	●
Oxalic Acid	-	●
Ozone Gas	≤ 0.5 ppm	●
Paraffine Oil	100	●
Perchloroethylene	-	●
Petroleum	100	●
Petroleum Ether	100	●
Phenol (aqueous)	ca. 9	●
Phosphoric Acid	50	●
Potassium Hydroxide liquor	50	●
Premium Fuel	-	●
Propyl Alcohol	-	●
Pyridine	-	●
Silicone Oil	-	●
Sodium Carbonate (aqueous)	-	●
Sodium Chloride (aqueous)	-	●
Sodium Hydrogen Sulfite	-	●

Kemikalie	Konc.	Resultat
Sodium Hydroxide liquor	60	●
Sodium Hydroxide liquor	15	●
Sodium Nitrate (aqueous)	-	●
Sodium Thiosulfate	-	●
Sulfuric Acid	96	●
Tetrahydrofuran (THF)	100	●
Toluene	100	●
Transformer Oil	-	●
Trichloroethylene	100	●
Vinegar (standard)	5 - 10	●
Water	-	●
Xylene	-	●