



PA6.6 GF30 60x1000 mm negro

Artikelnr P1002491
Material PA

1. Tekniskt datablad

Egenskap	Värde	Enhet	Standard
Densidad	1.3	g/cm³	ISO 1183
Límite de resistencia a la tracción	100	MPa	ISO 527
Módulo de elasticidad (tracción)	5900	MPa	ISO 527-2
Resistencia a la tensión	100	MPa	ISO 527-2
Deformación a la rotura	5	%	ISO 527-2
Punto de fusión	257.5	°C	ISO 3146
Temperatura de servicio máxima (corto plazo)	175	°C	UL746B
Temperatura de funcionamiento máxima	120	°C	
Temperatura mínima	-20	°C	
Deformación térmica (HDT/A)	150	°C	ISO 75-2
Deformación térmica (HDT/B)	250	°C	ISO 75
Fuerza dieléctrica	30	kV/mm	IEC 60243-1
Resistividad volumétrica	~10 ¹⁴	Ω·cm	IEC 60093
Constante dieléctrica (1 MHz)	3.6	-	IEC 60250
Factor de pérdida dieléctrica (1 MHz)	0.0	-	IEC 60250
Conductividad térmica	0.31	W/(m·K)	DIN 52612
Resistencia superficial	~10 ¹³	Ω	IEC 60093
Índice de seguimiento comparativo (CTI)	475	V	IEC 60112
Absorción de agua hasta la saturación	3.6	%	ISO 62
Absorción de agua hasta la saturación	5.5	%	ISO 62
Resistencia al impacto con entalla (Charpy)	6	kJ/m²	ISO 179/1eA
Resistencia al impacto (Charpy)	50	kJ/m²	ISO 179/1eU
Coeficiente de expansión térmica	0.5	10 ⁻⁴ /K	ISO 11359
Dureza Shore D	85	° Shore D	ISO 868
Dureza a la presión de bala	165	MPa	ISO 2039-1

2. Kemisk beständighet

● Beständig ● Delvis beständig ● Ej beständig

Kemikalie	Konc.	Resultat
1,4-Dioxane	100	●
2-Hydroxypropionic Acid	90	●
Acetic Acid	100	●
Acetone	100	●
Ammonia	conc.	●
Ammonium Chloride	-	●
Amyl Alcohol	-	●
Apple Juice	-	●
Benzene	-	●
Bleaching Solution	12.5 cl	●
Boric Acid	100	●
Brake Fluid	-	●
Butyl Acetate	-	●
Calcium Chloride	-	●
Carbon Disulfide	100	●
Carbon Tetrachloride	-	●
Chlorine (gas)	100	●
Chlorobenzene	100	●
Chloroform	-	●
Citric Acid	10	●
Cresol	-	●
Cyclohexanone	100	●
Cyclohexene	100	●
Diesel Fuel	-	●
Diethylene Oxide	-	●
Ethyl Acetate	100	●
Ethyl Alcohol	96	●
Ethylene Chloride	100	●
Food Oil	-	●
Formaldehyde (aqueous)	40	●
Formic Acid	10	●
Frost Protection Agent	-	●

Kemikalie	Konc.	Resultat
Fuel (aromatic free)	-	●
Glycerine	100	●
Glycol	100	●
Heating Oil	-	●
Heptane	100	●
Hydrochloric Acid	10	●
Hydrochloric Acid (concentrated)	conc.	●
Hydrofluoric Acid	40	●
Hydrogen Peroxide	10	●
Hydrogen Sulfide (aqueous)	-	●
Isopropyl Alcohol	100	●
Linseed Oil	-	●
Mercurochrome	-	●
Methyl Alcohol	100	●
Methyl Ethyl Ketone (MEK)	100	●
Methylene Chloride	100	●
Milk	-	●
Mineral Oils (aromatic free)	-	●
Nitric Acid	10	●
Nitric Acid	50	●
Nitrobenzene	-	●
Oxalic Acid	-	●
Ozone Gas	≤ 0.5 ppm	●
Paraffine Oil	100	●
Perchloroethylene	-	●
Petroleum	100	●
Petroleum Ether	100	●
Phenol (aqueous)	ca. 9	●
Phosphoric Acid	50	●
Potassium Hydroxide liquor	50	●
Premium Fuel	-	●
Propyl Alcohol	-	●
Pyridine	-	●
Silicone Oil	-	●

Kemikalie	Konc.	Resultat
Sodium Carbonate (aqueous)	-	●
Sodium Chloride (aqueous)	-	●
Sodium Hydrogen Sulfite	-	●
Sodium Hydroxide liquor	60	●
Sodium Hydroxide liquor	15	●
Sodium Nitrate (aqueous)	-	●
Sodium Thiosulfate	-	●
Sulfuric Acid	96	●
Tetrahydrofuran (THF)	100	●
Toluene	100	●
Transformer Oil	-	●
Trichloroethylene	100	●
Vinegar (standard)	5 - 10	●
Water	-	●
Xylene	-	●