



PE Ultra HD 70x2000 mm azul oscuro

Artikelnr P1400265

1. Tekniskt datablad

Egenskap	VÄrde	Enhet	Standard
Densidad	0.9	g/cm ³	ISO 1183
L�mite de resistencia a la tracci�n	17	MPa	ISO 527
M�dulo de elasticidad (tracci�n)	691.7	MPa	ISO 527
Deformaci�n a la rotura	316.7	%	ISO 527
Punto de fusi�n	135	�C	ISO 3146
Temperatura de funcionamiento m�xima	10	�C	
Temperatura m�nima	-200	�C	
Resistividad volum�trica	10 ¹¹ ��	��	IEC 60093
Conductividad t�rmica	0.4	W/(m�K)	DIN 52612
Resistencia superficial	10 ¹¹ ��	��	IEC 60093
Absorci�n de agua hasta la saturaci�n	0.01	%	
Absorci�n de agua hasta la saturaci�n	0.01	%	
Resistencia al impacto con entalla (Charpy)	80	kJ/m�	ISO 11542-2
Resistencia al impacto (Charpy)	80	kJ/m�	ISO 11542-2
Coefficiente de expansi�n t�rmica	1.7	10 ⁻⁶ �/K	DIN 53 752
Dureza Shore D	60	� Shore D	shore D
Dureza a la presi�n de bala	35.6	MPa	ISO 2039-1

2. Kemisk best ndighet

● Best ndig ● Delvis best ndig ● Ej best ndig

Kemikalie	Konc.	Resultat
Acetic acid	3%	●
Calcium carbonate	��	●
Ethanol	10%	●
Iron oxide	��	●
Magnesium stearate	��	●

Kemikalie	Konc.	Resultat
Olive oil	â€”	●
Silicon dioxide	â€”	●
Titanium dioxide	â€”	●