PE-1000 30x1000 mm negro

Artikelnr   P2200785

● Beständig   ● Delvis beständig   ● Ej beständig

Kemikalie	Concentración	Temp.	Beständighet
1,4-Dioxane	100	20 °C	●
2-Hydroxypropionic acid (lactic acid)	90	20 °C	●
Acetic acid	100	20 °C	●
Acetone	100	20 °C	●
Ammonia	â€"	20 °C	●
Ammonium chloride	â€"	20 °C	●
Amyl alcohol	â€"	20 °C	●
Benzene	â€"	20 °C	●
Boric acid	100	20 °C	●
Brake fluid	â€"	20 °C	●
Butyl acetate	â€"	20 °C	●
Calcium chloride	â€"	20 °C	●
Citric acid	10	20 °C	●
Cresol	â€"	20 °C	●
Cyclohexanone	100	20 °C	●
Cyclohexene	100	20 °C	●
Diesel	â€"	20 °C	●
Ethyl acetate	100	20 °C	●
Ethyl alcohol (ethanol)	96	20 °C	●
Food oil	â€"	20 °C	●
Formaldehyde, aqueous	40	20 °C	●
Formic acid	10	20 °C	●
Frost protection agent	â€"	20 °C	●
Fuel oil	â€"	20 °C	●
Fuel, aromatic free	â€"	20 °C	●
Glycerine	100	20 °C	●
Glycol	100	20 °C	●

Kemikalie	ConcentraciÃ³n	Temp.	BestÃ¤ndighet
Heptane	100	20 Â°C	🟢
Hydrochloric acid	10	20 Â°C	🟢
Hydrochloric acid (concentrated)	â€"	20 Â°C	🟢
Hydrogen peroxide	10	20 Â°C	🟢
Isopropyl alcohol	100	20 Â°C	🟢
Linseed oil	â€"	20 Â°C	🟢
Mercurochrome	â€"	20 Â°C	🟢
Methyl alcohol (methanol)	100	20 Â°C	🟢
Methylene chloride	100	20 Â°C	🟡
Milk	â€"	20 Â°C	🟢
Mineral oils, aromatic free	â€"	20 Â°C	🟢
Nitric acid	10	20 Â°C	🟢
Nitric acid	50	20 Â°C	🟡
Nitrobenzene	â€"	20 Â°C	🟢
Oxalic acid	â€"	20 Â°C	🟢
Ozone (gas)	â‰¤ 0.5 ppm	20 Â°C	🟢
Paraffin oil	100	20 Â°C	🟢
Perchloroethylene	â€"	20 Â°C	🟡
Petroleum ether	100	20 Â°C	🟢
Phenol, aqueous	ca. 9	20 Â°C	🟢
Phosphoric acid	50	20 Â°C	🟢
Potassium hydroxide solution	50	20 Â°C	🟢
Premium fuel	â€"	20 Â°C	🟢
Propyl alcohol	â€"	20 Â°C	🟢
Silicone oil	â€"	20 Â°C	🟢
Sodium carbonate, aqueous	â€"	20 Â°C	🟢
Sodium chloride, aqueous	â€"	20 Â°C	🟢
Sodium hydrogen sulfite	â€"	20 Â°C	🟢
Sodium hydroxide solution (caustic soda)	60	20 Â°C	🟢
Sodium hydroxide solution (caustic soda)	15	20 Â°C	🟢
Sodium nitrate, aqueous	â€"	20 Â°C	🟢
Sodium thiosulfate	â€"	20 Â°C	🟢
Sulphuric acid	96	20 Â°C	🟡
Transformer oil	â€"	20 Â°C	🟢
Vinegar, standard	5 - 10	20 Â°C	🟢

Kemikalie	ConcentraciÃ³n	Temp.	BestÃ¤ndighet
Water	â€”	20 Â°C	🟢
Xylene	â€”	20 Â°C	🔴