PLASTSHOP.SE

Komplett teknisk dokumentation

PlastShop.se - 2026-03-28

PE-500 110x1000 mm natural

Artikelnr	P2200642
Material	PE

1. Tekniskt datablad

Egenskap	Värde	Enhet	Standard
Densidad	**1.3**	g/cm³	DIN EN ISO 1183-1
Límite de resistencia a la tracción	**24.2**	MPa	DIN EN ISO 527
Módulo de elasticidad (tracción)	**1100**	MPa	DIN EN ISO 527
Deformación a la rotura	**138.75**	%	DIN EN ISO 527
Punto de fusión	**132.5**	°C	ISO 11357-3
Temperatura de servicio máxima (corto plazo)	**80**	°C	
Temperatura de funcionamiento máxima	**54**	°C	
Temperatura mínima	**-100**	°C	
Temperatura de ablandamiento Vicat (VST/B/50)	**79**	°C	DIN EN ISO 306
Fuerza dieléctrica	**40**	kV/mm	IEC 60243
Resistividad volumétrica	**10^{14}**	Ω	DIN EN 62631-3-1
Constante dieléctrica (1 MHz)	**2.3**	-	IEC 60250
Factor de pérdida dieléctrica (1 MHz)	**0.0**	-	IEC 60250
Factor de pérdida dieléctrica (100 Hz)	**0.0**	-	IEC 60250
Clasificación de resistencia al fuego (UL 94)	**3**		UL 94
Conductividad térmica	**0.4**	W/(m·K)	DIN 52612-1
Resistencia superficial	**~10^{8}**	Ω	DIN EN 62631-3-2
Índice de seguimiento comparativo (CTI)	**600**	V	IEC 60112
Absorción de agua hasta la saturación	**0.0**	%	DIN EN ISO 62
Absorción de agua hasta la saturación	**0.0**	%	DIN EN ISO 62
Resistencia al impacto con entalla (Charpy)	**2**	kJ/m²	DIN EN ISO 179
Coeficiente de expansión térmica	**2.4**	10^{-4}/K	DIN 53752
Dureza Shore D	**65**	° Shore D	DIN EN ISO 868
Dureza a la presión de bala	**50**	MPa	ISO 2039-1

2. Kemisk beständighet

Beständig Delvis beständig Ej beständig

Kemikalie	Konc.	Resultat
1,4-Dioxane	100%	
2-Hydroxypropionic Acid	90%	
Acetaldehyde	-	
Acetic Acid	100%	
Acetic acid	3%	
Acetic acid	3% w/w	
Acetic acid	100%	
Acetic acid	3%	
Acetic acid	3%	
Acetic acid, aqueous	70%	
Acetic anhydride	-	
Acetone	-	
Acetone	100%	
Acronal dispersions	-	
Acrylonitrile	-	
Allyl acetate	-	
Allyl alcohol	96%	
Allyl chloride	-	
Aluminium chloride, aqueous	any	
Aluminium chloride, solid	-	
Aluminium fluoride	Conc.	
Aluminium hydroxide	-	
Aluminium metaphosphate	-	
Aluminium sulphate, aqueous saturated	-	
Aluminium sulphate, solid	-	
Ammonia	concentrated	
Ammonia, gaseous	-	
Ammonia, liquid	-	
Ammonium Chloride	-	
Amyl Alcohol	-	
Aniline	any	
Anisole	-	

Kemikalie	Konc.	Resultat
Apple Juice	-	🟢
Aqua regia	-	🔴
Beer	-	🟢
Benzaldehyde, aqueous	any	🟢
Benzene	technically grade	🔴
Benzene	-	🟢
Benzoic acid, aqueous	any	🟢
Benzyl alcohol	-	🟢
Bitumen	-	🟢
Bleaching Solution	12.5 cl	🟡
Boric Acid	100%	🟢
Brake Fluid	-	🟢
Bromine, liquid	100%	🔴
Butanol, aqueous	any	🟢
Butter	-	🟢
Butyl Acetate	-	🟢
Calcium Chloride	-	🟢
Calcium carbonate	-	🟢
Calcium carbonate	-	🟢
Calcium hypochlorite, aqueous suspension	any	🟢
Camphor	-	🟡
Carbon Disulfide	100%	🟡
Carbon Tetrachloride	-	🟡
Carbon disulphide	-	🔴
Caustic soda	any	🟢
Chlorine (gas)	100%	🟡
Chlorine, liquid	-	🔴
Chloroacetic acid, aqueous	≤85%	🟢
Chlorobenzene	-	🟡
Chlorobenzene	100%	🟡
Chloroform	technically grade	🟡
Chloroform	-	🟡
Chromosulphuric acid	-	🔴
Cider	-	🟢

Kemikalie	Konc.	Resultat
Citric Acid	10%	🟢
Citrus fruit juices	-	🟢
Coconut oil	-	🟢
Cod liver oil	-	🟢
Cresol	100%	🟢
Cresol	-	🟢
Cyclohexane	-	🟢
Cyclohexanol	-	🟢
Cyclohexanone	100%	🟢
Cyclohexanone	-	🟢
Cyclohexene	100%	🟢
Detergents	-	🟢
Dibutyl ether	-	🟢
Dibutyl phthalate	-	🟢
Dichloroacetic acid	-	🟢
Dichloroethane	-	🟡
Diesel Fuel	-	🟢
Diesel fuel	-	🟢
Diethylene Oxide	-	🟢
Diglycolic acid, aqueous	30%	🟢
Dimethyl formamide	-	🟢
Dimethylamine	-	🟢
Dioxane	-	🟢
Ethanol	10%	🟢
Ethanol	10%	🟢
Ethanol	10% v/v	🟢
Ethanol	10%	🟢
Ethyl Acetate	100%	🟢
Ethyl Alcohol	96%	🟢
Ethyl acetate	-	🟢
Ethylene Chloride	100%	🟢
Ethylene alcohol	96%	🟢
Ethylene chloride	-	🔴
Ethylene diamine	-	🟢
Ethylene glycol	-	🟢

Kemikalie	Konc.	Resultat
Ferric chloride, aqueous	any	🟢
Ferric nitrate, aqueous saturated	-	🟢
Ferric sulphate, aqueous saturated	-	🟢
Ferrous (II) chloride, aqueous saturated	-	🟢
Ferrous (II) sulfate, aqueous saturated	-	🟢
Ferrous (III) chloride, aqueous saturated	-	🟢
Ferrous (III) nitrate, aqueous saturated	-	🟢
Ferrous (III) sulfate, aqueous saturated	-	🟢
Food Oil	-	🟢
Formaldehyde (aqueous)	40%	🟢
Formaldehyde, aqueous	≤40%	🟢
Formic Acid	10%	🟢
Formic acid, aqueous	85%	🟢
Frigen 12 (Freon 12)	100%	🔴
Frost Protection Agent	-	🟢
Fruit juices	any	🟢
Fuel (aromatic free)	-	🟢
Fuel oil	-	🟢
Furfural	-	🟢
Glycerin, aqueous	any	🟢
Glycerine	100%	🟢
Glycol	100%	🟢
Glykol, aqueous	as supplied	🟢
Glysantin	-	🟢
Heating Oil	-	🟢
Heptane	-	🟢
Heptane	100%	🟢
Hexane	-	🟢
Honey	-	🟢
Hydrobromic acid, aqueous	50%	🟢
Hydrochloric Acid	10%	🟢
Hydrochloric Acid (concentrated)	concentrated	🟢
Hydrochloric acid, aqueous	any	🟢
Hydrofluoric Acid	40%	🟢
Hydrogen Peroxide	10%	🟢

Kemikalie	Konc.	Resultat
Hydrogen Sulfide (aqueous solution)	-	🟢
Ink	-	🟢
Iodine in potassium iodide solution	3% iodine	🟢
Isooctane	-	🟢
Isopropanol	-	🟢
Isopropyl Alcohol	100%	🟢
Isopropyl ether	-	🟡
Jam	-	🟢
Kerosene	-	🟢
Linseed Oil	-	🟢
Linseed oil	technically grade	🟢
Lithium bromide	-	🟢
Magnesium stearate	-	🟢
Magnesium stearate	-	🟢
Maleic acid, aqueous	any	🟢
Menthol	-	🟢
Mercurochrome	-	🟢
Mercury	-	🟢
Methanol	technically grade	🟢
Methyl Alcohol	100%	🟢
Methyl Ethyl Ketone (MEK)	100%	🔴
Methyl chloride	gaseous, technically grade	🔴
Methyl ethyl ketone	technically grade	🟢
Methylene Chloride	100%	🟡
Milk	-	🟢
Milk	-	🟢
Mineral Oil (aromatic free)	-	🟢
Molasses	-	🟢
Motor oil (heavy duty oil) without additives	-	🟢
Naphtha	-	🟢
Naphthalene	-	🟢
Nitric Acid	10%	🟢
Nitric Acid (50%)	50%	🟡
Nitric acid, aqueous	25%	🟢

Kemikalie	Konc.	Resultat
Nitric acid, aqueous	50%	🟡
Nitrobenzene	-	🟢
Nitrobenzene	-	🟢
Oils, ethereal	-	🟡
Oils, vegetable and animal	-	🟢
Oleic acid	-	🟢
Oleum	any	🔴
Olive oil	-	🟢
Olive oil	-	🟢
Olive oil	-	🟢
Olive oil	-	🟢
Oxalic Acid	-	🟢
Oxalic acid, aqueous	any	🟢
Oxygen	-	🟢
Ozone	50 ppm	🟡
Ozone Gas	≤0.5 ppm	🟢
Paraffine Oil	100%	🟢
Perchloric acid, aqueous	20%	🟢
Perchloric acid, aqueous	50%	🟢
Perchloric acid, aqueous	70%	🟢
Perchloroethylene	-	🟡
Petroleum	100%	🟢
Petroleum	-	🟢
Petroleum Ether	100%	🟢
Petroleum ether	-	🟢
Phenol	-	🟢
Phenol (aqueous)	≈9%	🟢
Phosphoric Acid	50%	🟢
Phosphoric acid, aqueous	50%	🟢
Phosphoric acid, aqueous	80% L 95%	🟢
Phosphorus trichloride	-	🔴
Photographic developers	-	🟢
Photographic emulsions	as supplied	🟢
Photographic fixing baths	as supplied	🟢

Kemikalie	Konc.	Resultat
Phthalic acid, aqueous	50%	🟢
Polyester resins	-	🔴
Potassium Hydroxide liquor	50%	🟢
Premium Fuel	-	🟢
Propionic acid, aqueous	any	🟢
Propyl Alcohol	-	🟢
Pyridine	-	🟢
Pyridine	-	🟢
Sea water	-	🟢
Silicon dioxide	-	🟢
Silicon dioxide	-	🟢
Silicone Oil	-	🟢
Silicone oil	technically grade	🟢
Sodium Carbonate (aqueous)	-	🟢
Sodium Chloride (aqueous)	-	🟢
Sodium Hydrogen Sulfite	-	🟢
Sodium Hydroxide liquor	15%	🟢
Sodium Hydroxide liquor (60%)	60%	🟢
Sodium Nitrate (aqueous)	-	🟢
Sodium Thiosulfate	-	🟢
Sodium borate	-	🟢
Sodium bromide	-	🟢
Sodium hydroxide, aqueous	any	🟢
Sodium hydroxide, solid	-	🟢
Stearic acid	-	🟢
Sugar syrup	-	🟢
Sulfuric Acid	96%	🟡
Sulphuric acid, aqueous	80%	🟢
Sulphuric acid, aqueous	≤50%	🟢
Sulphuric acid, aqueous	70%	🟢
Sulphuric acid, aqueous	98%	🟢
Tallow	technically grade	🟢
Tannic acid (tannin), aqueous	10%	🟢
Tetrahydrofuran	technically grade	🔴

Kemikalie	Konc.	Resultat
Tetrahydrofuran (THF)	100%	🟡
Thionyl chloride	-	🔴
Thiophene	-	🔴
Tin (II) chloride, aqueous	any	🟢
Tin (IV) chloride, aqueous	saturated	🟢
Titanium dioxide	-	🟢
Titanium dioxide	-	🟢
Toluene	technically grade	🔴
Toluene	100%	🟡
Transformer Oil	-	🟢
Transformer oil (insulating oil)	technically grade	🟢
Trichloracetic acid	technically grade	🟢
Trichloroethylene	technically grade	🔴
Trichloroethylene	100%	🟢
Triethanolamine	-	🟢
Triethanolamine	-	🟢
Turpentine oil	technically grade	🟢
Urea, aqueous	≤33%	🟢
Vaseline	technically grade	🟢
Vinegar (standard)	5-10%	🟢
Washing up liquids	usual	🟢
Water	-	🟢
Water, distilled	-	🟢
Wine	-	🟢
Xylene	-	🔴
Xylene	-	🔴
Zinc sludge	-	🟢