

PE-500 350x1000 mm natural

Artikelnr P2200654

● Beständig ● Delvis beständig ● Ej beständig

Kemikalie	Concentración	Temp.	Beständighet
1,4-Dioxane	100%	20 °C	●
2-Hydroxypropionic Acid	90%	20 °C	●
Acetaldehyde	-	20 °C	●
Acetic Acid	100%	20 °C	●
Acetic acid	3%	100 °C	●
Acetic acid	3% w/w	20 °C	●
Acetic acid	100%	20 °C	●
Acetic acid	3%	100 °C	●
Acetic acid	3%	100 °C	●
Acetic acid, aqueous	70%	20 °C	●
Acetic anhydride	-	20 °C	●
Acetone	-	20 °C	●
Acetone	100%	20 °C	●
Acronal dispersions	-	20 °C	●
Acrylonitrile	-	20 °C	●
Allyl acetate	-	20 °C	●
Allyl alcohol	96%	20 °C	●
Allyl chloride	-	20 °C	●
Aluminium chloride, aqueous	any	20 °C	●
Aluminium chloride, solid	-	20 °C	●
Aluminium fluoride	Conc.	20 °C	●
Aluminium hydroxide	-	20 °C	●
Aluminium metaphosphate	-	20 °C	●
Aluminium sulphate, aqueous saturated	-	20 °C	●
Aluminium sulphate, solid	-	20 °C	●
Ammonia	concentrated	20 °C	●

Kemikalie	Concentración	Temp.	Beständighet
Ammonia, gaseous	-	20 °C	●
Ammonia, liquid	-	20 °C	●
Ammonium Chloride	-	20 °C	●
Amyl Alcohol	-	20 °C	●
Aniline	any	20 °C	●
Anisole	-	20 °C	●
Apple Juice	-	20 °C	●
Aqua regia	-	20 °C	●
Beer	-	20 °C	●
Benzaldehyde, aqueous	any	20 °C	●
Benzene	-	20 °C	●
Benzene	technically grade	20 °C	●
Benzoic acid, aqueous	any	20 °C	●
Benzyl alcohol	-	20 °C	●
Bitumen	-	20 °C	●
Bleaching Solution	12.5 cl	20 °C	●
Boric Acid	100%	20 °C	●
Brake Fluid	-	20 °C	●
Bromine, liquid	100%	20 °C	●
Butanol, aqueous	any	20 °C	●
Butter	-	20 °C	●
Butyl Acetate	-	20 °C	●
Calcium Chloride	-	20 °C	●
Calcium carbonate	-	20 °C	●
Calcium carbonate	-	20 °C	●
Calcium hypochlorite, aqueous suspension	any	20 °C	●
Camphor	-	20 °C	●
Carbon Disulfide	100%	20 °C	●
Carbon Tetrachloride	-	20 °C	●
Carbon disulphide	-	20 °C	●
Caustic soda	any	20 °C	●
Chlorine (gas)	100%	20 °C	●
Chlorine, liquid	-	20 °C	●
Chloroacetic acid, aqueous	≤85%	20 °C	●

Kemikalie	Concentración	Temp.	Beständighet
Chlorobenzene	-	20 °C	
Chlorobenzene	100%	20 °C	
Chloroform	technically grade	20 °C	
Chloroform	-	20 °C	
Chromosulphuric acid	-	20 °C	
Cider	-	20 °C	
Citric Acid	10%	20 °C	
Citrus fruit juices	-	20 °C	
Coconut oil	-	20 °C	
Cod liver oil	-	20 °C	
Cresol	-	20 °C	
Cresol	100%	20 °C	
Cyclohexane	-	20 °C	
Cyclohexanol	-	20 °C	
Cyclohexanone	-	20 °C	
Cyclohexanone	100%	20 °C	
Cyclohexene	100%	20 °C	
Detergents	-	20 °C	
Dibutyl ether	-	20 °C	
Dibutyl phthalate	-	20 °C	
Dichloroacetic acid	-	20 °C	
Dichloroethane	-	20 °C	
Diesel Fuel	-	20 °C	
Diesel fuel	-	20 °C	
Diethylene Oxide	-	20 °C	
Diglycolic acid, aqueous	30%	20 °C	
Dimethyl formamide	-	20 °C	
Dimethylamine	-	20 °C	
Dioxane	-	20 °C	
Ethanol	10%	100 °C	
Ethanol	10% v/v	20 °C	
Ethanol	10%	100 °C	
Ethanol	10%	100 °C	
Ethyl Acetate	100%	20 °C	

Kemikalie	Concentración	Temp.	Beständighet
Ethyl Alcohol	96%	20 °C	●
Ethyl acetate	-	20 °C	●
Ethylene Chloride	100%	20 °C	●
Ethylene alcohol	96%	20 °C	●
Ethylene chloride	-	20 °C	●
Ethylene diamine	-	20 °C	●
Ethylene glycol	-	20 °C	●
Ferric chloride, aqueous	any	20 °C	●
Ferric nitrate, aqueous saturated	-	20 °C	●
Ferric sulphate, aqueous saturated	-	20 °C	●
Ferrous (II) chloride, aqueous saturated	-	20 °C	●
Ferrous (II) sulfate, aqueous saturated	-	20 °C	●
Ferrous (III) chloride, aqueous saturated	-	20 °C	●
Ferrous (III) nitrate, aqueous saturated	-	20 °C	●
Ferrous (III) sulfate, aqueous saturated	-	20 °C	●
Food Oil	-	20 °C	●
Formaldehyde (aqueous)	40%	20 °C	●
Formaldehyde, aqueous	≤40%	20 °C	●
Formic Acid	10%	20 °C	●
Formic acid, aqueous	85%	20 °C	●
Frigen 12 (Freon 12)	100%	20 °C	●
Frost Protection Agent	-	20 °C	●
Fruit juices	any	20 °C	●
Fuel (aromatic free)	-	20 °C	●
Fuel oil	-	20 °C	●
Furfural	-	20 °C	●
Glycerin, aqueous	any	20 °C	●
Glycerine	100%	20 °C	●
Glycol	100%	20 °C	●
Glykol, aqueous	as supplied	20 °C	●
Glysantin	-	20 °C	●
Heating Oil	-	20 °C	●
Heptane	100%	20 °C	●
Heptane	-	20 °C	●

Kemikalie	Concentración	Temp.	Beständighet
Hexane	-	20 °C	●
Honey	-	20 °C	●
Hydrobromic acid, aqueous	50%	20 °C	●
Hydrochloric Acid	10%	20 °C	●
Hydrochloric Acid (concentrated)	concentrated	20 °C	●
Hydrochloric acid, aqueous	any	20 °C	●
Hydrofluoric Acid	40%	20 °C	●
Hydrogen Peroxide	10%	20 °C	●
Hydrogen Sulfide (aqueous solution)	-	20 °C	●
Ink	-	20 °C	●
Iodine in potassium iodide solution	3% iodine	20 °C	●
Isooctane	-	20 °C	●
Isopropanol	-	20 °C	●
Isopropyl Alcohol	100%	20 °C	●
Isopropyl ether	-	20 °C	●
Jam	-	20 °C	●
Kerosene	-	20 °C	●
Linseed Oil	-	20 °C	●
Linseed oil	technically grade	20 °C	●
Lithium bromide	-	20 °C	●
Magnesium stearate	-	20 °C	●
Magnesium stearate	-	20 °C	●
Maleic acid, aqueous	any	20 °C	●
Menthol	-	20 °C	●
Mercurochrome	-	20 °C	●
Mercury	-	20 °C	●
Methanol	technically grade	20 °C	●
Methyl Alcohol	100%	20 °C	●
Methyl Ethyl Ketone (MEK)	100%	20 °C	●
Methyl chloride	gaseous, technically grade	20 °C	●
Methyl ethyl ketone	technically grade	20 °C	●
Methylene Chloride	100%	20 °C	●
Milk	-	20 °C	●
Milk	-	20 °C	●

Kemikalie	Concentración	Temp.	Beständighet
Mineral Oil (aromatic free)	-	20 °C	●
Molasses	-	20 °C	●
Motor oil (heavy duty oil) without additives	-	20 °C	●
Naphtha	-	20 °C	●
Naphthalene	-	20 °C	●
Nitric Acid	10%	20 °C	●
Nitric Acid (50%)	50%	20 °C	●
Nitric acid, aqueous	50%	20 °C	●
Nitric acid, aqueous	25%	20 °C	●
Nitrobenzene	-	20 °C	●
Nitrobenzene	-	20 °C	●
Oils, ethereal	-	20 °C	●
Oils, vegetable and animal	-	20 °C	●
Oleic acid	-	20 °C	●
Oleum	any	20 °C	●
Olive oil	-	20 °C	●
Olive oil	-	100 °C	●
Olive oil	-	100 °C	●
Olive oil	-	100 °C	●
Olive oil	-	100 °C	●
Oxalic Acid	-	20 °C	●
Oxalic acid, aqueous	any	20 °C	●
Oxygen	-	20 °C	●
Ozone	50 ppm	20 °C	●
Ozone Gas	≤0.5 ppm	20 °C	●
Paraffine Oil	100%	20 °C	●
Perchloric acid, aqueous	20%	20 °C	●
Perchloric acid, aqueous	50%	20 °C	●
Perchloric acid, aqueous	70%	20 °C	●
Perchloroethylene	-	20 °C	●
Petroleum	100%	20 °C	●
Petroleum	-	20 °C	●
Petroleum Ether	100%	20 °C	●
Petroleum ether	-	20 °C	●
Phenol	-	20 °C	●
Phenol (aqueous)	≈9%	20 °C	●

Kemikalie	Concentración	Temp.	Beständighet
Phosphoric Acid	50%	20 °C	●
Phosphoric acid, aqueous	80% L 95%	20 °C	●
Phosphoric acid, aqueous	50%	20 °C	●
Phosphorus trichloride	-	20 °C	●
Photographic developers	-	20 °C	●
Photographic emulsions	as supplied	20 °C	●
Photographic fixing baths	as supplied	20 °C	●
Phthalic acid, aqueous	50%	20 °C	●
Polyester resins	-	20 °C	●
Potassium Hydroxide liquor	50%	20 °C	●
Premium Fuel	-	20 °C	●
Propionic acid, aqueous	any	20 °C	●
Propyl Alcohol	-	20 °C	●
Pyridine	-	20 °C	●
Pyridine	-	20 °C	●
Sea water	-	20 °C	●
Silicon dioxide	-	20 °C	●
Silicon dioxide	-	20 °C	●
Silicone Oil	-	20 °C	●
Silicone oil	technically grade	20 °C	●
Sodium Carbonate (aqueous)	-	20 °C	●
Sodium Chloride (aqueous)	-	20 °C	●
Sodium Hydrogen Sulfite	-	20 °C	●
Sodium Hydroxide liquor	15%	20 °C	●
Sodium Hydroxide liquor (60%)	60%	20 °C	●
Sodium Nitrate (aqueous)	-	20 °C	●
Sodium Thiosulfate	-	20 °C	●
Sodium borate	-	20 °C	●
Sodium bromide	-	20 °C	●
Sodium hydroxide, aqueous	any	20 °C	●
Sodium hydroxide, solid	-	20 °C	●
Stearic acid	-	20 °C	●
Sugar syrup	-	20 °C	●
Sulfuric Acid	96%	20 °C	●
Sulphuric acid, aqueous	≤50%	20 °C	●

Kemikalie	Concentración	Temp.	Beständighet
Sulphuric acid, aqueous	70%	20 °C	●
Sulphuric acid, aqueous	80%	20 °C	●
Sulphuric acid, aqueous	98%	20 °C	●
Tallow	technically grade	20 °C	●
Tannic acid (tannin), aqueous	10%	20 °C	●
Tetrahydrofuran	technically grade	20 °C	●
Tetrahydrofuran (THF)	100%	20 °C	●
Thionyl chloride	-	20 °C	●
Thiophene	-	20 °C	●
Tin (II) chloride, aqueous	any	20 °C	●
Tin (IV) chloride, aqueous	saturated	20 °C	●
Titanium dioxide	-	20 °C	●
Titanium dioxide	-	20 °C	●
Toluene	technically grade	20 °C	●
Toluene	100%	20 °C	●
Transformer Oil	-	20 °C	●
Transformer oil (insulating oil)	technically grade	20 °C	●
Trichloroacetic acid	technically grade	20 °C	●
Trichloroethylene	technically grade	20 °C	●
Trichloroethylene	100%	20 °C	●
Triethanolamine	-	20 °C	●
Triethanolamine	-	20 °C	●
Turpentine oil	technically grade	20 °C	●
Urea, aqueous	≤33%	20 °C	●
Vaseline	technically grade	20 °C	●
Vinegar (standard)	5-10%	20 °C	●
Washing up liquids	usual	20 °C	●
Water	-	20 °C	●
Water, distilled	-	20 °C	●
Wine	-	20 °C	●
Xylene	-	20 °C	●
Xylene	-	20 °C	●
Zinc sludge	-	20 °C	●

