

## PE-HD 18x2000 mm natural

Artikelnr P1003313

Material PE

### 1. Tekniskt datablad

Egenskap	Värde	Enhet	Standard
Densidad	0.96	g/cm <sup>3</sup>	ISO 1183
Nombre comercial del producto	Polyeten (PE)		
Límite de resistencia a la tracción	20	MPa	ISO 527
Módulo de elasticidad (tracción)	1200	MPa	ISO 527
Resistencia a la tensión	13	MPa	ISO 527
Deformación a la rotura	200	%	ISO 527
Punto de fusión	135	°C	ISO 3146
Temperatura de servicio máxima (corto plazo)	95	°C	UL746B
Temperatura de funcionamiento máxima	76	°C	
Temperatura mínima	-51	°C	
Deformación térmica (HDT/A)	45	°C	ISO 75-2
Deformación térmica (HDT/B)	69	°C	ISO 75
Temperatura de ablandamiento Vicat (VST/B/50)	79	°C	ISO 306
Clasificación GHS	Brandfarlig vid höga temperaturer.. Damm kan orsaka mekanisk irritation vid bearbetning.		
Fuerza dieléctrica	45	kV/mm	IEC 60243-1
Riesgos físicos y químicos	Brandfarlig vid höga temperaturer.		
Resistividad volumétrica	10 <sup>12</sup>	Ω·cm	EN 61340-5-1
Riesgos para la salud	Damm kan orsaka mekanisk irritation vid bearbetning.		
Constante dieléctrica (1 MHz)	2.4	-	IEC 60250
Riesgos ambientales	Inga kända miljörisker. Inte biologiskt nedbrytbart.		
Constante dieléctrica (100 Hz)	2.3	-	IEC 60250
Factor de pérdida dieléctrica (1 MHz)	0.0	-	IEC 60250

Egenskap	Värde	Enhet	Standard
Factor de pérdida dieléctrica (100 Hz)	0.0	-	IEC 60250
Caracterización química	<b>Polyeten (PE), CAS 9002-88-4</b>		
Sustancias peligrosas	<b>Produkten innehåller inga farliga ämnen som påbjuder ett röjande.</b>		
Información general	<b>Produkten klassas som ofarlig.</b>		
Al inhalar	<b>Vid inandning av rök/ångor: flytta till frisk luft, håll varm, sök läkarvård vid behov.</b>		
Al contacto con la piel	<b>Vid kontakt med smält material: kyl omedelbart med kallt vatten. Ta inte bort stelnat material. Sök sjukvård.</b>		
En caso de contacto con los ojos	<b>Skölj med vatten i minst 15 minuter.</b>		
Al ingerir	<b>Då produkten är ofarlig behöver ingen första hjälp vidtas.</b>		
Medio de extinción adecuado	<b>Vatten, skum, gasformiga och torra släckmedel.</b>		
Medidas de precaución personal	<b>Inte tillämpligt.</b>		
Medidas de precaución ambiental	<b>Inte tillämpligt.</b>		
Métodos de saneamiento	<b>Mekanisk borttagning.</b>		
Consejos para el manejo seguro	<b>Sug bort spån vid bearbetning. Undvik överhettning.</b>		
Límites de exposición profesional	<b>Ingredienser med yrkesmässiga exponeringsgränser som ska övervakas: Inga.</b>		
Forma física	<b>Platta, rundstång, rör</b>		
Estado físico	<b>Fast</b>		
Color	<b>Naturvit till svart</b>		
Olor	<b>Luktfri</b>		
Condiciones para evitar	<b>Temperaturer över smältpunkten. Undvik UV-exponering.</b>		
Materiales para evitar	<b>Starka oxidanter, syror.</b>		
Productos de degradación peligrosos	<b>Koldioxid, kolmonoxid, vaxångor.</b>		
Toxicidad aguda	<b>Inga negativa hälsoeffekter förväntas vid hantering enligt rekommendationer.</b>		
Irritación cutánea	<b>Inte tillämpligt.</b>		
Irritación ocular	<b>Inte tillämpligt.</b>		
Sensibilización	<b>Ingen känd.</b>		
Impacto ambiental	<b>Materialet är inte skadligt för miljön, men är inte biologiskt nedbrytbart.</b>		
Gestión de residuos	<b>Kasseras enligt lokala bestämmelser. Materialåtervinning möjlig.</b>		
Clasificación de transporte	<b>Inte klassificerad som farligt gods.</b>		
Información REACH	<b>Produkten kräver ingen varningsetikett enligt EU-direktiv.</b>		
Exención de responsabilidad	<b>Informationen är baserad på nuvarande kunskapsnivå. Säkerhetsdatabladet gäller material tillhandahållet av PlastShop.se.</b>		
Resistencia a la flexión	20	MPa	ISO527-2
Nombre de la empresa	<b>ARC Gruppen AB // PlastShop.se</b>		
Teléfono	<b>013-328 9400</b>		

Egenskap	Värde	Enhet	Standard
Correo electrónico	<b>info@plastshop.se</b>		
Conductividad térmica	<b>0.4</b>	W/(m·K)	DIN 52612
Resistencia superficial	<b>10<sup>13</sup></b>	Ω	EN 61340-5-1
Índice de seguimiento comparativo (CTI)	<b>600</b>	V	IEC 60112
Productos de combustión peligrosos	<b>Vid förbränning kan koldioxid, kolmonoxid och vaxångor frigöras.</b>		
Combate contra incendios	<b>Använd andningsskydd. Brandrester omhändertas enligt lokala regler.</b>		
Información adicional	<b>Brandrester omhändertas efter gällande lokala regler.</b>		
Condiciones de almacenamiento	<b>Förvara torrt och svalt. Håll borta från öppen låga. Välventilerade utrymmen.</b>		
Protección respiratoria	<b>Adekvat ventilering vid bearbetning.</b>		
Protección de ojos	<b>Skyddsglasögon vid bearbetning.</b>		
Protección de manos	<b>Skyddshandskar vid kontakt med varmt material.</b>		
Protección corporal	<b>Arbetskläder.</b>		
Medidas de higiene	<b>Välventilerad arbetsplats. Undvik inandning av damm vid bearbetning.</b>		
Punto de fusión	<b>125-135°C (PE-HD), 130-145°C (PE-UHMW)</b>		
Temperatura de degradación	<b>&gt;350 °C</b>		
Punto de inflamación	<b>&gt;300 °C</b>		
Temperatura de autoignición	<b>ca 350°C</b>		
GefStoffV (Alemania)	<b>Ingen identifikation nödvändig.</b>		
Absorción de agua hasta la saturación	<b>0.01</b>	%	ISO 62
Absorción de agua hasta la saturación	<b>0.01</b>	%	ISO 62
Resistencia al impacto con entalla (Charpy)	<b>7.5</b>	kJ/m <sup>2</sup>	ISO 179/1eA
Resistencia al impacto (Charpy)	<b>15</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Coefficiente de expansión térmica	<b>2</b>	10 <sup>-4</sup> /K	ISO 11359
Densidad (20°C)	<b>0,93-0,97 g/cm<sup>3</sup> (PE-HD), ISO 1183</b>		
Solubilidad (agua)	<b>Olöslig i vatten</b>		
Riesgo de explosión	<b>Icke explosiv</b>		
Características de oxidación	<b>Ingen</b>		
Dureza Shore D	<b>60</b>	° Shore D	shore D
Dureza a la presión de bala	<b>50</b>	MPa	ISO 2039-1

## 2. Kemisk beständighet

● Beständig ● Delvis beständig ● Ej beständig

Kemikalie	Konc.	Resultat
1,4-Dioxane	100%	●
2-Hydroxypropionic acid (lactic acid)	90%	●
Acetaldehyde	-	●
Acetic acid	100%	●
Acetic acid	100%	●
Acetic acid, aqueous	70%	●
Acetic anhydride	-	●
Acetone	100%	●
Acetone	-	●
Acronal dispersions	-	●
Acrylonitrile	-	●
Allyl acetate	-	●
Allyl alcohol	96%	●
Allyl chloride	-	●
Aluminium chloride, aqueous	any	●
Aluminium chloride, solid	-	●
Aluminium fluoride	Conc.	●
Aluminium hydroxide	-	●
Aluminium metaphosphate	-	●
Aluminium sulphate, aqueous saturated	-	●
Aluminium sulphate, solid	-	●
Ammonia	concentrated	●
Ammonia, gaseous	-	●
Ammonia, liquid	-	●
Ammonium chloride	-	●
Amyl alcohol	-	●
Aniline	any	●
Anisole	-	●
Aqua regia	-	●
Beer	-	●
Benzaldehyde, aqueous	any	●
Benzene	technically grade	●
Benzene	-	●

Kemikalie	Konc.	Resultat
Benzoic acid, aqueous	any	●
Benzyl alcohol	-	●
Bitumen	-	●
Bleaching solution	12.5 cl	●
Boric acid	100%	●
Brake fluid	-	●
Bromine, liquid	100%	●
Butanol, aqueous	any	●
Butter	-	●
Butyl acetate	-	●
Calcium chloride	-	●
Calcium hypochlorite, aqueous suspension	any	●
Camphor	-	●
Carbon disulphide	100%	●
Carbon disulphide	-	●
Carbon tetrachloride	-	●
Caustic soda (NaOH)	any	●
Chlorine (gas)	100%	●
Chlorine, liquid	-	●
Chloroacetic acid, aqueous	≤85%	●
Chlorobenzene	100%	●
Chlorobenzene	-	●
Chloroform	-	●
Chloroform	technically grade	●
Chromosulphuric acid	-	●
Cider	-	●
Citric acid	10%	●
Citrus fruit juices	-	●
Coconut oil	-	●
Cod liver oil	-	●
Cresol	100%	●
Cresol	-	●
Cyclohexane	-	●
Cyclohexanol	-	●
Cyclohexanone	100%	●

Kemikalie	Konc.	Resultat
Cyclohexanone	-	●
Cyclohexene	100%	●
Detergents	-	●
Detergents	usual	●
Dibutyl ether	-	●
Dibutyl phthalate	-	●
Dichloroacetic acid	-	●
Dichloroethane	-	●
Diesel	-	●
Diesel	-	●
Diethylene oxide	-	●
Diglycolic acid, aqueous	30%	●
Dimethyl formamide (DMF)	-	●
Dimethylamine	-	●
Dioxane	-	●
Essential oils	-	●
Ethyl acetate	100%	●
Ethyl acetate	-	●
Ethyl alcohol (ethanol)	96%	●
Ethylene alcohol	96%	●
Ethylene chloride	-	●
Ethylene chloride	100%	●
Ethylene diamine	-	●
Ethylene glycol	-	●
Ferric chloride, aqueous	any	●
Ferric nitrate, aqueous saturated	-	●
Ferric nitrate, aqueous saturated	-	●
Ferric sulphate, aqueous saturated	-	●
Ferric sulphate, aqueous saturated	-	●
Ferrous (II) chloride, aqueous saturated	-	●
Ferrous (II) sulfate, aqueous saturated	-	●
Ferrous (III) chloride, aqueous saturated	-	●
Food oil	-	●
Formaldehyde (aqueous)	40%	●
Formaldehyde, aqueous	≤40%	●

Kemikalie	Konc.	Resultat
Formic acid	10%	●
Formic acid, aqueous	85%	●
Frigen 12 (Freon 12)	100%	●
Frost protection agent	-	●
Fruit juices	any	●
Fuel (aromatic free)	-	●
Fuel oil	-	●
Fuel oil	-	●
Furfural	-	●
Glycerine	100%	●
Glycerine, aqueous	any	●
Glycol	100%	●
Glycol, aqueous	as supplied	●
Glysantin	-	●
Heptane	100%	●
Heptane	-	●
Hexane	-	●
Honey	-	●
Hydrobromic acid, aqueous	50%	●
Hydrochloric acid	10%	●
Hydrochloric acid (concentrated)	concentrated	●
Hydrochloric acid, aqueous	any	●
Hydrofluoric acid	40%	●
Hydrogen peroxide	10%	●
Hydrogen sulfide (aqueous)	-	●
Ink	-	●
Iodine in potassium iodide solution	3% iodine	●
Isooctane	-	●
Isopropanol	-	●
Isopropyl alcohol	100%	●
Isopropyl ether	-	●
Jam	-	●
Kerosene	-	●
Linseed oil	technically grade	●

Kemikalie	Konc.	Resultat
Linseed oil	-	●
Lithium bromide	-	●
Maleic acid, aqueous	any	●
Menthol	-	●
Mercurochrome	-	●
Mercury	-	●
Methanol	technically grade	●
Methyl alcohol (methanol)	100%	●
Methyl chloride	gaseous, technically grade	●
Methyl ethyl ketone (MEK)	technically grade	●
Methyl ethyl ketone (MEK)	100%	●
Methylene chloride	100%	●
Milk	-	●
Milk	-	●
Mineral oil (aromatic free)	-	●
Molasses	-	●
Motor oil (heavy duty) without additives	-	●
Naphtha	-	●
Naphthalene	-	●
Nitric acid	10%	●
Nitric acid (50%)	50%	●
Nitric acid, aqueous	25%	●
Nitric acid, aqueous	50%	●
Nitrobenzene	-	●
Nitrobenzene	-	●
Oils, vegetable and animal	-	●
Oleic acid	-	●
Oleum (fuming sulphuric acid)	any	●
Oxalic acid	-	●
Oxalic acid, aqueous	any	●
Oxygen	-	●
Ozone	50 ppm	●
Ozone (gas)	≤0.5 ppm	●
Paraffin oil	100%	●
Perchloric acid, aqueous	50%	●

Kemikalie	Konc.	Resultat
Perchloric acid, aqueous	70%	●
Perchloric acid, aqueous	20%	●
Perchloroethylene	-	●
Petroleum	-	●
Petroleum ether	-	●
Petroleum ether	100%	●
Phenol	-	●
Phenol (aqueous)	≈9%	●
Phosphoric acid	50%	●
Phosphoric acid, aqueous	50%	●
Phosphoric acid, aqueous	80% L 95%	●
Phosphorus trichloride	-	●
Photographic developer	-	●
Photographic emulsion	as supplied	●
Photographic fixing bath	as supplied	●
Phthalic acid, aqueous	50%	●
Polyester resins	-	●
Potassium hydroxide solution	50%	●
Premium fuel	-	●
Propionic acid, aqueous	any	●
Propyl alcohol	-	●
Pyridine	-	●
Pyridine	-	●
Sea water	-	●
Silicone oil	-	●
Silicone oil	technically grade	●
Sodium borate (borax)	-	●
Sodium bromide	-	●
Sodium carbonate (aqueous)	-	●
Sodium chloride (aqueous)	-	●
Sodium hydrogen sulfite	-	●
Sodium hydroxide solution (60%)	60%	●
Sodium hydroxide solution (caustic soda)	15%	●
Sodium hydroxide, aqueous	any	●

Kemikalie	Konc.	Resultat
Sodium hydroxide, solid	-	●
Sodium nitrate (aqueous)	-	●
Sodium thiosulfate	-	●
Stearic acid	-	●
Sugar syrup	-	●
Sulphuric acid	96%	●
Sulphuric acid, aqueous	98%	●
Sulphuric acid, aqueous	80%	●
Sulphuric acid, aqueous	70%	●
Sulphuric acid, aqueous	≤50%	●
Tallow	technically grade	●
Tannic acid (tannin), aqueous	10%	●
Tetrahydrofuran (THF)	technically grade	●
Tetrahydrofuran (THF)	100%	●
Thionyl chloride	-	●
Thiophene	-	●
Tin (II) chloride, aqueous	any	●
Tin (IV) chloride, aqueous	saturated	●
Toluene	technically grade	●
Toluene	100%	●
Transformer oil	-	●
Transformer oil (insulating oil)	technically grade	●
Trichloroacetic acid	technically grade	●
Trichloroethylene	100%	●
Trichloroethylene	technically grade	●
Triethanolamine	-	●
Turpentine oil	technically grade	●
Urea, vattenl.	≤33%	●
Vaseline	technically grade	●
Vinegar (standard)	5-10%	●
Water	-	●
Water, distilled	-	●
Wine	-	●
Xylene	-	●
Xylene	-	●

**Kemikalie**

**Konc.**

**Resultat**

Zinc sludge

-

