PE-HD 6 1/2"x1220 mm natural

Artikelnr P2200417

Beständig Delvis beständig Ej beständig

Kemikalie	Concentración	Temp.	Beständighet
1,4-Dioxane	100%	20 °C	
2-Hydroxypropionic acid (lactic acid)	90%	20 °C	
Acetaldehyde	-	20 °C	
Acetic acid	100%	20 °C	
Acetic acid	100%	20 °C	
Acetic acid, aqueous	70%	20 °C	
Acetic anhydride	-	20 °C	
Acetone	-	20 °C	
Acetone	100%	20 °C	
Acronal dispersions	-	20 °C	
Acrylonitrile	-	20 °C	
Allyl acetate	-	20 °C	
Allyl alcohol	96%	20 °C	
Allyl chloride	-	20 °C	
Aluminium chloride, aqueous	any	20 °C	
Aluminium chloride, solid	-	20 °C	
Aluminium fluoride	Conc.	20 °C	
Aluminium hydroxide	-	20 °C	
Aluminium metaphosphate	-	20 °C	
Aluminium sulphate, aqueous saturated	-	20 °C	
Aluminium sulphate, solid	-	20 °C	
Ammonia	concentrated	20 °C	
Ammonia, gaseous	-	20 °C	
Ammonia, liquid	-	20 °C	
Ammonium chloride	-	20 °C	
Amyl alcohol	-	20 °C	

Kemikalie	Concentración	Temp.	Beständighet
Aniline	any	20 °C	🟢
Anisole	-	20 °C	🟢
Aqua regia	-	20 °C	🔴
Beer	-	20 °C	🟢
Benzaldehyde, aqueous	any	20 °C	🟢
Benzene	-	20 °C	🟢
Benzene	technically grade	20 °C	🔴
Benzoic acid, aqueous	any	20 °C	🟢
Benzyl alcohol	-	20 °C	🟢
Bitumen	-	20 °C	🟢
Bleaching solution	12.5 cl	20 °C	🟡
Boric acid	100%	20 °C	🟢
Brake fluid	-	20 °C	🟢
Bromine, liquid	100%	20 °C	🔴
Butanol, aqueous	any	20 °C	🟢
Butter	-	20 °C	🟢
Butyl acetate	-	20 °C	🟢
Calcium chloride	-	20 °C	🟢
Calcium hypochlorite, aqueous suspension	any	20 °C	🟢
Camphor	-	20 °C	🟡
Carbon disulphide	100%	20 °C	🟡
Carbon disulphide	-	20 °C	🔴
Carbon tetrachloride	-	20 °C	🟡
Caustic soda (NaOH)	any	20 °C	🟢
Chlorine (gas)	100%	20 °C	🟡
Chlorine, liquid	-	20 °C	🔴
Chloroacetic acid, aqueous	≤85%	20 °C	🟢
Chlorobenzene	100%	20 °C	🟡
Chlorobenzene	-	20 °C	🟡
Chloroform	-	20 °C	🟡
Chloroform	technically grade	20 °C	🟡
Chromosulphuric acid	-	20 °C	🔴
Cider	-	20 °C	🟢
Citric acid	10%	20 °C	🟢

Kemikalie	Concentración	Temp.	Beständighet
Citrus fruit juices	-	20 °C	🟢
Coconut oil	-	20 °C	🟢
Cod liver oil	-	20 °C	🟢
Cresol	-	20 °C	🟢
Cresol	100%	20 °C	🟢
Cyclohexane	-	20 °C	🟢
Cyclohexanol	-	20 °C	🟢
Cyclohexanone	100%	20 °C	🟢
Cyclohexanone	-	20 °C	🟢
Cyclohexene	100%	20 °C	🟢
Detergents	-	20 °C	🟢
Detergents	usual	20 °C	🟢
Dibutyl ether	-	20 °C	🟢
Dibutyl phthalate	-	20 °C	🟢
Dichloroacetic acid	-	20 °C	🟢
Dichloroethane	-	20 °C	🟡
Diesel	-	20 °C	🟢
Diesel	-	20 °C	🟢
Diethylene oxide	-	20 °C	🟢
Diglycolic acid, aqueous	30%	20 °C	🟢
Dimethyl formamide (DMF)	-	20 °C	🟢
Dimethylamine	-	20 °C	🟢
Dioxane	-	20 °C	🟢
Essential oils	-	20 °C	🟡
Ethyl acetate	-	20 °C	🟢
Ethyl acetate	100%	20 °C	🟢
Ethyl alcohol (ethanol)	96%	20 °C	🟢
Ethylene alcohol	96%	20 °C	🟢
Ethylene chloride	100%	20 °C	🟢
Ethylene chloride	-	20 °C	🔴
Ethylene diamine	-	20 °C	🟢
Ethylene glycol	-	20 °C	🟢
Ferric chloride, aqueous	any	20 °C	🟢
Ferric nitrate, aqueous saturated	-	20 °C	🟢
Ferric nitrate, aqueous saturated	-	20 °C	🟢

Kemikalie	Concentración	Temp.	Beständighet
Ferric sulphate, aqueous saturated	-	20 °C	●
Ferric sulphate, aqueous saturated	-	20 °C	●
Ferrous (II) chloride, aqueous saturated	-	20 °C	●
Ferrous (II) sulfate, aqueous saturated	-	20 °C	●
Ferrous (III) chloride, aqueous saturated	-	20 °C	●
Food oil	-	20 °C	●
Formaldehyde (aqueous)	40%	20 °C	●
Formaldehyde, aqueous	≤40%	20 °C	●
Formic acid	10%	20 °C	●
Formic acid, aqueous	85%	20 °C	●
Frigen 12 (Freon 12)	100%	20 °C	●
Frost protection agent	-	20 °C	●
Fruit juices	any	20 °C	●
Fuel (aromatic free)	-	20 °C	●
Fuel oil	-	20 °C	●
Fuel oil	-	20 °C	●
Furfural	-	20 °C	●
Glycerine	100%	20 °C	●
Glycerine, aqueous	any	20 °C	●
Glycol	100%	20 °C	●
Glycol, aqueous	as supplied	20 °C	●
Glysantin	-	20 °C	●
Heptane	100%	20 °C	●
Heptane	-	20 °C	●
Hexane	-	20 °C	●
Honey	-	20 °C	●
Hydrobromic acid, aqueous	50%	20 °C	●
Hydrochloric acid	10%	20 °C	●
Hydrochloric acid (concentrated)	concentrated	20 °C	●
Hydrochloric acid, aqueous	any	20 °C	●
Hydrofluoric acid	40%	20 °C	●
Hydrogen peroxide	10%	20 °C	●
Hydrogen sulfide (aqueous)	-	20 °C	●
Ink	-	20 °C	●
Iodine in potassium iodide solution	3% iodine	20 °C	●

Kemikalie	Concentración	Temp.	Beständighet
Isooctane	-	20 °C	🟢
Isopropanol	-	20 °C	🟢
Isopropyl alcohol	100%	20 °C	🟢
Isopropyl ether	-	20 °C	🟡
Jam	-	20 °C	🟢
Kerosene	-	20 °C	🟢
Linseed oil	technically grade	20 °C	🟢
Linseed oil	-	20 °C	🟢
Lithium bromide	-	20 °C	🟢
Maleic acid, aqueous	any	20 °C	🟢
Menthol	-	20 °C	🟢
Mercurochrome	-	20 °C	🟢
Mercury	-	20 °C	🟢
Methanol	technically grade	20 °C	🟢
Methyl alcohol (methanol)	100%	20 °C	🟢
Methyl chloride	gaseous, technically grade	20 °C	🔴
Methyl ethyl ketone (MEK)	technically grade	20 °C	🟢
Methyl ethyl ketone (MEK)	100%	20 °C	🔴
Methylene chloride	100%	20 °C	🟡
Milk	-	20 °C	🟢
Milk	-	20 °C	🟢
Mineral oil (aromatic free)	-	20 °C	🟢
Molasses	-	20 °C	🟢
Motor oil (heavy duty) without additives	-	20 °C	🟢
Naphtha	-	20 °C	🟢
Naphthalene	-	20 °C	🟢
Nitric acid	10%	20 °C	🟢
Nitric acid (50%)	50%	20 °C	🟡
Nitric acid, aqueous	50%	20 °C	🟡
Nitric acid, aqueous	25%	20 °C	🟢
Nitrobenzene	-	20 °C	🟢
Nitrobenzene	-	20 °C	🟢
Oils, vegetable and animal	-	20 °C	🟢
Oleic acid	-	20 °C	🟢

Kemikalie	Concentración	Temp.	Beständighet
Oleum (fuming sulphuric acid)	any	20 °C	🔴
Oxalic acid	-	20 °C	🟢
Oxalic acid, aqueous	any	20 °C	🟢
Oxygen	-	20 °C	🟢
Ozone	50 ppm	20 °C	🟡
Ozone (gas)	≤0.5 ppm	20 °C	🟢
Paraffin oil	100%	20 °C	🟢
Perchloric acid, aqueous	50%	20 °C	🟢
Perchloric acid, aqueous	70%	20 °C	🟢
Perchloric acid, aqueous	20%	20 °C	🟢
Perchloroethylene	-	20 °C	🟡
Petroleum	-	20 °C	🟢
Petroleum ether	100%	20 °C	🟢
Petroleum ether	-	20 °C	🟢
Phenol	-	20 °C	🟢
Phenol (aqueous)	≈9%	20 °C	🟢
Phosphoric acid	50%	20 °C	🟢
Phosphoric acid, aqueous	80% L 95%	20 °C	🟢
Phosphoric acid, aqueous	50%	20 °C	🟢
Phosphorus trichloride	-	20 °C	🔴
Photographic developer	-	20 °C	🟢
Photographic emulsion	as supplied	20 °C	🟢
Photographic fixing bath	as supplied	20 °C	🟢
Phthalic acid, aqueous	50%	20 °C	🟢
Polyester resins	-	20 °C	🔴
Potassium hydroxide solution	50%	20 °C	🟢
Premium fuel	-	20 °C	🟢
Propionic acid, aqueous	any	20 °C	🟢
Propyl alcohol	-	20 °C	🟢
Pyridine	-	20 °C	🟢
Pyridine	-	20 °C	🟢
Sea water	-	20 °C	🟢
Silicone oil	-	20 °C	🟢
Silicone oil	technically grade	20 °C	🟢

Kemikalie	Concentración	Temp.	Beständighet
Sodium borate (borax)	-	20 °C	🟢
Sodium bromide	-	20 °C	🟢
Sodium carbonate (aqueous)	-	20 °C	🟢
Sodium chloride (aqueous)	-	20 °C	🟢
Sodium hydrogen sulfite	-	20 °C	🟢
Sodium hydroxide solution (60%)	60%	20 °C	🟢
Sodium hydroxide solution (caustic soda)	15%	20 °C	🟢
Sodium hydroxide, aqueous	any	20 °C	🟢
Sodium hydroxide, solid	-	20 °C	🟢
Sodium nitrate (aqueous)	-	20 °C	🟢
Sodium thiosulfate	-	20 °C	🟢
Stearic acid	-	20 °C	🟢
Sugar syrup	-	20 °C	🟢
Sulphuric acid	96%	20 °C	🟡
Sulphuric acid, aqueous	98%	20 °C	🟢
Sulphuric acid, aqueous	≤50%	20 °C	🟢
Sulphuric acid, aqueous	70%	20 °C	🟢
Sulphuric acid, aqueous	80%	20 °C	🟢
Tallow	technically grade	20 °C	🟢
Tannic acid (tannin), aqueous	10%	20 °C	🟢
Tetrahydrofuran (THF)	technically grade	20 °C	🔴
Tetrahydrofuran (THF)	100%	20 °C	🟡
Thionyl chloride	-	20 °C	🔴
Thiophene	-	20 °C	🔴
Tin (II) chloride, aqueous	any	20 °C	🟢
Tin (IV) chloride, aqueous	saturated	20 °C	🟢
Toluene	100%	20 °C	🟡
Toluene	technically grade	20 °C	🔴
Transformer oil	-	20 °C	🟢
Transformer oil (insulating oil)	technically grade	20 °C	🟢
Trichloroacetic acid	technically grade	20 °C	🟢
Trichloroethylene	technically grade	20 °C	🔴
Trichloroethylene	100%	20 °C	🟢
Triethanolamine	-	20 °C	🟢

Kemikalie	Concentración	Temp.	Beständighet
Turpentine oil	technically grade	20 °C	🟢
Urea, vattenl.	≤33%	20 °C	🟢
Vaseline	technically grade	20 °C	🟢
Vinegar (standard)	5-10%	20 °C	🟢
Water	-	20 °C	🟢
Water, distilled	-	20 °C	🟢
Wine	-	20 °C	🟢
Xylene	-	20 °C	🔴
Xylene	-	20 °C	🔴
Zinc sludge	-	20 °C	🟢