



# PEEK+PTFE 14x3000 mm azul

Artikelnr P1501462

## 1. Tekniskt datablad

| Egenskap                                     | Värde | Enhet   | Standard    |
|----------------------------------------------|-------|---------|-------------|
| Densidad                                     | 1.31  | g/cm³   | ISO 1183    |
| Módulo de elasticidad (tracción)             | 4400  | MPa     | ISO 527-2   |
| Deformación a la rotura                      | 20    | %       | ISO 527-2   |
| Punto de fusión                              | 340   | °C      | ISO 3146    |
| Temperatura de servicio máxima (corto plazo) | 310   | °C      |             |
| Temperatura de funcionamiento máxima         | 200   | °C      |             |
| Deformación térmica (HDT/A)                  | 160   | °C      | ISO 75-2    |
| Fuerza dieléctrica                           | 24    | kV/mm   | IEC 60243-1 |
| Resistividad volumétrica                     | 10¹⁵  | Ω·cm    | IEC 60093   |
| Constante dieléctrica (1 MHz)                | 3.6   | -       | IEC 60250   |
| Constante dieléctrica (100 Hz)               | 3.2   | -       | IEC 60250   |
| Factor de pérdida dieléctrica (1 MHz)        | 0.0   | -       | IEC 60250   |
| Factor de pérdida dieléctrica (100 Hz)       | 0.0   | -       | IEC 60250   |
| Resistencia a la flexión                     | 110   | MPa     | ISO 527-2   |
| Conductividad térmica                        | 0.25  | W/(m·K) | DIN 52612   |
| Resistencia superficial                      | 10¹⁵  | Ω       | IEC 60093   |
| Índice de seguimiento comparativo (CTI)      | 150   | V       | IEC 60112   |
| Absorción de agua hasta la saturación        | 0.2   | %       | ISO 62      |
| Absorción de agua hasta la saturación        | 0.45  | %       | ISO 62      |
| Resistencia al impacto con entalla (Charpy)  | 3.5   | kJ/m²   | ISO 179/1eA |
| Coefficiente de expansión térmica            | 0.5   | 10⁻⁵ /K | ISO 11359   |
| Dureza a la presión de bala                  | 230   | MPa     | ISO 2039-1  |

## 2. Kemisk beständighet

Beständig Delvis beständig Ej beständig

| Kemikalie | Konc. | Resultat |
|-----------|-------|----------|
|-----------|-------|----------|

| Kemikalie               | Konc. | Resultat |
|-------------------------|-------|----------|
| 1,4-Dioxane             | 100   | ●        |
| 2-Hydroxypropionic Acid | 90    | ●        |
| Acetic Acid             | 100   | ●        |
| Acetone                 | 100   | ●        |
| Ammonia                 | â€”   | ●        |
| Ammonium Chloride       | â€”   | ●        |
| Amyl Alcohol            | â€”   | ●        |
| Apple Juice             | â€”   | ●        |
| Benzene                 | â€”   | ●        |
| Bleaching Solution      | â€”   | ●        |
| Boric Acid              | 100   | ●        |
| Brake Fluid             | â€”   | ●        |
| Butyl Acetate           | â€”   | ●        |
| Calcium Chloride        | â€”   | ●        |
| Carbon Disulfide        | 100   | ●        |
| Carbon Tetrachloride    | â€”   | ●        |
| Chlorine (gas)          | 100   | ●        |
| Chlorobenzene           | 100   | ●        |
| Chloroform              | â€”   | ●        |
| Citric Acid             | 10    | ●        |
| Cresol                  | â€”   | ●        |
| Cyclohexanone           | 100   | ●        |
| Cyclohexene             | 100   | ●        |
| Diesel Fuel             | â€”   | ●        |
| Diethylene Oxide        | â€”   | ●        |
| Ethyl Acetate           | 100   | ●        |
| Ethyl Alcohol           | 96    | ●        |
| Ethylene Chloride       | 100   | ●        |
| Food Oil                | â€”   | ●        |
| Formaldehyde (aqueous)  | 40    | ●        |
| Formic Acid             | 10    | ●        |
| Frost Protection Agent  | â€”   | ●        |
| Fuel, aromatic free     | â€”   | ●        |
| Glycerine               | 100   | ●        |

| Kemikalie                        | Konc. | Resultat |
|----------------------------------|-------|----------|
| Glycol                           | 100   | ●        |
| Heating Oil                      | â€”   | ●        |
| Heptane                          | 100   | ●        |
| Hydrochloric Acid                | 10    | ●        |
| Hydrochloric Acid (concentrated) | â€”   | ●        |
| Hydrofluoric Acid                | 40    | ●        |
| Hydrogen Peroxide                | 10    | ●        |
| Hydrogen Sulfide (aqueous)       | â€”   | ●        |
| Isopropyl Alcohol                | 100   | ●        |
| Linseed Oil                      | â€”   | ●        |
| Mercurochrome                    | â€”   | ●        |
| Methyl Alcohol                   | 100   | ●        |
| Methyl Ethyl Ketone (MEK)        | 100   | ●        |
| Methylene Chloride               | 100   | ●        |
| Milk                             | â€”   | ●        |
| Mineral Oils (aromatic free)     | â€”   | ●        |
| Nitric Acid                      | 10    | ●        |
| Nitric Acid                      | 50    | ●        |
| Nitrobenzene                     | â€”   | ●        |
| Oxalic Acid                      | â€”   | ●        |
| Ozone Gas                        | â€”   | ●        |
| Paraffine Oil                    | 100   | ●        |
| Perchloroethylene                | â€”   | ●        |
| Petroleum                        | 100   | ●        |
| Petroleum Ether                  | 100   | ●        |
| Phenol (aqueous)                 | 9     | ●        |
| Phosphoric Acid                  | 50    | ●        |
| Potassium Hydroxide liquor       | 50    | ●        |
| Premium Fuel                     | â€”   | ●        |
| Propyl Alcohol                   | â€”   | ●        |
| Pyridine                         | â€”   | ●        |
| Silicone Oil                     | â€”   | ●        |
| Sodium Carbonate (aqueous)       | â€”   | ●        |
| Sodium Chloride (aqueous)        | â€”   | ●        |
| Sodium Hydrogen Sulfite          | â€”   | ●        |

| Kemikalie                | Konc. | Resultat |
|--------------------------|-------|----------|
| Sodium Hydroxide liquor  | 15    | ●        |
| Sodium Hydroxide liquor  | 60    | ●        |
| Sodium Nitrate (aqueous) | â€”   | ●        |
| Sodium Thiosulfate       | â€”   | ●        |
| Sulfuric Acid            | 96    | ●        |
| Tetrahydrofuran (THF)    | 100   | ●        |
| Toluene                  | 100   | ●        |
| Transformer Oil          | â€”   | ●        |
| Trichloroethylene        | 100   | ●        |
| Vinegar (standard)       | 5-10  | ●        |
| Water                    | â€”   | ●        |
| Xylene                   | â€”   | ●        |