PLASTSHOP.SE

Komplett teknisk dokumentation

PlastShop.se - 2026-03-27

POM CGL 32x1000 mm azul

Artikelnr	P1008011
Material	POM

1. Tekniskt datablad

Egenskap	Värde	Enhet	Standard
Densidad	**1.24**	g/cm³	ASTM D792
Límite de resistencia a la tracción	**51**	MPa	DIN EN ISO 527-2
Módulo de elasticidad (tracción)	**1200**	MPa	ASTM D790
Resistencia a la tensión	**76.5**	MPa	ISO 527
Deformación a la rotura	**300**	%	ASTM D638
Punto de fusión	**222**	°C	ISO 3146
Temperatura de servicio máxima (corto plazo)	**129**	°C	UL746B
Temperatura de funcionamiento máxima	**90**	°C	
Temperatura mínima	**-46.25**	°C	
Deformación térmica (HDT/A)	**105**	°C	ASTM D648
Deformación térmica (HDT/B)	**155**	°C	ISO 75
Temperatura de ablandamiento Vicat (VST/B/50)	**50**	°C	ISO 306
Fuerza dieléctrica	**85**	kV/mm	IEC 60243-1
Resistividad volumétrica	**10^{12}**	Ω	IEC 60093
Constante dieléctrica (1 MHz)	**3.7**	-	IEC 60250
Factor de pérdida dieléctrica (1 MHz)	**0.0**	-	IEC 60250
Factor de pérdida dieléctrica (100 Hz)	**0.0**	-	IEC 60250
Clasificación de resistencia al fuego (UL 94)	**60695**		UL 94
Resistencia a la flexión	**58**	MPa	ASTM D638
Conductividad térmica	**0.3**	W/(m·K)	DIN 52612
Resistencia superficial	**10^{13}**	Ω	IEC 60093
Índice de seguimiento comparativo (CTI)	**600**	V	IEC 60112
Absorción de agua hasta la saturación	**2.2**	%	ASTM D955
Absorción de agua hasta la saturación	**0.5**	%	ASTM D570

Egenskap	Värde	Enhet	Standard
Resistencia al impacto con entalla (Charpy)	**6**	kJ/m²	DIN EN ISO 179-1
Resistencia al impacto (Charpy)	**19**	kJ/m²	ISO 179/1eU
Coeficiente de expansión térmica	**0.4**	10^{-4}/K	ISO 11359
Dureza Shore D	**83**	° Shore D	ISO 868
Dureza a la presión de bala	**230**	MPa	ISO 2039-1

2. Kemisk beständighet

🟢 Beständig 🟡 Delvis beständig 🔴 Ej beständig

Kemikalie	Konc.	Resultat
1,4-Dioxane	100%	🟡
2-Hydroxypropionic Acid	90%	🟢
Acetic Acid	100%	🟡
Acetone	100%	🟢
Ammonia	conc.	🟢
Ammonium Chloride	-	🟡
Amyl Alcohol	-	🟢
Apple Juice	-	🟢
Benzene	-	🟡
Bleaching Solution	12.5 cl	🔴
Boric Acid	100%	🟡
Brake Fluid	-	🟢
Butyl Acetate	-	🟢
Calcium Chloride	-	🟢
Carbon Disulfide	100%	🟢
Carbon Tetrachloride	-	🟢
Chlorine (gas)	100%	🟢
Chlorobenzene	100%	🟡
Chloroform	-	🔴
Citric Acid	10%	🟡
Cresol	-	🟢
Cyclohexanone	100%	🟢
Cyclohexene	100%	🟢
Diesel Fuel	-	🟢
Diethylene Oxide	-	🟢

Kemikalie	Konc.	Resultat
Ethyl Acetate	100%	🟡
Ethyl Alcohol	96%	🟢
Ethylene Chloride	100%	🟢
Food Oil	-	🟢
Formaldehyde, aqueous	40%	🟢
Formic Acid	10%	🟢
Frost Protection Agent	-	🟢
Fuel, aromatic free	-	🟢
Glycerine	100%	🟢
Glycol	100%	🟢
Heating Oil	-	🟢
Heptane	100%	🟢
Hydrochloric Acid	10%	🔴
Hydrochloric Acid (concentrated)	conc.	🔴
Hydrofluoric Acid	40%	🔴
Hydrogen Peroxide	10%	🟢
Hydrogen Sulfide, aqueous solution	-	🟢
Isopropyl Alcohol	100%	🟢
Linseed Oil	-	🟢
Mercurochrome	-	🔴
Methyl Alcohol	100%	🟢
Methyl Ethyl Ketone (MEK)	100%	🟡
Methylene Chloride	100%	🔴
Milk	-	🟢
Mineral Oils (aromatic free)	-	🟢
Nitric Acid	10%	🔴
Nitric Acid (50%)	50%	🔴
Nitrobenzene	-	🟡
Oxalic Acid	-	🔴
Ozone Gas	≤0.5 ppm	🔴
Paraffine Oil	100%	🟢
Perchloroethylene	-	🟢
Petroleum	100%	🟢
Petroleum Ether	100%	🟢
Phenol, aqueous	ca. 9%	🔴

Kemikalie	Konc.	Resultat
Phosphoric Acid	50%	🔴
Potassium Hydroxide liquor	50%	🟡
Premium Fuel	-	🟢
Propyl Alcohol	-	🟢
Pyridine	-	🟢
Silicone Oil	-	🟢
Sodium Carbonate, aqueous	-	🟢
Sodium Chloride, aqueous	-	🟢
Sodium Hydrogen Sulfite	-	🔴
Sodium Hydroxide liquor (15%)	15%	🟢
Sodium Hydroxide liquor (60%)	60%	🟡
Sodium Nitrate, aqueous	-	🟢
Sodium Thiosulfate	-	🟢
Sulfuric Acid	96%	🔴
Tetrahydrofuran, THF	100%	🟡
Toluene	100%	🟢
Transformer Oil	-	🟢
Trichloroethylene	100%	🟡
Vinegar, standard	5-10%	🟢
Water	-	🟢
Xylene	-	🟢