

PA6 E 1000x1000x2,5 mm musta

Artikelnr P1001030

1. Tekniskt datablad

| Egenskap | Värde | Enhet | Standard |
|---|------------------|---------------------|----------------|
| Tiheys | 1.14 | g/cm ³ | ISO 1183 |
| Venymisrajan jännitys | 70 | MPa | DIN EN ISO 527 |
| Joustavuusmoduli (vetolujuus) | 3250 | MPa | ISO 527-2 |
| Murtolujuus | 75 | MPa | ISO 527-2 |
| Murtovenymä | 40 | % | ISO 527-2 |
| Sulamispiste | 220 | °C | ISO 3146 |
| Maksimaalinen käyttölämpötila (lyhytaikainen) | 160 | °C | |
| Maksimi käyttölämpötila | 90.5 | °C | |
| Alin lämpötila | -36 | °C | |
| Lämpökestävyys (HDT/A) | 70 | °C | ISO 75-2 |
| Lämpökestävyys (HDT/B) | 140 | °C | ISO 75-2 |
| Vicat-pehmenemislämpötila (VST/B/50) | 190 | °C | ISO 306 |
| Dielektrinen voimakkuus | 25 | kV/mm | IEC 60243-1 |
| Tilavuusresistanssi | 10 ¹² | Ω·cm | IEC 60093 |
| Dielektrinen vakio (1 MHz) | 3.7 | - | IEC 60250 |
| Dielektrinen vakio (100 Hz) | 3.9 | - | IEC 60250 |
| Dielektrinen hajoamiskerroin (1 MHz) | 0.0 | - | IEC 60250 |
| Dielektrinen hajoamiskerroin (100 Hz) | 0.0 | - | IEC 60250 |
| Paloaluokitus (UL 94) | 3 | | UL 94 |
| Taivutuslujuus | 76 | MPa | ISO 527-2 |
| Lämpöjohtavuus | 0.28 | W/(m·K) | DIN 52612 |
| Pintaresistanssi | 10 ¹² | Ω | IEC 60093 |
| Vertailukemiseindeksi (CTI) | 600 | V | IEC 60112 |
| Imeytymisen maksimointi | 2.5 | % | ISO 62 |
| Vesihaku kylmistymiseen | 9 | % | ISO 62 |
| Särkyäkesto (Charpy) | 5.5 | kJ/m ² | ISO 179/1eA |
| Lämpölaajenemiskerroin | 0.9 | 10 ⁻⁶ /K | ISO 11359 |

| Egenskap | Värde | Enhet | Standard |
|---------------------|-------|------------|----------------|
| Kovuus Shore D | 82 | Å° Shore D | DIN EN ISO 868 |
| Kulmapaineen kovuus | 150 | MPa | ISO 2039-1 |

2. Kemisk beständighet

● Beständig
 ● Delvis beständig
 ● Ej beständig

| Kemikalie | Konc. | Resultat |
|-------------------------|---------|----------|
| 1,4-Dioxane | 100 | ● |
| 2-Hydroxypropionic Acid | 90 | ● |
| Acetic Acid | 100 | ● |
| Acetone | 100 | ● |
| Ammonia | conc. | ● |
| Ammonium Chloride | â€” | ● |
| Amyl Alcohol | â€” | ● |
| Apple Juice | â€” | ● |
| Benzene | â€” | ● |
| Bleaching Solution | 12.5 cl | ● |
| Boric Acid | 100 | ● |
| Brake Fluid | â€” | ● |
| Butyl Acetate | â€” | ● |
| Calcium Chloride | â€” | ● |
| Carbon Disulfide | 100 | ● |
| Carbon Tetrachloride | â€” | ● |
| Chlorine (gas) | 100 | ● |
| Chlorobenzene | 100 | ● |
| Chloroform | â€” | ● |
| Citric Acid | 10 | ● |
| Cresol | â€” | ● |
| Cyclohexanone | 100 | ● |
| Cyclohexene | 100 | ● |
| Diesel Fuel | â€” | ● |
| Diethylene Oxide | â€” | ● |
| Ethyl Acetate | 100 | ● |
| Ethyl Alcohol | 96 | ● |

| Kemikalie | Konc. | Resultat |
|----------------------------------|-------------|----------|
| Ethylene Chloride | 100 | ● |
| Food Oil | â€” | ● |
| Formaldehyde (aqueous) | 40 | ● |
| Formic Acid | 10 | ● |
| Frost Protection Agent | â€” | ● |
| Fuel (aromatic free) | â€” | ● |
| Glycerine | 100 | ● |
| Glycol | 100 | ● |
| Heating Oil | â€” | ● |
| Heptane | 100 | ● |
| Hydrochloric Acid | 10 | ● |
| Hydrochloric Acid (concentrated) | conc. | ● |
| Hydrofluoric Acid | 40 | ● |
| Hydrogen Peroxide | 10 | ● |
| Hydrogen Sulfide (aqueous) | â€” | ● |
| Isopropyl Alcohol | 100 | ● |
| Linseed Oil | â€” | ● |
| Mercurochrome | â€” | ● |
| Methyl Alcohol | 100 | ● |
| Methyl Ethyl Ketone (MEK) | 100 | ● |
| Methylene Chloride | 100 | ● |
| Milk | â€” | ● |
| Mineral Oils (aromatic free) | â€” | ● |
| Nitric Acid | 50 | ● |
| Nitric Acid | 10 | ● |
| Nitrobenzene | â€” | ● |
| Oxalic Acid | â€” | ● |
| Ozone Gas | â‰ƒ 0.5 ppm | ● |
| Paraffine Oil | 100 | ● |
| Perchloroethylene | â€” | ● |
| Petroleum | 100 | ● |
| Petroleum Ether | 100 | ● |
| Phenol (aqueous) | ca. 9 | ● |
| Phosphoric Acid | 50 | ● |
| Potassium Hydroxide liquor | 50 | ● |

| Kemikalie | Konc. | Resultat |
|----------------------------|--------|----------|
| Premium Fuel | â€” | ● |
| Propyl Alcohol | â€” | ● |
| Pyridine | â€” | ● |
| Silicone Oil | â€” | ● |
| Sodium Carbonate (aqueous) | â€” | ● |
| Sodium Chloride (aqueous) | â€” | ● |
| Sodium Hydrogen Sulfite | â€” | ● |
| Sodium Hydroxide liquor | 15 | ● |
| Sodium Hydroxide liquor | 60 | ● |
| Sodium Nitrate (aqueous) | â€” | ● |
| Sodium Thiosulfate | â€” | ● |
| Sulfuric Acid | 96 | ● |
| Tetrahydrofuran (THF) | 100 | ● |
| Toluene | 100 | ● |
| Transformer Oil | â€” | ● |
| Trichloroethylene | 100 | ● |
| Vinegar (standard) | 5 - 10 | ● |
| Water | â€” | ● |
| Xylene | â€” | ● |