



PE-500 3000x1250x25 mm luonnollinen

Artikelnr P1200366  
Material PE

1. Tekniskt datablad

| Egenskap                                      | Värde            | Enhet               | Standard          |
|-----------------------------------------------|------------------|---------------------|-------------------|
| Tiheys                                        | 1.3              | g/cm³               | DIN EN ISO 1183-1 |
| Venymisrajan jännitys                         | 24.2             | MPa                 | DIN EN ISO 527    |
| Joustavuusmoduli (vetolujuus)                 | 1100             | MPa                 | DIN EN ISO 527    |
| Murtovenymä                                   | 138.75           | %                   | DIN EN ISO 527    |
| Sulamispiste                                  | 132.5            | °C                  | ISO 11357-3       |
| Maksimaalinen käyttölämpötila (lyhytaikainen) | 80               | °C                  |                   |
| Maksimi käyttölämpötila                       | 54               | °C                  |                   |
| Alin lämpötila                                | -100             | °C                  |                   |
| Vicat-pehmenemislämpötila (VST/B/50)          | 79               | °C                  | DIN EN ISO 306    |
| Dielektrinen voimakkuus                       | 40               | kV/mm               | IEC 60243         |
| Tilavuusresistanssi                           | 10 <sup>14</sup> | Ω                   | DIN EN 62631-3-1  |
| Dielektrinen vakio (1 MHz)                    | 2.3              | -                   | IEC 60250         |
| Dielektrinen hajoamiskerroin (1 MHz)          | 0.0              | -                   | IEC 60250         |
| Dielektrinen hajoamiskerroin (100 Hz)         | 0.0              | -                   | IEC 60250         |
| Paloaluokitus (UL 94)                         | 3                |                     | UL 94             |
| Lämmönjohtavuus                               | 0.4              | W/(m·K)             | DIN 52612-1       |
| Pintaresistanssi                              | ~10 <sup>8</sup> | Ω                   | DIN EN 62631-3-2  |
| Vertailukulkemisindeksi (CTI)                 | 600              | V                   | IEC 60112         |
| Imeytymisen maksimointi                       | 0.0              | %                   | DIN EN ISO 62     |
| Vesihaku kyllästymiseen                       | 0.0              | %                   | DIN EN ISO 62     |
| Särkyäkesto (Charpy)                          | 2                | kJ/m²               | DIN EN ISO 179    |
| Lämpölaajenemiskerroin                        | 2.4              | 10 <sup>-4</sup> /K | DIN 53752         |
| Kovuus Shore D                                | 65               | ° Shore D           | DIN EN ISO 868    |
| Kulmapaineen kovuus                           | 50               | MPa                 | ISO 2039-1        |

## 2. Kemisk beständighet

● Beständig   ● Delvis beständig   ● Ej beständig

| Kemikalie                             | Konc.        | Resultat |
|---------------------------------------|--------------|----------|
| 1,4-Dioxane                           | 100%         | ●        |
| 2-Hydroxypropionic Acid               | 90%          | ●        |
| Acetaldehyde                          | -            | ●        |
| Acetic Acid                           | 100%         | ●        |
| Acetic acid                           | 100%         | ●        |
| Acetic acid                           | 3%           | ●        |
| Acetic acid                           | 3% w/w       | ●        |
| Acetic acid                           | 3%           | ●        |
| Acetic acid                           | 3%           | ●        |
| Acetic acid, aqueous                  | 70%          | ●        |
| Acetic anhydride                      | -            | ●        |
| Acetone                               | -            | ●        |
| Acetone                               | 100%         | ●        |
| Acronal dispersions                   | -            | ●        |
| Acrylonitrile                         | -            | ●        |
| Allyl acetate                         | -            | ●        |
| Allyl alcohol                         | 96%          | ●        |
| Allyl chloride                        | -            | ●        |
| Aluminium chloride, aqueous           | any          | ●        |
| Aluminium chloride, solid             | -            | ●        |
| Aluminium fluoride                    | Conc.        | ●        |
| Aluminium hydroxide                   | -            | ●        |
| Aluminium metaphosphate               | -            | ●        |
| Aluminium sulphate, aqueous saturated | -            | ●        |
| Aluminium sulphate, solid             | -            | ●        |
| Ammonia                               | concentrated | ●        |
| Ammonia, gaseous                      | -            | ●        |
| Ammonia, liquid                       | -            | ●        |
| Ammonium Chloride                     | -            | ●        |
| Amyl Alcohol                          | -            | ●        |
| Aniline                               | any          | ●        |
| Anisole                               | -            | ●        |

| Kemikalie                                | Konc.             | Resultat |
|------------------------------------------|-------------------|----------|
| Apple Juice                              | -                 | ●        |
| Aqua regia                               | -                 | ●        |
| Beer                                     | -                 | ●        |
| Benzaldehyde, aqueous                    | any               | ●        |
| Benzene                                  | technically grade | ●        |
| Benzene                                  | -                 | ●        |
| Benzoic acid, aqueous                    | any               | ●        |
| Benzyl alcohol                           | -                 | ●        |
| Bitumen                                  | -                 | ●        |
| Bleaching Solution                       | 12.5 cl           | ●        |
| Boric Acid                               | 100%              | ●        |
| Brake Fluid                              | -                 | ●        |
| Bromine, liquid                          | 100%              | ●        |
| Butanol, aqueous                         | any               | ●        |
| Butter                                   | -                 | ●        |
| Butyl Acetate                            | -                 | ●        |
| Calcium Chloride                         | -                 | ●        |
| Calcium carbonate                        | -                 | ●        |
| Calcium carbonate                        | -                 | ●        |
| Calcium hypochlorite, aqueous suspension | any               | ●        |
| Camphor                                  | -                 | ●        |
| Carbon Disulfide                         | 100%              | ●        |
| Carbon Tetrachloride                     | -                 | ●        |
| Carbon disulphide                        | -                 | ●        |
| Caustic soda                             | any               | ●        |
| Chlorine (gas)                           | 100%              | ●        |
| Chlorine, liquid                         | -                 | ●        |
| Chloroacetic acid, aqueous               | ≤85%              | ●        |
| Chlorobenzene                            | 100%              | ●        |
| Chlorobenzene                            | -                 | ●        |
| Chloroform                               | technically grade | ●        |
| Chloroform                               | -                 | ●        |
| Chromosulphuric acid                     | -                 | ●        |
| Cider                                    | -                 | ●        |

| Kemikalie                | Konc.   | Resultat |
|--------------------------|---------|----------|
| Citric Acid              | 10%     | ●        |
| Citrus fruit juices      | -       | ●        |
| Coconut oil              | -       | ●        |
| Cod liver oil            | -       | ●        |
| Cresol                   | -       | ●        |
| Cresol                   | 100%    | ●        |
| Cyclohexane              | -       | ●        |
| Cyclohexanol             | -       | ●        |
| Cyclohexanone            | 100%    | ●        |
| Cyclohexanone            | -       | ●        |
| Cyclohexene              | 100%    | ●        |
| Detergents               | -       | ●        |
| Dibutyl ether            | -       | ●        |
| Dibutyl phthalate        | -       | ●        |
| Dichloroacetic acid      | -       | ●        |
| Dichloroethane           | -       | ●        |
| Diesel Fuel              | -       | ●        |
| Diesel fuel              | -       | ●        |
| Diethylene Oxide         | -       | ●        |
| Diglycolic acid, aqueous | 30%     | ●        |
| Dimethyl formamide       | -       | ●        |
| Dimethylamine            | -       | ●        |
| Dioxane                  | -       | ●        |
| Ethanol                  | 10%     | ●        |
| Ethanol                  | 10%     | ●        |
| Ethanol                  | 10% v/v | ●        |
| Ethanol                  | 10%     | ●        |
| Ethyl Acetate            | 100%    | ●        |
| Ethyl Alcohol            | 96%     | ●        |
| Ethyl acetate            | -       | ●        |
| Ethylene Chloride        | 100%    | ●        |
| Ethylene alcohol         | 96%     | ●        |
| Ethylene chloride        | -       | ●        |
| Ethylene diamine         | -       | ●        |
| Ethylene glycol          | -       | ●        |

| Kemikalie                                 | Konc.        | Resultat |
|-------------------------------------------|--------------|----------|
| Ferric chloride, aqueous                  | any          | ●        |
| Ferric nitrate, aqueous saturated         | -            | ●        |
| Ferric sulphate, aqueous saturated        | -            | ●        |
| Ferrous (II) chloride, aqueous saturated  | -            | ●        |
| Ferrous (II) sulfate, aqueous saturated   | -            | ●        |
| Ferrous (III) chloride, aqueous saturated | -            | ●        |
| Ferrous (III) nitrate, aqueous saturated  | -            | ●        |
| Ferrous (III) sulfate, aqueous saturated  | -            | ●        |
| Food Oil                                  | -            | ●        |
| Formaldehyde (aqueous)                    | 40%          | ●        |
| Formaldehyde, aqueous                     | ≤40%         | ●        |
| Formic Acid                               | 10%          | ●        |
| Formic acid, aqueous                      | 85%          | ●        |
| Frigen 12 (Freon 12)                      | 100%         | ●        |
| Frost Protection Agent                    | -            | ●        |
| Fruit juices                              | any          | ●        |
| Fuel (aromatic free)                      | -            | ●        |
| Fuel oil                                  | -            | ●        |
| Furfural                                  | -            | ●        |
| Glycerin, aqueous                         | any          | ●        |
| Glycerine                                 | 100%         | ●        |
| Glycol                                    | 100%         | ●        |
| Glykol, aqueous                           | as supplied  | ●        |
| Glysantin                                 | -            | ●        |
| Heating Oil                               | -            | ●        |
| Heptane                                   | 100%         | ●        |
| Heptane                                   | -            | ●        |
| Hexane                                    | -            | ●        |
| Honey                                     | -            | ●        |
| Hydrobromic acid, aqueous                 | 50%          | ●        |
| Hydrochloric Acid                         | 10%          | ●        |
| Hydrochloric Acid (concentrated)          | concentrated | ●        |
| Hydrochloric acid, aqueous                | any          | ●        |
| Hydrofluoric Acid                         | 40%          | ●        |
| Hydrogen Peroxide                         | 10%          | ●        |

| Kemikalie                                    | Konc.                      | Resultat |
|----------------------------------------------|----------------------------|----------|
| Hydrogen Sulfide (aqueous solution)          | -                          | ●        |
| Ink                                          | -                          | ●        |
| Iodine in potassium iodide solution          | 3% iodine                  | ●        |
| Isooctane                                    | -                          | ●        |
| Isopropanol                                  | -                          | ●        |
| Isopropyl Alcohol                            | 100%                       | ●        |
| Isopropyl ether                              | -                          | ●        |
| Jam                                          | -                          | ●        |
| Kerosene                                     | -                          | ●        |
| Linseed Oil                                  | -                          | ●        |
| Linseed oil                                  | technically grade          | ●        |
| Lithium bromide                              | -                          | ●        |
| Magnesium stearate                           | -                          | ●        |
| Magnesium stearate                           | -                          | ●        |
| Maleic acid, aqueous                         | any                        | ●        |
| Menthol                                      | -                          | ●        |
| Mercurochrome                                | -                          | ●        |
| Mercury                                      | -                          | ●        |
| Methanol                                     | technically grade          | ●        |
| Methyl Alcohol                               | 100%                       | ●        |
| Methyl Ethyl Ketone (MEK)                    | 100%                       | ●        |
| Methyl chloride                              | gaseous, technically grade | ●        |
| Methyl ethyl ketone                          | technically grade          | ●        |
| Methylene Chloride                           | 100%                       | ●        |
| Milk                                         | -                          | ●        |
| Milk                                         | -                          | ●        |
| Mineral Oil (aromatic free)                  | -                          | ●        |
| Molasses                                     | -                          | ●        |
| Motor oil (heavy duty oil) without additives | -                          | ●        |
| Naphtha                                      | -                          | ●        |
| Naphthalene                                  | -                          | ●        |
| Nitric Acid                                  | 10%                        | ●        |
| Nitric Acid (50%)                            | 50%                        | ●        |
| Nitric acid, aqueous                         | 50%                        | ●        |

| Kemikalie                  | Konc.       | Resultat |
|----------------------------|-------------|----------|
| Nitric acid, aqueous       | 25%         | ●        |
| Nitrobenzene               | -           | ●        |
| Nitrobenzene               | -           | ●        |
| Oils, ethereal             | -           | ●        |
| Oils, vegetable and animal | -           | ●        |
| Oleic acid                 | -           | ●        |
| Oleum                      | any         | ●        |
| Olive oil                  | -           | ●        |
| Olive oil                  | -           | ●        |
| Olive oil                  | -           | ●        |
| Olive oil                  | -           | ●        |
| Oxalic Acid                | -           | ●        |
| Oxalic acid, aqueous       | any         | ●        |
| Oxygen                     | -           | ●        |
| Ozone                      | 50 ppm      | ●        |
| Ozone Gas                  | ≤0.5 ppm    | ●        |
| Paraffine Oil              | 100%        | ●        |
| Perchloric acid, aqueous   | 70%         | ●        |
| Perchloric acid, aqueous   | 20%         | ●        |
| Perchloric acid, aqueous   | 50%         | ●        |
| Perchloroethylene          | -           | ●        |
| Petroleum                  | 100%        | ●        |
| Petroleum                  | -           | ●        |
| Petroleum Ether            | 100%        | ●        |
| Petroleum ether            | -           | ●        |
| Phenol                     | -           | ●        |
| Phenol (aqueous)           | ≈9%         | ●        |
| Phosphoric Acid            | 50%         | ●        |
| Phosphoric acid, aqueous   | 80% L 95%   | ●        |
| Phosphoric acid, aqueous   | 50%         | ●        |
| Phosphorus trichloride     | -           | ●        |
| Photographic developers    | -           | ●        |
| Photographic emulsions     | as supplied | ●        |
| Photographic fixing baths  | as supplied | ●        |

| Kemikalie                     | Konc.             | Resultat |
|-------------------------------|-------------------|----------|
| Phthalic acid, aqueous        | 50%               | ●        |
| Polyester resins              | -                 | ●        |
| Potassium Hydroxide liquor    | 50%               | ●        |
| Premium Fuel                  | -                 | ●        |
| Propionic acid, aqueous       | any               | ●        |
| Propyl Alcohol                | -                 | ●        |
| Pyridine                      | -                 | ●        |
| Pyridine                      | -                 | ●        |
| Sea water                     | -                 | ●        |
| Silicon dioxide               | -                 | ●        |
| Silicon dioxide               | -                 | ●        |
| Silicone Oil                  | -                 | ●        |
| Silicone oil                  | technically grade | ●        |
| Sodium Carbonate (aqueous)    | -                 | ●        |
| Sodium Chloride (aqueous)     | -                 | ●        |
| Sodium Hydrogen Sulfite       | -                 | ●        |
| Sodium Hydroxide liquor       | 15%               | ●        |
| Sodium Hydroxide liquor (60%) | 60%               | ●        |
| Sodium Nitrate (aqueous)      | -                 | ●        |
| Sodium Thiosulfate            | -                 | ●        |
| Sodium borate                 | -                 | ●        |
| Sodium bromide                | -                 | ●        |
| Sodium hydroxide, aqueous     | any               | ●        |
| Sodium hydroxide, solid       | -                 | ●        |
| Stearic acid                  | -                 | ●        |
| Sugar syrup                   | -                 | ●        |
| Sulfuric Acid                 | 96%               | ●        |
| Sulphuric acid, aqueous       | 70%               | ●        |
| Sulphuric acid, aqueous       | 80%               | ●        |
| Sulphuric acid, aqueous       | 98%               | ●        |
| Sulphuric acid, aqueous       | ≤50%              | ●        |
| Tallow                        | technically grade | ●        |
| Tannic acid (tannin), aqueous | 10%               | ●        |
| Tetrahydrofuran               | technically grade | ●        |

| Kemikalie                        | Konc.             | Resultat    |
|----------------------------------|-------------------|-------------|
| Tetrahydrofuran (THF)            | 100%              | <div></div> |
| Thionyl chloride                 | -                 | <div></div> |
| Thiophene                        | -                 | <div></div> |
| Tin (II) chloride, aqueous       | any               | <div></div> |
| Tin (IV) chloride, aqueous       | saturated         | <div></div> |
| Titanium dioxide                 | -                 | <div></div> |
| Titanium dioxide                 | -                 | <div></div> |
| Toluene                          | technically grade | <div></div> |
| Toluene                          | 100%              | <div></div> |
| Transformer Oil                  | -                 | <div></div> |
| Transformer oil (insulating oil) | technically grade | <div></div> |
| Trichloroacetic acid             | technically grade | <div></div> |
| Trichloroethylene                | technically grade | <div></div> |
| Trichloroethylene                | 100%              | <div></div> |
| Triethanolamine                  | -                 | <div></div> |
| Triethanolamine                  | -                 | <div></div> |
| Turpentine oil                   | technically grade | <div></div> |
| Urea, aqueous                    | ≤33%              | <div></div> |
| Vaseline                         | technically grade | <div></div> |
| Vinegar (standard)               | 5-10%             | <div></div> |
| Washing up liquids               | usual             | <div></div> |
| Water                            | -                 | <div></div> |
| Water, distilled                 | -                 | <div></div> |
| Wine                             | -                 | <div></div> |
| Xylene                           | -                 | <div></div> |
| Xylene                           | -                 | <div></div> |
| Zinc sludge                      | -                 | <div></div> |