



# PE-HD 2000x1000x50 mm luonnollinen

Artikelnr P2200290

Material PE

## 1. Tekniskt datablad

Egenskap	Värde	Enhet	Standard
Tiheys	0.96	g/cm <sup>3</sup>	ISO 1183
Kaupallinen tuotenimi	<b>Polyeten (PE)</b>		
Venymisrajan jännitys	20	MPa	ISO 527
Joustavuusmoduli (vetolujuus)	1200	MPa	ISO 527
Murtolujuus	13	MPa	ISO 527
Murtovenymä	200	%	ISO 527
Sulamispiste	135	°C	ISO 3146
Maksimaalinen käyttölämpötila (lyhytaikainen)	95	°C	UL746B
Maksimi käyttölämpötila	76	°C	
Alin lämpötila	-51	°C	
Lämpökäyrä (HDT/A)	45	°C	ISO 75-2
Lämpökäyrä (HDT/B)	69	°C	ISO 75
Vicat-pehmenemislämpötila (VST/B/50)	79	°C	ISO 306
GHS-luokitus	<b>Brandfarlig vid höga temperaturer.. Damm kan orsaka mekanisk irritation vid bearbetning.</b>		
Dielektrinen voimakkuus	45	kV/mm	IEC 60243-1
Fysikaaliset/kemialliset riskit	<b>Brandfarlig vid höga temperaturer.</b>		
Tilavuusresistanssi	10 <sup>12</sup>	Ω·cm	EN 61340-5-1
Terveysriskit	<b>Damm kan orsaka mekanisk irritation vid bearbetning.</b>		
Dielektrinen vakio (1 MHz)	2.4	-	IEC 60250
Ympäristöriskit	<b>Inga kända miljörisker. Inte biologiskt nedbrytbart.</b>		
Dielektrinen vakio (100 Hz)	2.3	-	IEC 60250
Dielektrinen hajoamiskerroin (1 MHz)	0.0	-	IEC 60250

Egenskap	Värde	Enhet	Standard
Dielektrinen hajoamiskerroin (100 Hz)	<b>0.0</b>	-	IEC 60250
Kemiallinen karakterisointi	<b>Polyeten (PE), CAS 9002-88-4</b>		
Vaaralliset aineet	<b>Produkten innehåller inga farliga ämnen som påbjuder ett röjande.</b>		
Yleinen tieto	<b>Produkten klassas som ofarlig.</b>		
Hengityksen kautta	<b>Vid inandning av rök/ångor: flytta till frisk luft, håll varm, sök läkarvård vid behov.</b>		
Ihokosketuksessa	<b>Vid kontakt med smält material: kyl omedelbart med kallt vatten. Ta inte bort stelnat material. Sök sjukvård.</b>		
Silmäkosketuksessa	<b>Spola med rikliga mängder vatten. Sök sjukvård om irritation kvarstår.</b>		
Nieltynä	<b>Då produkten är ofarlig behöver ingen första hjälp vidtas.</b>		
Sopiva sammutusväline	<b>Vatten, skum, gasformiga och torra släckmedel.</b>		
Henkilökohtaiset varotoimet	<b>Inte tillämpligt.</b>		
Ympäristönsuojelutoimenpiteet	<b>Inte tillämpligt.</b>		
Puhdistusmenetelmät	<b>Mekanisk borttagning.</b>		
Turvallisen käsittelyn ohjeet	<b>Sug bort spån vid bearbetning. Undvik överhettning.</b>		
Ammattimaiset altistumisraja-arvot	<b>Ingredienser med yrkesmässiga exponeringsgränser som ska övervakas: Inga.</b>		
Fyysinen muoto	<b>Platta, rundstång, rör</b>		
Fyysinen tila	<b>Fast</b>		
Väri	<b>Naturvit till svart</b>		
Haju	<b>Luktfri</b>		
Tilat, joita on syytä välttää	<b>Temperaturer över smältpunkten. Undvik UV-exponering.</b>		
Materiaaleja, joita on syytä välttää	<b>Starka oxidanter, syror.</b>		
Vaaralliset hajoamistuotteet	<b>Koldioxid, kolmonoxid, vaxångor.</b>		
Akuttotoksisuus	<b>Inga negativa hälsoeffekter förväntas vid hantering enligt rekommendationer.</b>		
Ihoärsytys	<b>Inte tillämpligt.</b>		
Silmäärtyne	<b>Inte tillämpligt.</b>		
Herättäminen	<b>Ingen känd.</b>		
Ympäristövaikutus	<b>Materialet är inte skadligt för miljön, men är inte biologiskt nedbrytbart.</b>		
Jätteiden käsittely	<b>Kasseras enligt lokala bestämmelser. Materialåtervinning möjlig.</b>		
Kuljetusluokitus	<b>Inte klassificerad som farligt gods.</b>		
REACH-tiedot	<b>Produkten kräver ingen varningsetikett enligt EU-direktiv.</b>		
Vastuuvapaus	<b>Informationen är baserad på nuvarande kunskapsnivå. Säkerhetsdatabladet gäller material tillhandahållet av PlastShop.se.</b>		
Taivutuslujuus	<b>20</b>	MPa	ISO527-2
Yrityksen nimi	<b>ARC Gruppen AB // PlastShop.se</b>		
Puhelin	<b>013-328 9400</b>		

Egenskap	Värde	Enhet	Standard
Sähköposti	<b>info@plastshop.se</b>		
Lämmönjohtavuus	<b>0.4</b>	W/(m·K)	DIN 52612
Pintaresistanssi	<b>10<sup>13</sup></b>	Ω	EN 61340-5-1
Vertailukulkemisindeksi (CTI)	<b>600</b>	V	IEC 60112
Vaaralliset palamistuotteet	<b>Vid förbränning kan koldioxid, kolmonoxid och vaxångor frigöras.</b>		
Palojen sammuttaminen	<b>Använd andningsskydd. Brandrester omhändertas enligt lokala regler.</b>		
Lisätietoja	<b>Brandrester omhändertas efter gällande lokala regler.</b>		
Säilytysolosuhteet	<b>Förvara torrt och svalt. Håll borta från öppen låga. Välventilerade utrymmen.</b>		
Hengityksensuoja	<b>Adekvat ventilering vid bearbetning.</b>		
Silmien suojaus	<b>Skyddsglasögon vid bearbetning.</b>		
Käsien suojaus	<b>Skyddshandskar vid kontakt med varmt material.</b>		
Kehon suoja	<b>Arbetskläder.</b>		
Hygienia-toimenpiteet	<b>Välventilerad arbetsplats. Undvik inandning av damm vid bearbetning.</b>		
Sulamispiste	<b>125-135°C (PE-HD), 130-145°C (PE-UHMW)</b>		
Hajoamislämpötila	<b>&gt;350 °C</b>		
Leimahduspiste	<b>&gt;300 °C</b>		
Itsestään syttyvän lämpötila	<b>ca 350°C</b>		
GefStoffV (Saksa)	<b>Ingen identifikation nödvändig.</b>		
Imeytymisen maksimointi	<b>0.01</b>	%	ISO 62
Vesihaku kyllästymiseen	<b>0.01</b>	%	ISO 62
Särkyäkesto (Charpy)	<b>7.5</b>	kJ/m <sup>2</sup>	ISO 179/1eA
Iskunkestävyys (Charpy)	<b>15</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Lämpölaajenemiskerroin	<b>2</b>	10 <sup>-4</sup> /K	ISO 11359
Tiheys (20°C)	<b>0,93-0,97 g/cm<sup>3</sup> (PE-HD), ISO 1183</b>		
Liukenne (vesi)	<b>Olöslig i vatten</b>		
Räjähdyksvaara	<b>Icke explosiv</b>		
Happamisen ominaisuudet	<b>Ingen</b>		
Kovuus Shore D	<b>60</b>	° Shore D	shore D
Kulmapaineen kovuus	<b>50</b>	MPa	ISO 2039-1

## 2. Kemisk beständighet

● Beständig
 ● Delvis beständig
 ● Ej beständig

Kemikalie	Konc.	Resultat
1,4-Dioxane	100%	●
2-Hydroxypropionic acid (lactic acid)	90%	●
Acetaldehyde	-	●
Acetic acid	100%	●
Acetic acid	100%	●
Acetic acid, aqueous	70%	●
Acetic anhydride	-	●
Acetone	100%	●
Acetone	-	●
Acronal dispersions	-	●
Acrylonitrile	-	●
Allyl acetate	-	●
Allyl alcohol	96%	●
Allyl chloride	-	●
Aluminium chloride, aqueous	any	●
Aluminium chloride, solid	-	●
Aluminium fluoride	Conc.	●
Aluminium hydroxide	-	●
Aluminium metaphosphate	-	●
Aluminium sulphate, aqueous saturated	-	●
Aluminium sulphate, solid	-	●
Ammonia	concentrated	●
Ammonia, gaseous	-	●
Ammonia, liquid	-	●
Ammonium chloride	-	●
Amyl alcohol	-	●
Aniline	any	●
Anisole	-	●
Aqua regia	-	●
Beer	-	●
Benzaldehyde, aqueous	any	●
Benzene	technically grade	●
Benzene	-	●
Benzoic acid, aqueous	any	●
Benzyl alcohol	-	●

Kemikalie	Konc.	Resultat
Bitumen	-	●
Bleaching solution	12.5 cl	●
Boric acid	100%	●
Brake fluid	-	●
Bromine, liquid	100%	●
Butanol, aqueous	any	●
Butter	-	●
Butyl acetate	-	●
Calcium chloride	-	●
Calcium hypochlorite, aqueous suspension	any	●
Camphor	-	●
Carbon disulphide	-	●
Carbon disulphide	100%	●
Carbon tetrachloride	-	●
Caustic soda (NaOH)	any	●
Chlorine (gas)	100%	●
Chlorine, liquid	-	●
Chloroacetic acid, aqueous	≤85%	●
Chlorobenzene	100%	●
Chlorobenzene	-	●
Chloroform	-	●
Chloroform	technically grade	●
Chromosulphuric acid	-	●
Cider	-	●
Citric acid	10%	●
Citrus fruit juices	-	●
Coconut oil	-	●
Cod liver oil	-	●
Cresol	-	●
Cresol	100%	●
Cyclohexane	-	●
Cyclohexanol	-	●
Cyclohexanone	100%	●
Cyclohexanone	-	●
Cyclohexene	100%	●

Kemikalie	Konc.	Resultat
Detergents	-	●
Detergents	usual	●
Dibutyl ether	-	●
Dibutyl phthalate	-	●
Dichloroacetic acid	-	●
Dichloroethane	-	●
Diesel	-	●
Diesel	-	●
Diethylene oxide	-	●
Diglycolic acid, aqueous	30%	●
Dimethyl formamide (DMF)	-	●
Dimethylamine	-	●
Dioxane	-	●
Essential oils	-	●
Ethyl acetate	100%	●
Ethyl acetate	-	●
Ethyl alcohol (ethanol)	96%	●
Ethylene alcohol	96%	●
Ethylene chloride	-	●
Ethylene chloride	100%	●
Ethylene diamine	-	●
Ethylene glycol	-	●
Ferric chloride, aqueous	any	●
Ferric nitrate, aqueous saturated	-	●
Ferric nitrate, aqueous saturated	-	●
Ferric sulphate, aqueous saturated	-	●
Ferric sulphate, aqueous saturated	-	●
Ferrous (II) chloride, aqueous saturated	-	●
Ferrous (II) sulfate, aqueous saturated	-	●
Ferrous (III) chloride, aqueous saturated	-	●
Food oil	-	●
Formaldehyde (aqueous)	40%	●
Formaldehyde, aqueous	≤40%	●
Formic acid	10%	●

Kemikalie	Konc.	Resultat
Formic acid, aqueous	85%	●
Frigen 12 (Freon 12)	100%	●
Frost protection agent	-	●
Fruit juices	any	●
Fuel (aromatic free)	-	●
Fuel oil	-	●
Fuel oil	-	●
Furfural	-	●
Glycerine	100%	●
Glycerine, aqueous	any	●
Glycol	100%	●
Glycol, aqueous	as supplied	●
Glysantin	-	●
Heptane	100%	●
Heptane	-	●
Hexane	-	●
Honey	-	●
Hydrobromic acid, aqueous	50%	●
Hydrochloric acid	10%	●
Hydrochloric acid (concentrated)	concentrated	●
Hydrochloric acid, aqueous	any	●
Hydrofluoric acid	40%	●
Hydrogen peroxide	10%	●
Hydrogen sulfide (aqueous)	-	●
Ink	-	●
Iodine in potassium iodide solution	3% iodine	●
Isooctane	-	●
Isopropanol	-	●
Isopropyl alcohol	100%	●
Isopropyl ether	-	●
Jam	-	●
Kerosene	-	●
Linseed oil	technically grade	●
Linseed oil	-	●
Lithium bromide	-	●

Kemikalie	Konc.	Resultat
Maleic acid, aqueous	any	●
Menthol	-	●
Mercurochrome	-	●
Mercury	-	●
Methanol	technically grade	●
Methyl alcohol (methanol)	100%	●
Methyl chloride	gaseous, technically grade	●
Methyl ethyl ketone (MEK)	technically grade	●
Methyl ethyl ketone (MEK)	100%	●
Methylene chloride	100%	●
Milk	-	●
Milk	-	●
Mineral oil (aromatic free)	-	●
Molasses	-	●
Motor oil (heavy duty) without additives	-	●
Naphtha	-	●
Naphthalene	-	●
Nitric acid	10%	●
Nitric acid (50%)	50%	●
Nitric acid, aqueous	50%	●
Nitric acid, aqueous	25%	●
Nitrobenzene	-	●
Nitrobenzene	-	●
Oils, vegetable and animal	-	●
Oleic acid	-	●
Oleum (fuming sulphuric acid)	any	●
Oxalic acid	-	●
Oxalic acid, aqueous	any	●
Oxygen	-	●
Ozone	50 ppm	●
Ozone (gas)	≤0.5 ppm	●
Paraffin oil	100%	●
Perchloric acid, aqueous	70%	●
Perchloric acid, aqueous	20%	●
Perchloric acid, aqueous	50%	●

Kemikalie	Konc.	Resultat
Perchloroethylene	-	●
Petroleum	-	●
Petroleum ether	100%	●
Petroleum ether	-	●
Phenol	-	●
Phenol (aqueous)	≈9%	●
Phosphoric acid	50%	●
Phosphoric acid, aqueous	50%	●
Phosphoric acid, aqueous	80% L 95%	●
Phosphorus trichloride	-	●
Photographic developer	-	●
Photographic emulsion	as supplied	●
Photographic fixing bath	as supplied	●
Phthalic acid, aqueous	50%	●
Polyester resins	-	●
Potassium hydroxide solution	50%	●
Premium fuel	-	●
Propionic acid, aqueous	any	●
Propyl alcohol	-	●
Pyridine	-	●
Pyridine	-	●
Sea water	-	●
Silicone oil	-	●
Silicone oil	technically grade	●
Sodium borate (borax)	-	●
Sodium bromide	-	●
Sodium carbonate (aqueous)	-	●
Sodium chloride (aqueous)	-	●
Sodium hydrogen sulfite	-	●
Sodium hydroxide solution (60%)	60%	●
Sodium hydroxide solution (caustic soda)	15%	●
Sodium hydroxide, aqueous	any	●
Sodium hydroxide, solid	-	●
Sodium nitrate (aqueous)	-	●

Kemikalie	Konc.	Resultat
Sodium thiosulfate	-	●
Stearic acid	-	●
Sugar syrup	-	●
Sulphuric acid	96%	●
Sulphuric acid, aqueous	≤50%	●
Sulphuric acid, aqueous	70%	●
Sulphuric acid, aqueous	80%	●
Sulphuric acid, aqueous	98%	●
Tallow	technically grade	●
Tannic acid (tannin), aqueous	10%	●
Tetrahydrofuran (THF)	technically grade	●
Tetrahydrofuran (THF)	100%	●
Thionyl chloride	-	●
Thiophene	-	●
Tin (II) chloride, aqueous	any	●
Tin (IV) chloride, aqueous	saturated	●
Toluene	100%	●
Toluene	technically grade	●
Transformer oil	-	●
Transformer oil (insulating oil)	technically grade	●
Trichloroacetic acid	technically grade	●
Trichloroethylene	technically grade	●
Trichloroethylene	100%	●
Triethanolamine	-	●
Turpentine oil	technically grade	●
Urea, vattenl.	≤33%	●
Vaseline	technically grade	●
Vinegar (standard)	5-10%	●
Water	-	●
Water, distilled	-	●
Wine	-	●
Xylene	-	●
Xylene	-	●
Zinc sludge	-	●

