

PE-HD 4000x2000x6 mm musta

Artikelnr P1200412

● Best ndig ● Delvis best ndig ● Ej best ndig

Kemikalie	Pitoisuus	Temp.	Best�ndighet
1,4-Dioxane	100%	20 �C	�
2-Hydroxypropionic acid (lactic acid)	90%	20 �C	�
Acetaldehyde	��	20 �C	�
Acetic acid	100%	20 �C	�
Acetic acid	100%	20 �C	�
Acetic acid, aqueous	70%	20 �C	�
Acetic anhydride	��	20 �C	�
Acetone	��	20 �C	�
Acetone	100%	20 �C	�
Acronal dispersions	��	20 �C	�
Acrylonitrile	��	20 �C	�
Allyl acetate	��	20 �C	�
Allyl alcohol	96%	20 �C	�
Allyl chloride	��	20 �C	�
Aluminium chloride, aqueous	any	20 �C	�
Aluminium chloride, solid	��	20 �C	�
Aluminium fluoride	Conc.	20 �C	�
Aluminium hydroxide	��	20 �C	�
Aluminium metaphosphate	��	20 �C	�
Aluminium sulphate, aqueous saturated	��	20 �C	�
Aluminium sulphate, solid	��	20 �C	�
Ammonia	concentrated	20 �C	�
Ammonia, gaseous	��	20 �C	�
Ammonia, liquid	��	20 �C	�
Ammonium chloride	��	20 �C	�
Amyl alcohol	��	20 �C	�
Aniline	any	20 �C	�

Kemikalie	Pitoisuus	Temp.	Bestäändighet
Anisole	â€”	20 Å°C	●
Aqua regia	â€”	20 Å°C	●
Beer	â€”	20 Å°C	●
Benzaldehyde, aqueous	any	20 Å°C	●
Benzene	technically grade	20 Å°C	●
Benzene	â€”	20 Å°C	●
Benzoic acid, aqueous	any	20 Å°C	●
Benzyl alcohol	â€”	20 Å°C	●
Bitumen	â€”	20 Å°C	●
Bleaching solution	12.5 cl	20 Å°C	●
Boric acid	100%	20 Å°C	●
Brake fluid	â€”	20 Å°C	●
Bromine, liquid	100%	20 Å°C	●
Butanol, aqueous	any	20 Å°C	●
Butter	â€”	20 Å°C	●
Butyl acetate	â€”	20 Å°C	●
Calcium chloride	â€”	20 Å°C	●
Calcium hypochlorite, aqueous suspension	any	20 Å°C	●
Camphor	â€”	20 Å°C	●
Carbon disulphide	â€”	20 Å°C	●
Carbon disulphide	100%	20 Å°C	●
Carbon tetrachloride	â€”	20 Å°C	●
Caustic soda (NaOH)	any	20 Å°C	●
Chlorine (gas)	100%	20 Å°C	●
Chlorine, liquid	â€”	20 Å°C	●
Chloroacetic acid, aqueous	â‰ƒ85%	20 Å°C	●
Chlorobenzene	â€”	20 Å°C	●
Chlorobenzene	100%	20 Å°C	●
Chloroform	technically grade	20 Å°C	●
Chloroform	â€”	20 Å°C	●
Chromosulphuric acid	â€”	20 Å°C	●
Cider	â€”	20 Å°C	●
Citric acid	10%	20 Å°C	●
Citrus fruit juices	â€”	20 Å°C	●

Kemikalie	Pitoisuus	Temp.	BestÄndighet
Coconut oil	â€”	20 Â°C	●
Cod liver oil	â€”	20 Â°C	●
Cresol	100%	20 Â°C	●
Cresol	â€”	20 Â°C	●
Cyclohexane	â€”	20 Â°C	●
Cyclohexanol	â€”	20 Â°C	●
Cyclohexanone	100%	20 Â°C	●
Cyclohexanone	â€”	20 Â°C	●
Cyclohexene	100%	20 Â°C	●
Detergents	usual	20 Â°C	●
Detergents	â€”	20 Â°C	●
Dibutyl ether	â€”	20 Â°C	●
Dibutyl phthalate	â€”	20 Â°C	●
Dichloroacetic acid	â€”	20 Â°C	●
Dichloroethane	â€”	20 Â°C	●
Diesel	â€”	20 Â°C	●
Diesel	â€”	20 Â°C	●
Diethylene oxide	â€”	20 Â°C	●
Diglycolic acid, aqueous	30%	20 Â°C	●
Dimethyl formamide (DMF)	â€”	20 Â°C	●
Dimethylamine	â€”	20 Â°C	●
Dioxane	â€”	20 Â°C	●
Essential oils	â€”	20 Â°C	●
Ethyl acetate	â€”	20 Â°C	●
Ethyl acetate	100%	20 Â°C	●
Ethyl alcohol (ethanol)	96%	20 Â°C	●
Ethylene alcohol	96%	20 Â°C	●
Ethylene chloride	100%	20 Â°C	●
Ethylene chloride	â€”	20 Â°C	●
Ethylene diamine	â€”	20 Â°C	●
Ethylene glycol	â€”	20 Â°C	●
Ferric chloride, aqueous	any	20 Â°C	●
Ferric nitrate, aqueous saturated	â€”	20 Â°C	●
Ferric nitrate, aqueous saturated	â€”	20 Â°C	●
Ferric sulphate, aqueous saturated	â€”	20 Â°C	●

Kemikalie	Pitoisuus	Temp.	Beständighet
Ferric sulphate, aqueous saturated	â€”	20 Å°C	●
Ferrous (II) chloride, aqueous saturated	â€”	20 Å°C	●
Ferrous (II) sulfate, aqueous saturated	â€”	20 Å°C	●
Ferrous (III) chloride, aqueous saturated	â€”	20 Å°C	●
Food oil	â€”	20 Å°C	●
Formaldehyde (aqueous)	40%	20 Å°C	●
Formaldehyde, aqueous	â‰ƒ40%	20 Å°C	●
Formic acid	10%	20 Å°C	●
Formic acid, aqueous	85%	20 Å°C	●
Frigen 12 (Freon 12)	100%	20 Å°C	●
Frost protection agent	â€”	20 Å°C	●
Fruit juices	any	20 Å°C	●
Fuel (aromatic free)	â€”	20 Å°C	●
Fuel oil	â€”	20 Å°C	●
Fuel oil	â€”	20 Å°C	●
Furfural	â€”	20 Å°C	●
Glycerine	100%	20 Å°C	●
Glycerine, aqueous	any	20 Å°C	●
Glycol	100%	20 Å°C	●
Glycol, aqueous	as supplied	20 Å°C	●
Glysantin	â€”	20 Å°C	●
Heptane	100%	20 Å°C	●
Heptane	â€”	20 Å°C	●
Hexane	â€”	20 Å°C	●
Honey	â€”	20 Å°C	●
Hydrobromic acid, aqueous	50%	20 Å°C	●
Hydrochloric acid	10%	20 Å°C	●
Hydrochloric acid (concentrated)	concentrated	20 Å°C	●
Hydrochloric acid, aqueous	any	20 Å°C	●
Hydrofluoric acid	40%	20 Å°C	●
Hydrogen peroxide	10%	20 Å°C	●
Hydrogen sulfide (aqueous)	â€”	20 Å°C	●
Ink	â€”	20 Å°C	●
Iodine in potassium iodide solution	3% iodine	20 Å°C	●
Isooctane	â€”	20 Å°C	●

Kemikalie	Pitoisuus	Temp.	Beständighet
Isopropanol	â€”	20 Â°C	●
Isopropyl alcohol	100%	20 Â°C	●
Isopropyl ether	â€”	20 Â°C	●
Jam	â€”	20 Â°C	●
Kerosene	â€”	20 Â°C	●
Linseed oil	technically grade	20 Â°C	●
Linseed oil	â€”	20 Â°C	●
Lithium bromide	â€”	20 Â°C	●
Maleic acid, aqueous	any	20 Â°C	●
Menthol	â€”	20 Â°C	●
Mercurochrome	â€”	20 Â°C	●
Mercury	â€”	20 Â°C	●
Methanol	technically grade	20 Â°C	●
Methyl alcohol (methanol)	100%	20 Â°C	●
Methyl chloride	gaseous, technically grade	20 Â°C	●
Methyl ethyl ketone (MEK)	technically grade	20 Â°C	●
Methyl ethyl ketone (MEK)	100%	20 Â°C	●
Methylene chloride	100%	20 Â°C	●
Milk	â€”	20 Â°C	●
Milk	â€”	20 Â°C	●
Mineral oil (aromatic free)	â€”	20 Â°C	●
Molasses	â€”	20 Â°C	●
Motor oil (heavy duty) without additives	â€”	20 Â°C	●
Naphtha	â€”	20 Â°C	●
Naphthalene	â€”	20 Â°C	●
Nitric acid	10%	20 Â°C	●
Nitric acid (50%)	50%	20 Â°C	●
Nitric acid, aqueous	25%	20 Â°C	●
Nitric acid, aqueous	50%	20 Â°C	●
Nitrobenzene	â€”	20 Â°C	●
Nitrobenzene	â€”	20 Â°C	●
Oils, vegetable and animal	â€”	20 Â°C	●
Oleic acid	â€”	20 Â°C	●
Oleum (fuming sulphuric acid)	any	20 Â°C	●

Kemikalie	Pitoisuus	Temp.	BestÄndighet
Oxalic acid	â€”	20 Â°C	●
Oxalic acid, aqueous	any	20 Â°C	●
Oxygen	â€”	20 Â°C	●
Ozone	50 ppm	20 Â°C	●
Ozone (gas)	â‰‰0.5 ppm	20 Â°C	●
Paraffin oil	100%	20 Â°C	●
Perchloric acid, aqueous	50%	20 Â°C	●
Perchloric acid, aqueous	70%	20 Â°C	●
Perchloric acid, aqueous	20%	20 Â°C	●
Perchloroethylene	â€”	20 Â°C	●
Petroleum	â€”	20 Â°C	●
Petroleum ether	100%	20 Â°C	●
Petroleum ether	â€”	20 Â°C	●
Phenol	â€”	20 Â°C	●
Phenol (aqueous)	â‰‰9%	20 Â°C	●
Phosphoric acid	50%	20 Â°C	●
Phosphoric acid, aqueous	50%	20 Â°C	●
Phosphoric acid, aqueous	80% L 95%	20 Â°C	●
Phosphorus trichloride	â€”	20 Â°C	●
Photographic developer	â€”	20 Â°C	●
Photographic emulsion	as supplied	20 Â°C	●
Photographic fixing bath	as supplied	20 Â°C	●
Phthalic acid, aqueous	50%	20 Â°C	●
Polyester resins	â€”	20 Â°C	●
Potassium hydroxide solution	50%	20 Â°C	●
Premium fuel	â€”	20 Â°C	●
Propionic acid, aqueous	any	20 Â°C	●
Propyl alcohol	â€”	20 Â°C	●
Pyridine	â€”	20 Â°C	●
Pyridine	â€”	20 Â°C	●
Sea water	â€”	20 Â°C	●
Silicone oil	technically grade	20 Â°C	●
Silicone oil	â€”	20 Â°C	●
Sodium borate (borax)	â€”	20 Â°C	●
Sodium bromide	â€”	20 Â°C	●

Kemikalie	Pitoisuus	Temp.	BestÄndighet
Sodium carbonate (aqueous)	â€”	20 Â°C	●
Sodium chloride (aqueous)	â€”	20 Â°C	●
Sodium hydrogen sulfite	â€”	20 Â°C	●
Sodium hydroxide solution (60%)	60%	20 Â°C	●
Sodium hydroxide solution (caustic soda)	15%	20 Â°C	●
Sodium hydroxide, aqueous	any	20 Â°C	●
Sodium hydroxide, solid	â€”	20 Â°C	●
Sodium nitrate (aqueous)	â€”	20 Â°C	●
Sodium thiosulfate	â€”	20 Â°C	●
Stearic acid	â€”	20 Â°C	●
Sugar syrup	â€”	20 Â°C	●
Sulphuric acid	96%	20 Â°C	●
Sulphuric acid, aqueous	98%	20 Â°C	●
Sulphuric acid, aqueous	â‰‰50%	20 Â°C	●
Sulphuric acid, aqueous	70%	20 Â°C	●
Sulphuric acid, aqueous	80%	20 Â°C	●
Tallow	technically grade	20 Â°C	●
Tannic acid (tannin), aqueous	10%	20 Â°C	●
Tetrahydrofuran (THF)	technically grade	20 Â°C	●
Tetrahydrofuran (THF)	100%	20 Â°C	●
Thionyl chloride	â€”	20 Â°C	●
Thiophene	â€”	20 Â°C	●
Tin (II) chloride, aqueous	any	20 Â°C	●
Tin (IV) chloride, aqueous	saturated	20 Â°C	●
Toluene	100%	20 Â°C	●
Toluene	technically grade	20 Â°C	●
Transformer oil	â€”	20 Â°C	●
Transformer oil (insulating oil)	technically grade	20 Â°C	●
Trichloroacetic acid	technically grade	20 Â°C	●
Trichloroethylene	100%	20 Â°C	●
Trichloroethylene	technically grade	20 Â°C	●
Triethanolamine	â€”	20 Â°C	●
Turpentine oil	technically grade	20 Â°C	●
Urea, vattenl.	â‰‰33%	20 Â°C	●
Vaseline	technically grade	20 Â°C	●

Kemikalie	Pitoisuus	Temp.	Beständighet
Vinegar (standard)	5-10%	20 Å°C	●
Water	â€”	20 Å°C	●
Water, distilled	â€”	20 Å°C	●
Wine	â€”	20 Å°C	●
Xylene	â€”	20 Å°C	●
Xylene	â€”	20 Å°C	●
Zinc sludge	â€”	20 Å°C	●