



# PEEK CMP 200/175x1000 mm beesi

Artikelnr P1500769

Beständig Delvis beständig Ej beständig

| Kemikalie                             | Pitoisuus | Temp.  | Beständighet |
|---------------------------------------|-----------|--------|--------------|
| 1,4-Dioxane                           | 100       | 20 Å°C |              |
| 2-Hydroxypropionic acid (lactic acid) | 90        | 20 Å°C |              |
| Acetic acid                           | 100       | 20 Å°C |              |
| Acetone                               | 100       | 20 Å°C |              |
| Ammonia                               | â€”       | 20 Å°C |              |
| Ammonium chloride                     | â€”       | 20 Å°C |              |
| Amyl alcohol                          | â€”       | 20 Å°C |              |
| Apple juice                           | â€”       | 20 Å°C |              |
| Benzene                               | â€”       | 20 Å°C |              |
| Boric acid                            | 100       | 20 Å°C |              |
| Brake fluid                           | â€”       | 20 Å°C |              |
| Butyl acetate                         | â€”       | 20 Å°C |              |
| Calcium chloride                      | â€”       | 20 Å°C |              |
| Carbon tetrachloride                  | â€”       | 20 Å°C |              |
| Chlorine (gas)                        | 100       | 20 Å°C |              |
| Chlorobenzene                         | 100       | 20 Å°C |              |
| Chloroform                            | â€”       | 20 Å°C |              |
| Citric acid                           | 10        | 20 Å°C |              |
| Cyclohexanone                         | 100       | 20 Å°C |              |
| Cyclohexene                           | 100       | 20 Å°C |              |
| Diesel                                | â€”       | 20 Å°C |              |
| Diethylene oxide                      | â€”       | 20 Å°C |              |
| Ethyl acetate                         | 100       | 20 Å°C |              |
| Ethyl alcohol (ethanol)               | 96        | 20 Å°C |              |
| Ethylene chloride                     | 100       | 20 Å°C |              |
| Food oil                              | â€”       | 20 Å°C |              |
| Formaldehyde (aqueous)                | 40        | 20 Å°C |              |

| Kemikalie                        | Pitoisuus | Temp.  | Beständighet |
|----------------------------------|-----------|--------|--------------|
| Formic acid                      | 10        | 20 Å°C | <div></div>  |
| Frost protection agent           | â€”       | 20 Å°C | <div></div>  |
| Fuel oil                         | â€”       | 20 Å°C | <div></div>  |
| Fuel, aromatic free              | â€”       | 20 Å°C | <div></div>  |
| Glycerine                        | 100       | 20 Å°C | <div></div>  |
| Glycol                           | 100       | 20 Å°C | <div></div>  |
| Heptane                          | 100       | 20 Å°C | <div></div>  |
| Hydrochloric acid                | 10        | 20 Å°C | <div></div>  |
| Hydrochloric acid (concentrated) | â€”       | 20 Å°C | <div></div>  |
| Hydrofluoric acid                | 40        | 20 Å°C | <div></div>  |
| Hydrogen peroxide                | 10        | 20 Å°C | <div></div>  |
| Hydrogen sulfide (aqueous)       | â€”       | 20 Å°C | <div></div>  |
| Isopropyl alcohol                | 100       | 20 Å°C | <div></div>  |
| Linseed oil                      | â€”       | 20 Å°C | <div></div>  |
| Mercurochrome                    | â€”       | 20 Å°C | <div></div>  |
| Methyl alcohol (methanol)        | 100       | 20 Å°C | <div></div>  |
| Methyl ethyl ketone (MEK)        | 100       | 20 Å°C | <div></div>  |
| Methylene chloride               | 100       | 20 Å°C | <div></div>  |
| Milk                             | â€”       | 20 Å°C | <div></div>  |
| Mineral oils (aromatic free)     | â€”       | 20 Å°C | <div></div>  |
| Nitric acid                      | 50        | 20 Å°C | <div></div>  |
| Nitric acid                      | 10        | 20 Å°C | <div></div>  |
| Nitrobenzene                     | â€”       | 20 Å°C | <div></div>  |
| Oxalic acid                      | â€”       | 20 Å°C | <div></div>  |
| Ozone (gas)                      | â€”       | 20 Å°C | <div></div>  |
| Paraffin oil                     | 100       | 20 Å°C | <div></div>  |
| Perchloroethylene                | â€”       | 20 Å°C | <div></div>  |
| Petroleum                        | 100       | 20 Å°C | <div></div>  |
| Petroleum ether                  | 100       | 20 Å°C | <div></div>  |
| Phenol (aqueous)                 | 9         | 20 Å°C | <div></div>  |
| Phosphoric acid                  | 50        | 20 Å°C | <div></div>  |
| Potassium hydroxide solution     | 50        | 20 Å°C | <div></div>  |
| Premium fuel                     | â€”       | 20 Å°C | <div></div>  |
| Propyl alcohol                   | â€”       | 20 Å°C | <div></div>  |
| Pyridine                         | â€”       | 20 Å°C | <div></div>  |

| Kemikalie                                | Pitoisuus | Temp.  | Beständighet |
|------------------------------------------|-----------|--------|--------------|
| Silicone oil                             | â€”       | 20 Å°C | ●            |
| Sodium carbonate (aqueous)               | â€”       | 20 Å°C | ●            |
| Sodium chloride (aqueous)                | â€”       | 20 Å°C | ●            |
| Sodium hydrogen sulfite                  | â€”       | 20 Å°C | ●            |
| Sodium hydroxide solution (caustic soda) | 60        | 20 Å°C | ●            |
| Sodium hydroxide solution (caustic soda) | 15        | 20 Å°C | ●            |
| Sodium nitrate (aqueous)                 | â€”       | 20 Å°C | ●            |
| Sodium thiosulfate                       | â€”       | 20 Å°C | ●            |
| Sulphuric acid                           | 96        | 20 Å°C | ●            |
| Tetrahydrofuran (THF)                    | 100       | 20 Å°C | ●            |
| Toluene                                  | 100       | 20 Å°C | ●            |
| Transformer oil                          | â€”       | 20 Å°C | ●            |
| Trichloroethylene                        | 100       | 20 Å°C | ●            |
| Vinegar (standard)                       | 5-10      | 20 Å°C | ●            |
| Water                                    | â€”       | 20 Å°C | ●            |
| Xylene                                   | â€”       | 20 Å°C | ●            |