



# PEEK 125/100x3000 mm beesi

Artikelnr P1500336

Best ndig Delvis best ndig Ej best ndig

| Kemikalie                             | Pitoisuus | Temp. | Best ndighet |
|---------------------------------------|-----------|-------|--------------|
| 1,4-Dioxane                           | 100       | 20  C | Best ndig    |
| 2-Hydroxypropionic acid (lactic acid) | 90        | 20  C | Best ndig    |
| Acetic acid                           | 100       | 20  C | Best ndig    |
| Acetone                               | 100       | 20  C | Best ndig    |
| Ammonia                               |           | 20  C | Best ndig    |
| Ammonium chloride                     |           | 20  C | Best ndig    |
| Amyl alcohol                          |           | 20  C | Best ndig    |
| Apple juice                           |           | 20  C | Best ndig    |
| Benzene                               |           | 20  C | Best ndig    |
| Boric acid                            | 100       | 20  C | Best ndig    |
| Brake fluid                           |           | 20  C | Best ndig    |
| Butyl acetate                         |           | 20  C | Best ndig    |
| Calcium chloride                      |           | 20  C | Best ndig    |
| Carbon tetrachloride                  |           | 20  C | Best ndig    |
| Chlorine (gas)                        | 100       | 20  C | Best ndig    |
| Chlorobenzene                         | 100       | 20  C | Best ndig    |
| Chloroform                            |           | 20  C | Best ndig    |
| Citric acid                           | 10        | 20  C | Best ndig    |
| Cyclohexanone                         | 100       | 20  C | Best ndig    |
| Cyclohexene                           | 100       | 20  C | Best ndig    |
| Diesel                                |           | 20  C | Best ndig    |
| Diethylene oxide                      |           | 20  C | Best ndig    |
| Ethyl acetate                         | 100       | 20  C | Best ndig    |
| Ethyl alcohol (ethanol)               | 96        | 20  C | Best ndig    |
| Ethylene chloride                     | 100       | 20  C | Best ndig    |
| Food oil                              |           | 20  C | Best ndig    |
| Formaldehyde (aqueous)                | 40        | 20  C | Best ndig    |

| Kemikalie                        | Pitoisuus | Temp.  | Beständighet |
|----------------------------------|-----------|--------|--------------|
| Formic acid                      | 10        | 20 Å°C | ●            |
| Frost protection agent           | â€”       | 20 Å°C | ●            |
| Fuel oil                         | â€”       | 20 Å°C | ●            |
| Fuel, aromatic free              | â€”       | 20 Å°C | ●            |
| Glycerine                        | 100       | 20 Å°C | ●            |
| Glycol                           | 100       | 20 Å°C | ●            |
| Heptane                          | 100       | 20 Å°C | ●            |
| Hydrochloric acid                | 10        | 20 Å°C | ●            |
| Hydrochloric acid (concentrated) | â€”       | 20 Å°C | ●            |
| Hydrofluoric acid                | 40        | 20 Å°C | ●            |
| Hydrogen peroxide                | 10        | 20 Å°C | ●            |
| Hydrogen sulfide (aqueous)       | â€”       | 20 Å°C | ●            |
| Isopropyl alcohol                | 100       | 20 Å°C | ●            |
| Linseed oil                      | â€”       | 20 Å°C | ●            |
| Mercurochrome                    | â€”       | 20 Å°C | ●            |
| Methyl alcohol (methanol)        | 100       | 20 Å°C | ●            |
| Methyl ethyl ketone (MEK)        | 100       | 20 Å°C | ●            |
| Methylene chloride               | 100       | 20 Å°C | ●            |
| Milk                             | â€”       | 20 Å°C | ●            |
| Mineral oils (aromatic free)     | â€”       | 20 Å°C | ●            |
| Nitric acid                      | 50        | 20 Å°C | ●            |
| Nitric acid                      | 10        | 20 Å°C | ●            |
| Nitrobenzene                     | â€”       | 20 Å°C | ●            |
| Oxalic acid                      | â€”       | 20 Å°C | ●            |
| Ozone (gas)                      | â€”       | 20 Å°C | ●            |
| Paraffin oil                     | 100       | 20 Å°C | ●            |
| Perchloroethylene                | â€”       | 20 Å°C | ●            |
| Petroleum                        | 100       | 20 Å°C | ●            |
| Petroleum ether                  | 100       | 20 Å°C | ●            |
| Phenol (aqueous)                 | 9         | 20 Å°C | ●            |
| Phosphoric acid                  | 50        | 20 Å°C | ●            |
| Potassium hydroxide solution     | 50        | 20 Å°C | ●            |
| Premium fuel                     | â€”       | 20 Å°C | ●            |
| Propyl alcohol                   | â€”       | 20 Å°C | ●            |
| Pyridine                         | â€”       | 20 Å°C | ●            |

| Kemikalie                                | Pitoisuus | Temp.  | Beständighet |
|------------------------------------------|-----------|--------|--------------|
| Silicone oil                             | â€”       | 20 Å°C | ●            |
| Sodium carbonate (aqueous)               | â€”       | 20 Å°C | ●            |
| Sodium chloride (aqueous)                | â€”       | 20 Å°C | ●            |
| Sodium hydrogen sulfite                  | â€”       | 20 Å°C | ●            |
| Sodium hydroxide solution (caustic soda) | 60        | 20 Å°C | ●            |
| Sodium hydroxide solution (caustic soda) | 15        | 20 Å°C | ●            |
| Sodium nitrate (aqueous)                 | â€”       | 20 Å°C | ●            |
| Sodium thiosulfate                       | â€”       | 20 Å°C | ●            |
| Sulphuric acid                           | 96        | 20 Å°C | ●            |
| Tetrahydrofuran (THF)                    | 100       | 20 Å°C | ●            |
| Toluene                                  | 100       | 20 Å°C | ●            |
| Transformer oil                          | â€”       | 20 Å°C | ●            |
| Trichloroethylene                        | 100       | 20 Å°C | ●            |
| Vinegar (standard)                       | 5-10      | 20 Å°C | ●            |
| Water                                    | â€”       | 20 Å°C | ●            |
| Xylene                                   | â€”       | 20 Å°C | ●            |