



PEEK 165/130x3000 mm musta

Artikelnr P1500399

Beständig Delvis beständig Ej beständig

Kemikalie	Pitoisuus	Temp.	Beständighet
1,4-Dioxane	100	20 Å°C	Beständig
2-Hydroxypropionic acid (lactic acid)	90	20 Å°C	Beständig
Acetic acid	100	20 Å°C	Beständig
Acetone	100	20 Å°C	Beständig
Ammonia	â€	20 Å°C	Beständig
Ammonium chloride	â€	20 Å°C	Beständig
Amyl alcohol	â€	20 Å°C	Beständig
Apple juice	â€	20 Å°C	Beständig
Benzene	â€	20 Å°C	Beständig
Boric acid	100	20 Å°C	Beständig
Brake fluid	â€	20 Å°C	Beständig
Butyl acetate	â€	20 Å°C	Beständig
Calcium chloride	â€	20 Å°C	Beständig
Carbon tetrachloride	â€	20 Å°C	Beständig
Chlorine (gas)	100	20 Å°C	Beständig
Chlorobenzene	100	20 Å°C	Beständig
Chloroform	â€	20 Å°C	Beständig
Citric acid	10	20 Å°C	Beständig
Cyclohexanone	100	20 Å°C	Beständig
Cyclohexene	100	20 Å°C	Beständig
Diesel	â€	20 Å°C	Beständig
Diethylene oxide	â€	20 Å°C	Beständig
Ethyl acetate	100	20 Å°C	Beständig
Ethyl alcohol (ethanol)	96	20 Å°C	Beständig
Ethylene chloride	100	20 Å°C	Beständig
Food oil	â€	20 Å°C	Beständig
Formaldehyde (aqueous)	40	20 Å°C	Beständig

Kemikalie	Pitoisuus	Temp.	Beständighet
Formic acid	10	20 Å°C	●
Frost protection agent	â€”	20 Å°C	●
Fuel oil	â€”	20 Å°C	●
Fuel, aromatic free	â€”	20 Å°C	●
Glycerine	100	20 Å°C	●
Glycol	100	20 Å°C	●
Heptane	100	20 Å°C	●
Hydrochloric acid	10	20 Å°C	●
Hydrochloric acid (concentrated)	â€”	20 Å°C	●
Hydrofluoric acid	40	20 Å°C	●
Hydrogen peroxide	10	20 Å°C	●
Hydrogen sulfide (aqueous)	â€”	20 Å°C	●
Isopropyl alcohol	100	20 Å°C	●
Linseed oil	â€”	20 Å°C	●
Mercurochrome	â€”	20 Å°C	●
Methyl alcohol (methanol)	100	20 Å°C	●
Methyl ethyl ketone (MEK)	100	20 Å°C	●
Methylene chloride	100	20 Å°C	●
Milk	â€”	20 Å°C	●
Mineral oils (aromatic free)	â€”	20 Å°C	●
Nitric acid	50	20 Å°C	●
Nitric acid	10	20 Å°C	●
Nitrobenzene	â€”	20 Å°C	●
Oxalic acid	â€”	20 Å°C	●
Ozone (gas)	â€”	20 Å°C	●
Paraffin oil	100	20 Å°C	●
Perchloroethylene	â€”	20 Å°C	●
Petroleum	100	20 Å°C	●
Petroleum ether	100	20 Å°C	●
Phenol (aqueous)	9	20 Å°C	●
Phosphoric acid	50	20 Å°C	●
Potassium hydroxide solution	50	20 Å°C	●
Premium fuel	â€”	20 Å°C	●
Propyl alcohol	â€”	20 Å°C	●
Pyridine	â€”	20 Å°C	●

Kemikalie	Pitoisuus	Temp.	Beständighet
Silicone oil	â€”	20 Å°C	●
Sodium carbonate (aqueous)	â€”	20 Å°C	●
Sodium chloride (aqueous)	â€”	20 Å°C	●
Sodium hydrogen sulfite	â€”	20 Å°C	●
Sodium hydroxide solution (caustic soda)	60	20 Å°C	●
Sodium hydroxide solution (caustic soda)	15	20 Å°C	●
Sodium nitrate (aqueous)	â€”	20 Å°C	●
Sodium thiosulfate	â€”	20 Å°C	●
Sulphuric acid	96	20 Å°C	●
Tetrahydrofuran (THF)	100	20 Å°C	●
Toluene	100	20 Å°C	●
Transformer oil	â€”	20 Å°C	●
Trichloroethylene	100	20 Å°C	●
Vinegar (standard)	5-10	20 Å°C	●
Water	â€”	20 Å°C	●
Xylene	â€”	20 Å°C	●