



PEEK 65/45x3000 mm musta

Artikelnr P1500210
Material PEEK

1. Tekniskt datablad

Egenskap	Värde	Enhet	Standard
Tiheys	1.31	g/cm³	ISO 1183
Venymisrajan jännitys	112	MPa	ISO527-2
Joustavuusmoduli (vetolujuus)	4400	MPa	ISO 527-2
Murtolujuus	67	MPa	ISO 527
Murtovenymä	20	%	ISO 527-2
Sulamispiste	340	°C	ISO 3146
Maksimaalinen käyttölämpötila (lyhytaikainen)	291	°C	UL746B
Maksimi käyttölämpötila	245	°C	
Alin lämpötila	-35	°C	
Lämpökäyrä (HDT/A)	160	°C	ISO 75-2
Lämpökäyrä (HDT/B)	240	°C	ISO 75
Vicat-pehmenemislämpötila (VST/B/50)	50	°C	ISO 306
Dielektrinen voimakkuus	24	kV/mm	IEC 60243-1
Tilavuusresistanssi	10 ¹⁴	Ω·cm	IEC 60093
Dielektrinen vakio (1 MHz)	3.6	-	IEC 60250
Dielektrinen vakio (100 Hz)	3.2	-	IEC 60250
Dielektrinen hajoamiskerroin (1 MHz)	0.0	-	IEC 60250
Dielektrinen hajoamiskerroin (100 Hz)	0.0	-	IEC 60250
Paloaluokitus (UL 94)	0		UL 94
Taivutuslujuus	110	MPa	ISO 527-2
Lämmönjohtavuus	0.25	W/(m·K)	DIN 52612
Pintaresistanssi	10 ¹³	Ω	IEC 60093
Vertailukulkemisindeksi (CTI)	150	V	IEC 60112
Imeytymisen maksimointi	0.2	%	ISO 62
Vesihaku kyllästymiseen	0.45	%	ISO 62

Egenskap	Värde	Enhet	Standard
Särkyäkesto (Charpy)	3.5	kJ/m²	ISO 179/1eA
Iskunkestävyys (Charpy)	92	kJ/m²	ISO179/1eU
Lämpölaajenemiskerroin	0.5	10 ⁻⁴ /K	DIN 11359
Kovuus Shore D	90	° Shore D	DIN EN ISO 868
Kulmapaineen kovuus	230	MPa	ISO 2039-1

2. Kemisk beständighet

● Beständig ● Delvis beständig ● Ej beständig

Kemikalie	Konc.	Resultat
1,4-Dioxane	100	●
2-Hydroxypropionic acid (lactic acid)	90	●
Acetic acid	100	●
Acetone	100	●
Ammonia	-	●
Ammonium chloride	-	●
Amyl alcohol	-	●
Apple juice	-	●
Benzene	-	●
Boric acid	100	●
Brake fluid	-	●
Butyl acetate	-	●
Calcium chloride	-	●
Carbon tetrachloride	-	●
Chlorine (gas)	100	●
Chlorobenzene	100	●
Chloroform	-	●
Citric acid	10	●
Cyclohexanone	100	●
Cyclohexene	100	●
Diesel	-	●
Diethylene oxide	-	●
Ethyl acetate	100	●
Ethyl alcohol (ethanol)	96	●
Ethylene chloride	100	●
Food oil	-	●

Kemikalie	Konc.	Resultat
Formaldehyde (aqueous)	40	●
Formic acid	10	●
Frost protection agent	-	●
Fuel oil	-	●
Fuel, aromatic free	-	●
Glycerine	100	●
Glycol	100	●
Heptane	100	●
Hydrochloric acid	10	●
Hydrochloric acid (concentrated)	-	●
Hydrofluoric acid	40	●
Hydrogen peroxide	10	●
Hydrogen sulfide (aqueous)	-	●
Isopropyl alcohol	100	●
Linseed oil	-	●
Mercurochrome	-	●
Methyl alcohol (methanol)	100	●
Methyl ethyl ketone (MEK)	100	●
Methylene chloride	100	●
Milk	-	●
Mineral oils (aromatic free)	-	●
Nitric acid	50	●
Nitric acid	10	●
Nitrobenzene	-	●
Oxalic acid	-	●
Ozone (gas)	-	●
Paraffin oil	100	●
Perchloroethylene	-	●
Petroleum	100	●
Petroleum ether	100	●
Phenol (aqueous)	9	●
Phosphoric acid	50	●
Potassium hydroxide solution	50	●
Premium fuel	-	●

Kemikalie	Konc.	Resultat
Propyl alcohol	-	●
Pyridine	-	●
Silicone oil	-	●
Sodium carbonate (aqueous)	-	●
Sodium chloride (aqueous)	-	●
Sodium hydrogen sulfite	-	●
Sodium hydroxide solution (caustic soda)	60	●
Sodium hydroxide solution (caustic soda)	15	●
Sodium nitrate (aqueous)	-	●
Sodium thiosulfate	-	●
Sulphuric acid	96	●
Tetrahydrofuran (THF)	100	●
Toluene	100	●
Transformer oil	-	●
Trichloroethylene	100	●
Vinegar (standard)	5-10	●
Water	-	●
Xylene	-	●