PET ZX 1000x1000x30 mm vaalea harmaa

Artikelnr P1004222

🟢 BestÃ¤ndig 🟡 Delvis bestÃ¤ndig 🔴 Ej bestÃ¤ndig

Kemikalie	Pitoisuus	Temp.	BestÃ¤ndighet
1,4-Dioxane	100	60 Â°C	🟡
1,4-Dioxane	100	20 Â°C	🟡
Acetic acid	100	20 Â°C	🔴
Acetic acid	100%	20 Â°C	🟢
Acetic acid	100	60 Â°C	🔴
Acetone	100	60 Â°C	🔴
Acetone	100	20 Â°C	🟡
Ammonia	conc.	20 Â°C	🟡
Ammonia	conc.	60 Â°C	🔴
Apple juice	â€”	20 Â°C	🟢
Apple juice	â€”	20 Â°C	🟢
Benzene	â€”	20 Â°C	🟡
Benzene	â€”	60 Â°C	🔴
Bleaching solution	â€”	20 Â°C	🟢
Brake fluid	â€”	60 Â°C	🟢
Brake fluid	â€”	20 Â°C	🟢
Butyl acetate	â€”	60 Â°C	🟢
Butyl acetate	â€”	20 Â°C	🟢
Calcium chloride	â€”	60 Â°C	🟢
Calcium chloride	â€”	20 Â°C	🟢
Carbon disulphide	100	60 Â°C	🟡
Carbon disulphide	100	20 Â°C	🟢
Carbon tetrachloride	â€”	20 Â°C	🟢
Carbon tetrachloride	â€”	20 Â°C	🟢
Carbon tetrachloride	â€”	60 Â°C	🟡
Chlorobenzene	100%	20 Â°C	🟢
Chlorobenzene	100	60 Â°C	🔴

Kemikalie	Pitoisuus	Temp.	BestÃ¤ndighet
Chlorobenzene	100	20 Â°C	🔴
Chloroform	â€”	60 Â°C	🔴
Chloroform	â€”	20 Â°C	🔴
Citric acid	10	20 Â°C	🟢
Citric acid	10	60 Â°C	🟡
Diesel	â€”	20 Â°C	🟢
Diesel	â€”	60 Â°C	🟢
Diethylene oxide	â€”	20 Â°C	🟢
Diethylene oxide	â€”	20 Â°C	🟢
Ethyl acetate	100	20 Â°C	🟢
Ethyl acetate	100	60 Â°C	🔴
Ethyl alcohol (ethanol)	96	60 Â°C	🟢
Ethyl alcohol (ethanol)	96%	20 Â°C	🟢
Ethyl alcohol (ethanol)	96	20 Â°C	🟢
Ethylene chloride	100	20 Â°C	🟡
Ethylene chloride	100	60 Â°C	🔴
Food oil	â€”	20 Â°C	🟢
Food oil	â€”	60 Â°C	🟢
Food oil	â€”	20 Â°C	🟢
Formic acid	10	20 Â°C	🟢
Formic acid	10	60 Â°C	🟡
Frost protection agent	â€”	20 Â°C	🟢
Frost protection agent	â€”	60 Â°C	🟡
Fuel oil	â€”	60 Â°C	🟢
Fuel oil	â€”	20 Â°C	🟢
Fuel, aromatic free	â€”	60 Â°C	🟢
Fuel, aromatic free	â€”	20 Â°C	🟢
Glycerine	100	60 Â°C	🟢
Glycerine	100	20 Â°C	🟢
Glycerine	100%	20 Â°C	🟢
Glycol	100	60 Â°C	🟡
Glycol	100	20 Â°C	🟢
Heptane	100	20 Â°C	🟢
Heptane	100	60 Â°C	🟢

Kemikalie	Pitoisuus	Temp.	BestÃ¤ndighet
Hydrochloric acid	conc.	20 Â°C	🔴
Hydrochloric acid	10	60 Â°C	🟡
Hydrochloric acid	10	20 Â°C	🟢
Hydrochloric acid	conc.	60 Â°C	🔴
Hydrochloric acid (concentrated)	conc.	20 Â°C	🟢
Hydrofluoric acid	40%	20 Â°C	🟢
Hydrofluoric acid	40	60 Â°C	🔴
Hydrofluoric acid	40	20 Â°C	🔴
Hydrogen peroxide	10	20 Â°C	🟢
Hydrogen peroxide	10	60 Â°C	🟡
Hydrogen sulfide, aqueous	â€”	20 Â°C	🟢
Isopropyl alcohol	100	60 Â°C	🟡
Isopropyl alcohol	100%	20 Â°C	🟢
Isopropyl alcohol	100	20 Â°C	🟢
Linseed oil	â€”	60 Â°C	🟢
Linseed oil	â€”	20 Â°C	🟢
Mercurochrome	â€”	20 Â°C	🟢
Methyl alcohol (methanol)	100	20 Â°C	🟢
Methyl alcohol (methanol)	100	60 Â°C	🟡
Methyl alcohol (methanol)	100%	20 Â°C	🟢
Methyl ethyl ketone (MEK)	100	60 Â°C	🟡
Methyl ethyl ketone (MEK)	100	20 Â°C	🟢
Methylene chloride	100	20 Â°C	🔴
Methylene chloride	100	60 Â°C	🔴
Milk	â€”	20 Â°C	🟢
Milk	â€”	60 Â°C	🟢
Mineral oils, aromatic free	â€”	20 Â°C	🟢
Mineral oils, aromatic free	â€”	60 Â°C	🟢
Nitric acid	50	20 Â°C	🔴
Nitric acid	50	60 Â°C	🔴
Nitric acid	10%	20 Â°C	🟢
Nitric acid	10	20 Â°C	🟢
Nitric acid	10	60 Â°C	🟡
Paraffin oil	100	20 Â°C	🟢

Kemikalie	Pitoisuus	Temp.	BestÃ¤ndighet
Paraffin oil	100	60 Â°C	🟢
Perchloroethylene	â€”	60 Â°C	🔴
Perchloroethylene	â€”	20 Â°C	🟢
Petroleum	100%	20 Â°C	🟢
Petroleum	100	20 Â°C	🟢
Petroleum ether	100	60 Â°C	🟢
Petroleum ether	100	20 Â°C	🟢
Petroleum ether	100%	20 Â°C	🟢
Phenol, aqueous	ca.9	20 Â°C	🔴
Phosphoric acid	50	20 Â°C	🟢
Phosphoric acid	50	60 Â°C	🟡
Potassium hydroxide solution	50	60 Â°C	🔴
Potassium hydroxide solution	50	20 Â°C	🔴
Premium fuel	â€”	60 Â°C	🟡
Premium fuel	â€”	20 Â°C	🟢
Propyl alcohol	â€”	60 Â°C	🔴
Propyl alcohol	â€”	20 Â°C	🟢
Silicone oil	â€”	20 Â°C	🟢
Silicone oil	â€”	60 Â°C	🟢
Sodium carbonate, aqueous	â€”	20 Â°C	🟢
Sodium carbonate, aqueous	â€”	60 Â°C	🟢
Sodium chloride, aqueous	â€”	20 Â°C	🟢
Sodium chloride, aqueous	â€”	60 Â°C	🟢
Sodium hydrogen sulfite	â€”	60 Â°C	🟢
Sodium hydrogen sulfite	â€”	20 Â°C	🟡
Sodium hydrogen sulfite	â€”	20 Â°C	🟢
Sodium hydroxide solution (caustic soda)	15	20 Â°C	🔴
Sodium hydroxide solution (caustic soda)	60	20 Â°C	🔴
Sodium hydroxide solution (caustic soda)	60	60 Â°C	🔴
Sodium hydroxide solution (caustic soda)	15	60 Â°C	🔴
Sodium nitrate, aqueous	â€”	20 Â°C	🟢
Sodium thiosulfate	â€”	20 Â°C	🟢
Sulphuric acid	96	20 Â°C	🔴
Sulphuric acid	96	60 Â°C	🔴

Kemikalie	Pitoisuus	Temp.	BestÃ¤ndighet
Tetrahydrofuran (THF)	100	60 Â°C	🔴
Tetrahydrofuran (THF)	100	20 Â°C	🔴
Toluene	100	60 Â°C	🔴
Toluene	100	20 Â°C	🟢
Toluene	100%	20 Â°C	🟢
Transformer oil	â€”	60 Â°C	🟢
Transformer oil	â€”	20 Â°C	🟢
Trichloroethylene	100	60 Â°C	🔴
Trichloroethylene	100	20 Â°C	🟡
Vinegar, standard	5-10	60 Â°C	🟡
Vinegar, standard	5-10	20 Â°C	🟢
Vinegar, standard	5-10%	20 Â°C	🟢
Water	â€”	20 Â°C	🟢
Water	â€”	60 Â°C	🔴
Xylene	â€”	20 Â°C	🟡
Xylene	â€”	60 Â°C	🔴

This document is for informational purposes only. Specifications may change without notice. Generated 2026-03-16