

PET 1000x1000x3 mm musta

Artikelnr P1003718

Material PET

1. Tekniskt datablad

Egenskap	Värde	Enhet	Standard
Tiheys	1.46	g/cm ³	ISO 1183
Venymisrajan jännitys	52	MPa	ISO 527
Joustavuusmoduli (vetolujuus)	3400	MPa	ISO 527-2
Murtolujuus	58	MPa	ISO 527
Murtovenymä	5	%	ISO 527-2
Sulamispiste	224	°C	ISO 3146
Maksimaalinen käyttölämpötila (lyhytaikainen)	138.75	°C	UL746B
Maksimi käyttölämpötila	97	°C	
Alin lämpötila	-25	°C	
Lämpökäyrä (HDT/A)	85	°C	ISO 75
Lämpökäyrä (HDT/B)	100	°C	ISO 75
Vicat-pehmenemislämpötila (VST/B/50)	219	°C	ISO 306
Dielektrinen voimakkuus	22	kV/mm	IEC 60243-1
Tilavuusresistanssi	10¹⁸	Ω·cm	DIN EN 62631-3-1
Dielektrinen vakio (1 MHz)	3.3	-	IEC 60250
Dielektrinen hajoamiskerroin (1 MHz)	0.0	-	IEC 60250
Dielektrinen hajoamiskerroin (100 Hz)	0.0	-	IEC 60250
Taivutuslujuus	75.25	MPa	ISO 178
Lämmönjohtavuus	0.33	W/(m·K)	DIN 52612
Pintaresistanssi	10¹⁴	Ω	IEC 60093
Vertailukulkemisindeksi (CTI)	600	V	IEC 60112
Imeytymisen maksimointi	0.02	%	ISO 62
Vesihaku kyllästymiseen	0.02	%	ISO 62
Särkyäkesto (Charpy)	90	kJ/m ²	ISO 180
Iskunkestävyys (Charpy)	37	kJ/m ²	ISO 179/1eU

Egenskap	Värde	Enhet	Standard
Lämpölaajenemiskerroin	0.8	10 ⁻⁴ /K	DIN 11359
Kovuus Shore D	77	° Shore D	ISO 868
Rockwell-kovuus	112	M-scale	
Kulmapaineen kovuus	166	MPa	ISO 2039

2. Kemisk beständighet

● Beständig ● Delvis beständig ● Ej beständig

Kemikalie	Konc.	Resultat
1,4-Dioxane	100	●
1,4-Dioxane	100	●
Acetic acid	100	●
Acetic acid	100%	●
Acetic acid	100	●
Acetone	100	●
Acetone	100	●
Ammonia	conc.	●
Ammonia	conc.	●
Apple juice	-	●
Apple juice	-	●
Benzene	-	●
Benzene	-	●
Bleaching solution	-	●
Brake fluid	-	●
Brake fluid	-	●
Butyl acetate	-	●
Butyl acetate	-	●
Calcium chloride	-	●
Calcium chloride	-	●
Carbon disulphide	100	●
Carbon disulphide	100	●
Carbon tetrachloride	-	●
Carbon tetrachloride	-	●
Carbon tetrachloride	-	●
Chlorobenzene	100%	●
Chlorobenzene	100	●

Kemikalie	Konc.	Resultat
Chlorobenzene	100	●
Chloroform	-	●
Chloroform	-	●
Citric acid	10	●
Citric acid	10	●
Diesel	-	●
Diesel	-	●
Diethylene oxide	-	●
Diethylene oxide	-	●
Ethyl acetate	100	●
Ethyl acetate	100	●
Ethyl alcohol (ethanol)	96	●
Ethyl alcohol (ethanol)	96%	●
Ethyl alcohol (ethanol)	96	●
Ethylene chloride	100	●
Ethylene chloride	100	●
Food oil	-	●
Food oil	-	●
Food oil	-	●
Formic acid	10	●
Formic acid	10	●
Frost protection agent	-	●
Frost protection agent	-	●
Fuel oil	-	●
Fuel oil	-	●
Fuel, aromatic free	-	●
Fuel, aromatic free	-	●
Glycerine	100	●
Glycerine	100	●
Glycerine	100%	●
Glycol	100	●
Glycol	100	●
Heptane	100	●
Heptane	100	●

Kemikalie	Konc.	Resultat
Hydrochloric acid	conc.	●
Hydrochloric acid	10	●
Hydrochloric acid	10	●
Hydrochloric acid	conc.	●
Hydrochloric acid (concentrated)	conc.	●
Hydrofluoric acid	40%	●
Hydrofluoric acid	40	●
Hydrofluoric acid	40	●
Hydrogen peroxide	10	●
Hydrogen peroxide	10	●
Hydrogen sulfide, aqueous	-	●
Isopropyl alcohol	100	●
Isopropyl alcohol	100%	●
Isopropyl alcohol	100	●
Linseed oil	-	●
Linseed oil	-	●
Mercurochrome	-	●
Methyl alcohol (methanol)	100	●
Methyl alcohol (methanol)	100	●
Methyl alcohol (methanol)	100%	●
Methyl ethyl ketone (MEK)	100	●
Methyl ethyl ketone (MEK)	100	●
Methylene chloride	100	●
Methylene chloride	100	●
Milk	-	●
Milk	-	●
Mineral oils, aromatic free	-	●
Mineral oils, aromatic free	-	●
Nitric acid	50	●
Nitric acid	50	●
Nitric acid	10%	●
Nitric acid	10	●
Nitric acid	10	●
Paraffin oil	100	●
Paraffin oil	100	●

Kemikalie	Konc.	Resultat
Perchloroethylene	-	●
Perchloroethylene	-	●
Petroleum	100%	●
Petroleum	100	●
Petroleum ether	100	●
Petroleum ether	100	●
Petroleum ether	100%	●
Phenol, aqueous	ca.9	●
Phosphoric acid	50	●
Phosphoric acid	50	●
Potassium hydroxide solution	50	●
Potassium hydroxide solution	50	●
Premium fuel	-	●
Premium fuel	-	●
Propyl alcohol	-	●
Propyl alcohol	-	●
Silicone oil	-	●
Silicone oil	-	●
Sodium carbonate, aqueous	-	●
Sodium carbonate, aqueous	-	●
Sodium chloride, aqueous	-	●
Sodium chloride, aqueous	-	●
Sodium hydrogen sulfite	-	●
Sodium hydrogen sulfite	-	●
Sodium hydrogen sulfite	-	●
Sodium hydroxide solution (caustic soda)	15	●
Sodium hydroxide solution (caustic soda)	60	●
Sodium hydroxide solution (caustic soda)	60	●
Sodium hydroxide solution (caustic soda)	15	●
Sodium nitrate, aqueous	-	●
Sodium thiosulfate	-	●
Sulphuric acid	96	●
Sulphuric acid	96	●
Tetrahydrofuran (THF)	100	●
Tetrahydrofuran (THF)	100	●

Kemikalie	Konc.	Resultat
Toluene	100	●
Toluene	100	●
Toluene	100%	●
Transformer oil	-	●
Transformer oil	-	●
Trichloroethylene	100	●
Trichloroethylene	100	●
Vinegar, standard	5-10	●
Vinegar, standard	5-10	●
Vinegar, standard	5-10%	●
Water	-	●
Water	-	●
Xylene	-	●
Xylene	-	●