



PFA 1500x1500x0,8 mm luonnollinen

Artikelnr P2202784

1. Tekniskt datablad

Egenskap	Värde	Enhet	Standard
Tiheys	2.15	g/cm³	DIN EN ISO 1183
Venymisrajan jännitys	15	MPa	DIN EN ISO 527
Joustavuusmoduli (vetolujuus)	450	MPa	DIN EN ISO 527
Murtolujuus	24	MPa	DIN EN ISO 527
Murtovenymä	250	%	DIN EN ISO 527
Sulamispiste	300	°C	ISO 3146
Maksimaalinen käyttölämpötila (lyhytaikainen)	260	°C	
Maksimi käyttölämpötila	260	°C	
Alin lämpötila	-190	°C	
Lämpökestävyys (HDT/A)	75	°C	ISO 75
Dielektrinen voimakkuus	33	kV/mm	DIN IEC 60243-1
Pintaresistanssi	~10¹³	Ω	DIN EN 61340
Lämpölaajenemiskerroin	1.4	10⁻⁵/K	ISO 11359-2
Kovuus Shore D	55	° Shore D	DIN EN ISO 868

2. Kemisk beständighet

Beständig Delvis beständig Ej beständig

Kemikalie	Konc.	Resultat
1,4-Dioxane	100	
2-Hydroxypropionic Acid	90	
Acetic Acid	100	
Acetone	100	
Ammonia	â€	
Ammonium Chloride	â€	
Amyl Alcohol	â€	
Apple Juice	â€	

Kemikalie	Konc.	Resultat
Benzene	â€”	
Bleaching Solution	â€”	
Boric Acid	100	
Brake Fluid	â€”	
Butyl Acetate	â€”	
Calcium Chloride	â€”	
Carbon Disulfide	100	
Carbon Tetrachloride	â€”	
Chlorine (gas)	100	
Chlorobenzene	100	
Chloroform	â€”	
Citric Acid	10	
Cresol	â€”	
Cyclohexanone	100	
Cyclohexene	100	
Diesel Fuel	â€”	
Diethylene Oxide	â€”	
Ethyl Acetate	100	
Ethyl Alcohol	96	
Ethylene Chloride	100	
Food Oil	â€”	
Formaldehyde (aqueous)	40	
Formic Acid	10	
Frost Protection Agent	â€”	
Fuel, aromatic free	â€”	
Glycerine	100	
Glycol	100	
Heating Oil	â€”	
Heptane	100	
Hydrochloric Acid	10	
Hydrochloric Acid (concentrated)	â€”	
Hydrofluoric Acid	40	
Hydrogen Peroxide	10	
Hydrogen Sulfide (aqueous)	â€”	

Kemikalie	Konc.	Resultat
Isopropyl Alcohol	100	
Linseed Oil	â€”	
Mercurochrome	â€”	
Methyl Alcohol	100	
Methyl Ethyl Ketone (MEK)	100	
Methylene Chloride	100	
Milk	â€”	
Mineral Oils (aromatic free)	â€”	
Nitric Acid	10	
Nitric Acid (50%)	50	
Nitrobenzene	â€”	
Oxalic Acid	â€”	
Ozone Gas	â‰‰ 0.5 ppm	
Paraffine Oil	100	
Perchloroethylene	â€”	
Petroleum	100	
Petroleum Ether	100	
Phenol (aqueous)	ca. 9	
Phosphoric Acid	50	
Potassium Hydroxide liquor	50	
Premium Fuel	â€”	
Propyl Alcohol	â€”	
Pyridine	â€”	
Silicone Oil	â€”	
Sodium Carbonate (aqueous)	â€”	
Sodium Chloride (aqueous)	â€”	
Sodium Hydrogen Sulfite	â€”	
Sodium Hydroxide liquor	15	
Sodium Hydroxide liquor (60)	60	
Sodium Nitrate (aqueous)	â€”	
Sodium Thiosulfate	â€”	
Sulfuric Acid	96	
Tetrahydrofuran (THF)	100	
Toluene	100	

Kemikalie	Konc.	Resultat
Transformer Oil	â€”	●
Trichloroethylene	100	●
Vinegar (standard)	5 - 10	●
Water	â€”	●
Xylene	â€”	●