



PMMA E 2050x1520x15 mm läpinäkyvä

Artikelnr P1203057
Material PMMA

1. Tekniskt datablad

Egenskap	Värde	Enhet	Standard
Tiheys	1.19	g/cm³	ISO 1183
Venymisrajan jännitys	72	MPa	ISO 527
Joustavuusmoduli (vetolujuus)	3300	MPa	ISO 527-2
Murtolujuus	70	MPa	ISO 527-2
Murtovenymä	5	%	ISO 527-2
Sulamispiste	160	°C	ISO 3146
Maksimaalinen käyttölämpötila (lyhytaikainen)	107.5	°C	UL746B
Maksimi käyttölämpötila	75	°C	
Alin lämpötila	-40	°C	
Lämpökäyrä (HDT/A)	95	°C	ISO 75
Lämpökäyrä (HDT/B)	100	°C	ISO 75
Vicat-pehmenemislämpötila (VST/B/50)	103	°C	ISO 306
Dielektrinen voimakkuus	30	kV/mm	IEC 60243-1
Tilavuusresistanssi	10 ¹⁵	Ω·cm	IEC 60093
Dielektrinen vakio (1 MHz)	1	-	IEC 60250
Dielektrinen vakio (100 Hz)	2.7	-	DIN 53483-2
Dielektrinen hajoamiskerroin (1 MHz)	0.03	-	IEC 60250
Dielektrinen hajoamiskerroin (100 Hz)	0.06	-	DIN 53483-2
Taivutuslujuus	75	MPa	ISO 527-2
Lämmönjohtavuus	0.19	W/(m·K)	DIN 52612
Pintaresistanssi	10 ¹³	Ω	IEC 60093
Vertailukulkemisindeksi (CTI)	600	V	IEC 60112
Imeytymisen maksimointi	2.1	%	ISO 62
Vesihaku kyllästymiseen	2.1	%	ISO 62

Egenskap	Värde	Enhet	Standard
Särkyäkesto (Charpy)	1.6	kJ/m²	ISO 179/1eA
Iskunkestävyys (Charpy)	15	kJ/m²	ISO 179/1eU
Lämpölaajenemiskerroin	0.0	10 ⁻⁴ /K	DIN 11359
Kovuus Shore D	15	° Shore D	
Rockwell-kovuus	100	M-scale	ISO 2039-2
Kulmapaineen kovuus	175	MPa	ISO 2039-1

2. Kemisk beständighet

● Beständig
 ● Delvis beständig
 ● Ej beständig

Kemikalie	Konc.	Resultat
Acetic acid	100%	●
Acetone	100%	●
Ammonia	conc.	●
Amyl alcohol	-	●
Apple juice	-	●
Benzene	-	●
Butyl acetate	-	●
Calcium chloride	-	●
Carbon disulphide	100%	●
Carbon tetrachloride	-	●
Chlorine gas	100%	●
Chloroform	-	●
Citric acid	10%	●
Cresol	-	●
Cyclohexanone	100%	●
Cyclohexene	100%	●
Diesel	-	●
Diethylene oxide	-	●
Ethyl acetate	100%	●
Ethyl alcohol (ethanol)	96%	●
Ethylene chloride	100%	●
Formaldehyde, aqueous	40%	●
Formic acid	10%	●
Fuel oil	-	●

Kemikalie	Konc.	Resultat
Fuel, aromatic free	-	●
Glycerine	100%	●
Glycol	100%	●
Heptane	100%	●
Hydrochloric acid	10%	●
Hydrochloric acid (concentrated)	conc.	●
Hydrofluoric acid	40%	●
Hydrogen peroxide	10%	●
Hydrogen sulfide, aqueous	-	●
Isopropyl alcohol	100%	●
Linseed oil	-	●
Mercurochrome	-	●
Methyl alcohol (methanol)	100%	●
Methyl ethyl ketone (MEK)	100%	●
Methylene chloride	100%	●
Milk	-	●
Mineral oils, aromatic free	-	●
Nitric acid	10%	●
Nitric acid (50%)	50%	●
Nitrobenzene	-	●
Oxalic acid	-	●
Ozone (gas)	≤ 0.5 ppm	●
Paraffin oil	100%	●
Perchloroethylene	-	●
Petroleum	100%	●
Petroleum ether	100%	●
Phenol, aqueous	ca. 9%	●
Phosphoric acid	50%	●
Potassium hydroxide solution	50%	●
Premium fuel	-	●
Silicone oil	-	●
Sodium carbonate, aqueous	-	●
Sodium chloride, aqueous	-	●
Sodium hydrogen sulfite	-	●
Sodium hydroxide solution (60%)	60%	●

Kemikalie	Konc.	Resultat
Sodium hydroxide solution (caustic soda)	15%	●
Sodium thiosulfate	-	●
Sulphuric acid	96%	●
Tetrahydrofuran (THF)	100%	●
Toluene	100%	●
Transformer oil	-	●
Trichloroethylene	100%	●
Vinegar, standard	5-10%	●
Water	-	●
Xylene	-	●