



PMMA E 3050x2050x3 mm opaali-valkoinen 3%

Artikelnr P1200690

Best ndig Delvis best ndig Ej best ndig

Kemikalie	Pitoisuus	Temp.	Best�ndighet
Acetic acid	100%	20 �C	
Acetone	100%	20 �C	
Ammonia	conc.	20 �C	
Amyl alcohol	��	20 �C	
Apple juice	��	20 �C	
Benzene	��	20 �C	
Butyl acetate	��	20 �C	
Calcium chloride	��	20 �C	
Carbon disulphide	100%	20 �C	
Carbon tetrachloride	��	20 �C	
Chlorine gas	100%	20 �C	
Chloroform	��	20 �C	
Citric acid	10%	20 �C	
Cresol	��	20 �C	
Cyclohexanone	100%	20 �C	
Cyclohexene	100%	20 �C	
Diesel	��	20 �C	
Diethylene oxide	��	20 �C	
Ethyl acetate	100%	20 �C	
Ethyl alcohol (ethanol)	96%	20 �C	
Ethylene chloride	100%	20 �C	
Formaldehyde, aqueous	40%	20 �C	
Formic acid	10%	20 �C	
Fuel oil	��	20 �C	
Fuel, aromatic free	��	20 �C	
Glycerine	100%	20 �C	
Glycol	100%	20 �C	

Kemikalie	Pitoisuus	Temp.	Beständighet
Heptane	100%	20 Å°C	●
Hydrochloric acid	10%	20 Å°C	●
Hydrochloric acid (concentrated)	conc.	20 Å°C	●
Hydrofluoric acid	40%	20 Å°C	●
Hydrogen peroxide	10%	20 Å°C	●
Hydrogen sulfide, aqueous	â€”	20 Å°C	●
Isopropyl alcohol	100%	20 Å°C	●
Linseed oil	â€”	20 Å°C	●
Mercurochrome	â€”	20 Å°C	●
Methyl alcohol (methanol)	100%	20 Å°C	●
Methyl ethyl ketone (MEK)	100%	20 Å°C	●
Methylene chloride	100%	20 Å°C	●
Milk	â€”	20 Å°C	●
Mineral oils, aromatic free	â€”	20 Å°C	●
Nitric acid	10%	20 Å°C	●
Nitric acid (50%)	50%	20 Å°C	●
Nitrobenzene	â€”	20 Å°C	●
Oxalic acid	â€”	20 Å°C	●
Ozone (gas)	â‰ƒ 0.5 ppm	20 Å°C	●
Paraffin oil	100%	20 Å°C	●
Perchloroethylene	â€”	20 Å°C	●
Petroleum	100%	20 Å°C	●
Petroleum ether	100%	20 Å°C	●
Phenol, aqueous	ca. 9%	20 Å°C	●
Phosphoric acid	50%	20 Å°C	●
Potassium hydroxide solution	50%	20 Å°C	●
Premium fuel	â€”	20 Å°C	●
Silicone oil	â€”	20 Å°C	●
Sodium carbonate, aqueous	â€”	20 Å°C	●
Sodium chloride, aqueous	â€”	20 Å°C	●
Sodium hydrogen sulfite	â€”	20 Å°C	●
Sodium hydroxide solution (60%)	60%	20 Å°C	●
Sodium hydroxide solution (caustic soda)	15%	20 Å°C	●
Sodium thiosulfate	â€”	20 Å°C	●

Kemikalie	Pitoisuus	Temp.	Beständighet
Sulphuric acid	96%	20 Å°C	●
Tetrahydrofuran (THF)	100%	20 Å°C	●
Toluene	100%	20 Å°C	●
Transformer oil	â€”	20 Å°C	●
Trichloroethylene	100%	20 Å°C	●
Vinegar, standard	5-10%	20 Å°C	●
Water	â€”	20 Å°C	●
Xylene	â€”	20 Å°C	●