



# PMMA E 400/390x2000 mm l  pin  kyv  

Artikelnr P1200765

Best  ndig Delvis best  ndig Ej best  ndig

| Kemikalie               | Pitoisuus | Temp.  | Best  ndighet     |
|-------------------------|-----------|--------|-------------------|
| Acetic acid             | 100%      | 20   C | Ej best  ndig     |
| Acetone                 | 100%      | 20   C | Ej best  ndig     |
| Ammonia                 | conc.     | 20   C | Best  ndig        |
| Amyl alcohol            |           | 20   C | Ej best  ndig     |
| Apple juice             |           | 20   C | Best  ndig        |
| Benzene                 |           | 20   C | Ej best  ndig     |
| Butyl acetate           |           | 20   C | Ej best  ndig     |
| Calcium chloride        |           | 20   C | Best  ndig        |
| Carbon disulphide       | 100%      | 20   C | Ej best  ndig     |
| Carbon tetrachloride    |           | 20   C | Ej best  ndig     |
| Chlorine gas            | 100%      | 20   C | Delvis best  ndig |
| Chloroform              |           | 20   C | Ej best  ndig     |
| Citric acid             | 10%       | 20   C | Best  ndig        |
| Cresol                  |           | 20   C | Ej best  ndig     |
| Cyclohexanone           | 100%      | 20   C | Ej best  ndig     |
| Cyclohexene             | 100%      | 20   C | Ej best  ndig     |
| Diesel                  |           | 20   C | Best  ndig        |
| Diethylene oxide        |           | 20   C | Ej best  ndig     |
| Ethyl acetate           | 100%      | 20   C | Ej best  ndig     |
| Ethyl alcohol (ethanol) | 96%       | 20   C | Best  ndig        |
| Ethylene chloride       | 100%      | 20   C | Ej best  ndig     |
| Formaldehyde, aqueous   | 40%       | 20   C | Best  ndig        |
| Formic acid             | 10%       | 20   C | Ej best  ndig     |
| Fuel oil                |           | 20   C | Best  ndig        |
| Fuel, aromatic free     |           | 20   C | Best  ndig        |
| Glycerine               | 100%      | 20   C | Best  ndig        |
| Glycol                  | 100%      | 20   C | Best  ndig        |

| Kemikalie                                | Pitoisuus   | Temp.  | Beständighet |
|------------------------------------------|-------------|--------|--------------|
| Heptane                                  | 100%        | 20 Å°C | ●            |
| Hydrochloric acid                        | 10%         | 20 Å°C | ●            |
| Hydrochloric acid (concentrated)         | conc.       | 20 Å°C | ●            |
| Hydrofluoric acid                        | 40%         | 20 Å°C | ●            |
| Hydrogen peroxide                        | 10%         | 20 Å°C | ●            |
| Hydrogen sulfide, aqueous                | â€”         | 20 Å°C | ●            |
| Isopropyl alcohol                        | 100%        | 20 Å°C | ●            |
| Linseed oil                              | â€”         | 20 Å°C | ●            |
| Mercurochrome                            | â€”         | 20 Å°C | ●            |
| Methyl alcohol (methanol)                | 100%        | 20 Å°C | ●            |
| Methyl ethyl ketone (MEK)                | 100%        | 20 Å°C | ●            |
| Methylene chloride                       | 100%        | 20 Å°C | ●            |
| Milk                                     | â€”         | 20 Å°C | ●            |
| Mineral oils, aromatic free              | â€”         | 20 Å°C | ●            |
| Nitric acid                              | 10%         | 20 Å°C | ●            |
| Nitric acid (50%)                        | 50%         | 20 Å°C | ●            |
| Nitrobenzene                             | â€”         | 20 Å°C | ●            |
| Oxalic acid                              | â€”         | 20 Å°C | ●            |
| Ozone (gas)                              | â‰ƒ 0.5 ppm | 20 Å°C | ●            |
| Paraffin oil                             | 100%        | 20 Å°C | ●            |
| Perchloroethylene                        | â€”         | 20 Å°C | ●            |
| Petroleum                                | 100%        | 20 Å°C | ●            |
| Petroleum ether                          | 100%        | 20 Å°C | ●            |
| Phenol, aqueous                          | ca. 9%      | 20 Å°C | ●            |
| Phosphoric acid                          | 50%         | 20 Å°C | ●            |
| Potassium hydroxide solution             | 50%         | 20 Å°C | ●            |
| Premium fuel                             | â€”         | 20 Å°C | ●            |
| Silicone oil                             | â€”         | 20 Å°C | ●            |
| Sodium carbonate, aqueous                | â€”         | 20 Å°C | ●            |
| Sodium chloride, aqueous                 | â€”         | 20 Å°C | ●            |
| Sodium hydrogen sulfite                  | â€”         | 20 Å°C | ●            |
| Sodium hydroxide solution (60%)          | 60%         | 20 Å°C | ●            |
| Sodium hydroxide solution (caustic soda) | 15%         | 20 Å°C | ●            |
| Sodium thiosulfate                       | â€”         | 20 Å°C | ●            |

| Kemikalie             | Pitoisuus | Temp.  | Beständighet |
|-----------------------|-----------|--------|--------------|
| Sulphuric acid        | 96%       | 20 Å°C | ●            |
| Tetrahydrofuran (THF) | 100%      | 20 Å°C | ●            |
| Toluene               | 100%      | 20 Å°C | ●            |
| Transformer oil       | â€”       | 20 Å°C | ●            |
| Trichloroethylene     | 100%      | 20 Å°C | ●            |
| Vinegar, standard     | 5-10%     | 20 Å°C | ●            |
| Water                 | â€”       | 20 Å°C | ●            |
| Xylene                | â€”       | 20 Å°C | ●            |