



# POM C FG 200/160x1000 mm luonnollinen

Artikelnr P1007452

Beständig Delvis beständig Ej beständig

| Kemikalie                             | Pitoisuus | Temp.  | Beständighet |
|---------------------------------------|-----------|--------|--------------|
| 1,4-Dioxane                           | 100%      | 20 Å°C |              |
| 2-Hydroxypropionic acid (lactic acid) | 90%       | 20 Å°C |              |
| Acetic acid                           | 100%      | 20 Å°C |              |
| Acetone                               | 100%      | 20 Å°C |              |
| Ammonia                               | conc.     | 20 Å°C |              |
| Ammonium chloride                     | â€”       | 20 Å°C |              |
| Amyl alcohol                          | â€”       | 20 Å°C |              |
| Apple juice                           | â€”       | 20 Å°C |              |
| Benzene                               | â€”       | 20 Å°C |              |
| Bleaching solution                    | 12.5 cl   | 20 Å°C |              |
| Boric acid                            | 100%      | 20 Å°C |              |
| Brake fluid                           | â€”       | 20 Å°C |              |
| Butyl acetate                         | â€”       | 20 Å°C |              |
| Calcium chloride                      | â€”       | 20 Å°C |              |
| Carbon disulphide                     | 100%      | 20 Å°C |              |
| Carbon tetrachloride                  | â€”       | 20 Å°C |              |
| Chlorobenzene                         | 100%      | 20 Å°C |              |
| Chloroform                            | â€”       | 20 Å°C |              |
| Citric acid                           | 10%       | 20 Å°C |              |
| Cyclohexanone                         | 100%      | 20 Å°C |              |
| Cyclohexene                           | 100%      | 20 Å°C |              |
| Diesel                                | â€”       | 20 Å°C |              |
| Diethylene oxide                      | â€”       | 20 Å°C |              |
| Ethyl acetate                         | 100%      | 20 Å°C |              |
| Ethyl alcohol (ethanol)               | 96%       | 20 Å°C |              |
| Food oil                              | â€”       | 20 Å°C |              |
| Formaldehyde, aqueous                 | 40%       | 20 Å°C |              |

| Kemikalie                        | Pitoisuus  | Temp.  | Beständighet |
|----------------------------------|------------|--------|--------------|
| Formic acid                      | 10%        | 20 Å°C | ●            |
| Frost protection agent           | â€”        | 20 Å°C | ●            |
| Fuel oil                         | â€”        | 20 Å°C | ●            |
| Fuel, aromatic free              | â€”        | 20 Å°C | ●            |
| Glycerine                        | 100%       | 20 Å°C | ●            |
| Glycol                           | 100%       | 20 Å°C | ●            |
| Heptane                          | 100%       | 20 Å°C | ●            |
| Hydrochloric acid                | 10%        | 20 Å°C | ●            |
| Hydrochloric acid (concentrated) | conc.      | 20 Å°C | ●            |
| Hydrofluoric acid                | 40%        | 20 Å°C | ●            |
| Hydrogen peroxide                | 10%        | 20 Å°C | ●            |
| Hydrogen sulfide, aqueous        | â€”        | 20 Å°C | ●            |
| Isopropyl alcohol                | 100%       | 20 Å°C | ●            |
| Linseed oil                      | â€”        | 20 Å°C | ●            |
| Mercurochrome                    | â€”        | 20 Å°C | ●            |
| Methyl alcohol (methanol)        | 100%       | 20 Å°C | ●            |
| Methyl ethyl ketone (MEK)        | 100%       | 20 Å°C | ●            |
| Methylene chloride               | 100%       | 20 Å°C | ●            |
| Milk                             | â€”        | 20 Å°C | ●            |
| Mineral oils (aromatic free)     | â€”        | 20 Å°C | ●            |
| Nitric acid                      | 10%        | 20 Å°C | ●            |
| Nitric acid (50%)                | 50%        | 20 Å°C | ●            |
| Nitrobenzene                     | â€”        | 20 Å°C | ●            |
| Oxalic acid                      | â€”        | 20 Å°C | ●            |
| Ozone (gas)                      | â‰‰0.5 ppm | 20 Å°C | ●            |
| Paraffin oil                     | 100%       | 20 Å°C | ●            |
| Perchloroethylene                | â€”        | 20 Å°C | ●            |
| Petroleum                        | 100%       | 20 Å°C | ●            |
| Petroleum ether                  | 100%       | 20 Å°C | ●            |
| Phenol, aqueous                  | ca. 9%     | 20 Å°C | ●            |
| Phosphoric acid                  | 50%        | 20 Å°C | ●            |
| Potassium hydroxide solution     | 50%        | 20 Å°C | ●            |
| Premium fuel                     | â€”        | 20 Å°C | ●            |
| Propyl alcohol                   | â€”        | 20 Å°C | ●            |
| Silicone oil                     | â€”        | 20 Å°C | ●            |

| Kemikalie                       | Pitoisuus | Temp.  | Beständighet |
|---------------------------------|-----------|--------|--------------|
| Sodium carbonate, aqueous       | â€”       | 20 Â°C | ●            |
| Sodium chloride, aqueous        | â€”       | 20 Â°C | ●            |
| Sodium hydrogen sulfite         | â€”       | 20 Â°C | ●            |
| Sodium hydroxide solution (15%) | 15%       | 20 Â°C | ●            |
| Sodium hydroxide solution (60%) | 60%       | 20 Â°C | ●            |
| Sodium nitrate, aqueous         | â€”       | 20 Â°C | ●            |
| Sulphuric acid                  | 96%       | 20 Â°C | ●            |
| Tetrahydrofuran (THF)           | 100%      | 20 Â°C | ●            |
| Toluene                         | 100%      | 20 Â°C | ●            |
| Transformer oil                 | â€”       | 20 Â°C | ●            |
| Trichloroethylene               | 100%      | 20 Â°C | ●            |
| Vinegar, standard               | 5-10%     | 20 Â°C | ●            |
| Water                           | â€”       | 20 Â°C | ●            |
| Xylene                          | â€”       | 20 Â°C | ●            |