



# PP-C 2000x1000x12 mm harmaa

Artikelnr P2201622

## 1. Tekniskt datablad

| Egenskap                                      | Värde            | Enhet               | Standard          |
|-----------------------------------------------|------------------|---------------------|-------------------|
| Tiäys                                         | 0.9              | g/cm³               | DIN EN ISO 1183-1 |
| Venymisrajan jännitys                         | 24               | MPa                 | DIN EN ISO 527    |
| Joustavuusmoduli (vetolujuus)                 | 1241.2           | MPa                 | DIN EN ISO 527    |
| Murtovenymä                                   | 50               | %                   | DIN EN ISO 527    |
| Sulamispiste                                  | 164              | °C                  | ISO 11357-3       |
| Maksimaalinen käyttölämpötila (lyhytaikainen) | 116              | °C                  |                   |
| Maksimi käyttölämpötila                       | 75               | °C                  |                   |
| Alin lämpötila                                | -23              | °C                  |                   |
| Vicat-pehmenemislämpötila (VST/B/50)          | 87               | °C                  | DIN EN ISO 306    |
| Dielektrinen voimakkuus                       | 40               | kV/mm               | IEC 60243         |
| Tilavuusresistanssi                           | 10 <sup>14</sup> | Ω·cm                | DIN EN 62631-3-1  |
| Dielektrinen vakio (1 MHz)                    | 2.48             | -                   | IEC 60250         |
| Dielektrinen hajoamiskerroin (1 MHz)          | 0.0              | -                   | IEC 60250         |
| Dielektrinen hajoamiskerroin (100 Hz)         | 0.0              | -                   | IEC 60250         |
| Lämmönjohtavuus                               | 0.2              | W/(m·K)             | DIN 52612-1       |
| Pintaresistanssi                              | 10 <sup>14</sup> | Ω                   | DIN EN 62631-3-2  |
| Vertailukemisindeksi (CTI)                    | 600              | V                   | IEC 60112         |
| Imeytymisen maksimointi                       | 0.1              | %                   | DIN EN ISO 62     |
| Vesihaku kyllästymiseen                       | 0.1              | %                   | DIN EN ISO 62     |
| Särkyäkesto (Charpy)                          | 4                | kJ/m²               | DIN EN ISO 179    |
| Lämpölaajenemiskerroin                        | 0.0              | 10 <sup>-6</sup> /K | DIN 53752         |
| Kovuus Shore D                                | 67.25            | ° Shore D           | DIN EN ISO 868    |
| Kulmapaineen kovuus                           | 50               | MPa                 | DIN EN ISO 2039-1 |

## 2. Kemisk beständighet

Beständig Delvis beständig Ej beständig

| Kemikalie               | Konc. | Resultat    |
|-------------------------|-------|-------------|
| 1,4-Dioxane             | 100   | <div></div> |
| 2-Hydroxypropionic Acid | 90    | <div></div> |
| Acetic Acid             | 100   | <div></div> |
| Acetone                 | 100   | <div></div> |
| Ammonia                 | â€”   | <div></div> |
| Ammonium Chloride       | â€”   | <div></div> |
| Amyl Alcohol            | â€”   | <div></div> |
| Apple Juice             | â€”   | <div></div> |
| Benzene                 | â€”   | <div></div> |
| Bleaching Solution      | â€”   | <div></div> |
| Boric Acid              | 100   | <div></div> |
| Brake Fluid             | â€”   | <div></div> |
| Butyl Acetate           | â€”   | <div></div> |
| Calcium Chloride        | â€”   | <div></div> |
| Carbon Disulfide        | 100   | <div></div> |
| Carbon Tetrachloride    | â€”   | <div></div> |
| Chlorine (gas)          | 100   | <div></div> |
| Chlorobenzene           | 100   | <div></div> |
| Chloroform              | â€”   | <div></div> |
| Citric Acid             | 10    | <div></div> |
| Cresol                  | â€”   | <div></div> |
| Cyclohexanone           | 100   | <div></div> |
| Cyclohexene             | 100   | <div></div> |
| Diesel Fuel             | â€”   | <div></div> |
| Diethylene Oxide        | â€”   | <div></div> |
| Ethyl Acetate           | 100   | <div></div> |
| Ethyl Alcohol           | 96    | <div></div> |
| Ethylene Chloride       | 100   | <div></div> |
| Food Oil                | â€”   | <div></div> |
| Formaldehyde, aqueous   | 40    | <div></div> |
| Formic Acid             | 10    | <div></div> |
| Frost Protection Agent  | â€”   | <div></div> |
| Fuel, aromatic free     | â€”   | <div></div> |
| Glycerine               | 100   | <div></div> |

| Kemikalie                          | Konc.       | Resultat |
|------------------------------------|-------------|----------|
| Glycol                             | 100         | ●        |
| Heating Oil                        | â€”         | ●        |
| Heptane                            | 100         | ●        |
| Hydrochloric Acid                  | 10          | ●        |
| Hydrochloric Acid (concentrated)   | â€”         | ●        |
| Hydrofluoric Acid                  | 40          | ●        |
| Hydrogen Peroxide                  | 10          | ●        |
| Hydrogen Sulfide, aqueous solution | â€”         | ●        |
| Isopropyl Alcohol                  | 100         | ●        |
| Linseed Oil                        | â€”         | ●        |
| Mercurochrome                      | â€”         | ●        |
| Methyl Alcohol                     | 100         | ●        |
| Methyl Ethyl Ketone (MEK)          | 100         | ●        |
| Methylene Chloride                 | 100         | ●        |
| Milk                               | â€”         | ●        |
| Mineral Oils (aromatic free)       | â€”         | ●        |
| Nitric Acid                        | 50          | ●        |
| Nitric Acid                        | 10          | ●        |
| Nitrobenzene                       | â€”         | ●        |
| Oxalic Acid                        | â€”         | ●        |
| Ozone Gas                          | â‰¥ 0.5 ppm | ●        |
| Paraffine Oil                      | 100         | ●        |
| Perchloroethylene                  | â€”         | ●        |
| Petroleum                          | 100         | ●        |
| Petroleum Ether                    | 100         | ●        |
| Phenol, aqueous                    | ca. 9       | ●        |
| Phosphoric Acid                    | 50          | ●        |
| Potassium Hydroxide liquor         | 50          | ●        |
| Premium Fuel                       | â€”         | ●        |
| Propyl Alcohol                     | â€”         | ●        |
| Pyridine                           | â€”         | ●        |
| Silicone Oil                       | â€”         | ●        |
| Sodium Carbonate, aqueous          | â€”         | ●        |
| Sodium Chloride, aqueous           | â€”         | ●        |
| Sodium Hydrogen Sulfite            | â€”         | ●        |

| Kemikalie               | Konc.  | Resultat |
|-------------------------|--------|----------|
| Sodium Hydroxide liquor | 15     | ●        |
| Sodium Hydroxide liquor | 60     | ●        |
| Sodium Nitrate, aqueous | â€”    | ●        |
| Sodium Thiosulfate      | â€”    | ●        |
| Sulfuric Acid           | 96     | ●        |
| Tetrahydrofuran (THF)   | 100    | ●        |
| Toluene                 | 100    | ●        |
| Transformer Oil         | â€”    | ●        |
| Trichloroethylene       | 100    | ●        |
| Vinegar, standard       | 5 - 10 | ●        |
| Water                   | â€”    | ●        |
| Xylene                  | â€”    | ●        |